

Australian Standard<sup>®</sup>

---

**METHODS FOR THE ANALYSIS OF  
ZIRCON SAND CONCENTRATES**

**Part 9—DETERMINATION OF  
MAGNESIUM CONTENT  
(FLAME ATOMIC  
ABSORPTION  
SPECTROMETRIC  
METHOD)**

---

This Australian standard was prepared by Committee MN/4, Heavy Mineral Sands. It was approved on behalf of the Council of the Standards Association of Australia on 28 June 1983 and published on 5 September 1983.

---

The following interests are represented on Committee MN/4:

Australian Foundry Institute  
Australian Mineral Development Laboratories  
Chamber of Mines of W.A. (Incorporated)  
CSIRO, Division of Mineral Chemistry  
CSIRO, Division of Mineralogy  
Mineral Sands Producers' Association

---

*Review of Australian Standards.* To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

---

## PREFACE

This standard was prepared by the Association's Committee on Heavy Mineral Sands under the direction of the Minerals Standards Committee in order to provide a method for use in the settling of disputes arising from discrepancies between buyer and seller in the determination of magnesium in zircon sand concentrates.

The committee organized an inter-laboratory test program to obtain information on the repeatability and reproducibility of the method. Laboratories from the following organizations participated in the test program to obtain the results given in Table 1:

ARM Laboratories  
Associated Minerals Consolidated Limited, Capel  
Australian Laboratory Services  
Laporte Australia Ltd  
Mineral Deposits Ltd

First published . . . . . 1983
--------------------------------

*This standard was issued in draft form for comment as DR 82146.*

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## STANDARDS ASSOCIATION OF AUSTRALIA

## Australian Standard

## METHODS FOR THE ANALYSIS OF ZIRCON SAND CONCENTRATES

## PART 9—DETERMINATION OF MAGNESIUM CONTENT (FLAME ATOMIC ABSORPTION SPECTROMETRIC METHOD)

**1 SCOPE.** This standard sets out a method for the determination of magnesium in zircon sand concentrates using flame atomic absorption spectrometry.

**2 APPLICATION.** The method is applicable to zircon sand concentrates containing between 0.001 percent and 0.2 percent MgO.

**3 REFERENCED DOCUMENTS.** The following standards are referred to in this standard:

AS 2134 Code of Practice for the Chemical Analysis of Materials by Flame Atomic Absorption Spectroscopy

AS 2162 Code of Practice for the Use of Volumetric Glassware

BS 4237 Report on Reproducibility of Methods of Chemical Analysis Used in the Iron and Steel Industry

**4 PRINCIPLE.** Decomposition of the test portion by fusion with sodium tetrafluoroborate. Dissolution of the melt with sulphuric acid and hydrofluoric acid and removal of fluoride and silica by fuming. Aspiration of the solution into a nitrous oxide/acetylene flame and measurement of the atomic absorption at 285.2 nm.

**5 REAGENTS.**

**5.1 General.** During the analysis use only reagents of recognized analytical reagent grade and only distilled water or water of equivalent purity.

**5.2 Solids.**

**5.2.1** Sodium tetrafluoroborate ( $\text{NaBF}_4$ ).

NOTE: Sodium tetrafluoroborate of a suitable analytical reagent grade is commercially available. Alternatively a material with low impurity level may be prepared from the laboratory reagent grade by recrystallization (see Appendix A).

**5.2.2** Zirconium dioxide ( $\text{ZrO}_2$ ). Zirconium dioxide powder containing less than 0.0005 percent MgO.

**5.3 Solutions.**

**5.3.1** Sulphuric acid ( $\rho_{20}$  1840  $\text{kg/m}^3$ ).

**5.3.2** Hydrofluoric acid ( $\rho_{20}$  1150  $\text{kg/m}^3$ ).

**5.3.3** Nitric acid ( $\rho_{20}$  1420  $\text{kg/m}^3$ ), diluted 1 + 4.

**5.4 Standard Magnesium Solutions.**

**5.4.1** *Standard solution A* (1 mL  $\equiv$  250  $\mu\text{g}$  Mg). Dissolve 0.2500 g of magnesium metal ribbon (> 99.5 percent Mg) in 25 mL of nitric acid (5.3.3). Transfer to a 1 L volumetric flask, dilute to volume and mix.

**5.4.2** *Standard solution B* (1 mL  $\equiv$  5  $\mu\text{g}$  Mg). Pipette 10.00 mL of solution A (5.4.1) into a 500 mL volumetric flask. Dilute to volume and mix.

NOTE: This solution should be freshly prepared for each series of determinations.

**6 APPARATUS.**

**6.1 Ordinary laboratory apparatus.**

**6.2 Glassware.** All glassware should be cleaned by soaking with chromic acid or nitric acid (diluted 1 + 2) then rinsing well with tap water and finally rinsing with distilled water.

**6.3 Volumetric glassware.** Grade A volumetric glassware complying with the relevant Australian standards to be used in accordance with AS 2162.

**6.4 Platinum, or preferably platinum/gold, crucibles or basins.** With a minimum capacity of 25 mL.