

Australian Standard<sup>®</sup>

**Zinc sulfide concentrates—Chemical  
analysis**

**Part 2: Determination of zinc—Ion-  
exchange/EDTA titrimetric method**



This Australian Standard® was prepared by Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 24 January 2008.  
This Standard was published on 12 March 2008.

---

The following are represented on Committee MN-005:

- CSIRO Minerals
- Minerals Council of Australia

Additional Interests:

- Minerals industry analytical laboratories
- 

This Standard was issued in draft form for comment as DR 07036.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

---

### **Keeping Standards up-to-date**

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting [www.standards.org.au](http://www.standards.org.au)

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.org.au](mailto:mail@standards.org.au), or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

---

Australian Standard<sup>®</sup>

**Zinc sulfide concentrates—Chemical analysis**

**Part 2: Determination of zinc—Ion-exchange/EDTA titrimetric method**

Originated as AS 2678.2—1999.  
Second edition 2008.

**COPYRIGHT**

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia  
ISBN 0 7337 8587 5

## PREFACE

This Standard was prepared by the Standards Australia Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates, to supersede AS 2678.2—1999.

The objective of this Standard is to provide those responsible for the analysis of zinc concentrates with a standardized method of determining zinc, supported by precision data obtained from an interlaboratory test program.

The objective of this revision is to adopt the latest edition of the corresponding International Standard.

This Standard is identical with, and has been reproduced from ISO 12739:2006, *Zinc sulfide concentrates—Determination of zinc—Ion-exchange/EDTA titrimetric method*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number appears on the cover and title page while the International Standard number appears only on the cover.
- (b) In the source text ‘this International Standard’ should read ‘this Australian Standard’.
- (c) A full point substitutes for a comma when referring to a decimal marker.
- (d) Substitute ‘L’ for ‘l’ as the unit for litres.

References to International Standards should be replaced by references to Australian Standards, as follows:

<i>Reference to International Standard</i>	<i>Australian Standard</i>
ISO	AS
9599 Copper, lead and zinc sulfide concentrates—Determination of hygroscopic moisture in the analysis sample—Gravimetric method	2816 Copper, lead and zinc sulfide concentrates—Determination of hygroscopic moisture in the analysis sample—Gravimetric method

Only international references that have been adopted as Australian Standards have been listed.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annex to which they apply. A ‘normative’ annex is an integral part of a Standard, whereas an ‘informative’ annex is only for information and guidance.

## CONTENTS

	<i>Page</i>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Principle</b> .....	<b>1</b>
<b>4 Reagents</b> .....	<b>1</b>
<b>5 Apparatus</b> .....	<b>3</b>
<b>6 Sample</b> .....	<b>3</b>
<b>6.1 Test sample</b> .....	<b>3</b>
<b>6.2 Test portion</b> .....	<b>3</b>
<b>7 Procedure</b> .....	<b>3</b>
<b>7.1 Number of determinations</b> .....	<b>3</b>
<b>7.2 Blank test</b> .....	<b>4</b>
<b>7.3 Dissolution of test portion</b> .....	<b>4</b>
<b>7.4 Preparation of the ion-exchange column</b> .....	<b>4</b>
<b>7.5 Adsorption of zinc on ion-exchange column</b> .....	<b>5</b>
<b>7.6 Elution of zinc from ion-exchange column</b> .....	<b>5</b>
<b>7.7 Titration</b> .....	<b>5</b>
<b>7.8 Determination of the titration factor of the EDTA standard volumetric solution</b> .....	<b>5</b>
<b>8 Expression of results</b> .....	<b>6</b>
<b>9 Precision</b> .....	<b>7</b>
<b>9.1 Expression of precision</b> .....	<b>7</b>
<b>9.2 Procedure for obtaining the final result</b> .....	<b>7</b>
<b>9.3 Between-laboratories precision</b> .....	<b>7</b>
<b>9.4 Check of trueness</b> .....	<b>8</b>
<b>10 Test report</b> .....	<b>9</b>
<b>Annex A (normative) Ion-exchange resins and columns</b> .....	<b>10</b>
<b>Annex B (normative) Procedure for the preparation and determination of the mass of a predried test portion</b> .....	<b>12</b>
<b>Annex C (normative) Determination of cadmium by atomic absorption spectrometry</b> .....	<b>14</b>
<b>Annex D (normative) Flowchart of the procedure for the acceptance of analytical values for test samples</b> .....	<b>16</b>
<b>Annex E (informative) Effect of potentially interfering elements</b> .....	<b>17</b>
<b>Annex F (informative) Derivation of precision equations</b> .....	<b>18</b>
<b>Bibliography</b> .....	<b>23</b>

## AUSTRALIAN STANDARD

**Zinc sulfide concentrates—Chemical analysis**

## Part 2:

## Determination of zinc—Ion-exchange/EDTA titrimetric method

**WARNING** — This International Standard may involve hazardous materials, operations and equipment. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

**1 Scope**

This International Standard specifies an ion-exchange/EDTA titrimetric method for the determination of the mass fraction of zinc in zinc concentrates. The method is applicable to zinc sulfide concentrates having a mass fraction of zinc in the range from 11 % to 62 %.

**2 Normative references**

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — One-mark pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4787, *Laboratory glassware — Volumetric glassware — Methods for use and testing of capacity*

ISO 9599, *Copper, lead and zinc sulfide concentrates — Determination of hygroscopic moisture in the analysis sample — Gravimetric method*

**3 Principle**

The test portion of zinc concentrate is dissolved in hydrochloric, nitric and sulfuric acids. The acidity is adjusted to about 2 mol/l with respect to hydrochloric acid. Zinc is adsorbed on a strongly basic anion-exchange resin. Some interfering ions are removed by elution with 2 mol/l dilute hydrochloric acid. Zinc is eluted with an ammonia/ammonium chloride solution. Zinc is determined in the eluate by titration with EDTA at a pH of approximately 5,6 using xylenol-orange indicator.

**4 Reagents**

During the analysis, only reagents of recognized analytical grade and water that complies with grade 2 of ISO 3696 shall be used.

**4.1 Zinc**, 99,99 % minimum purity, free from oxide prior to use.