

Australian Standard™

**Zinc and zinc alloys—Determination
of impurities and alloying elements—
Atomic emission spectrometric method**

This Australian Standard was prepared by Committee CH/10, Analysis of Metals. It was approved on behalf of the Council of Standards Australia on 29 October 1999 and published on 17 January 2000.

The following interests are represented on Committee CH/10:

Australasian Institute of Mining and Metallurgy

Australian Aluminium Council

Australian Industry Group

Australian Railway Association

National Association of Testing Authorities, Australia

University of New South Wales

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for the improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, PO Box 1055, Strathfield, NSW 2135.

Australian Standard™

**Zinc and zinc alloys— Determination
of impurities and alloying elements—
Atomic emission spectrometric method**

First published as AS 4699—2000.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
PO Box 1055, Strathfield, NSW 2135, Australia

ISBN 0 7337 3051 5

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee CH/10, Analysis of Metals. It is the result of a consensus among the representatives on the Joint Committee to produce it as an Australian Standard.

The objective of this Standard is to provide a method for the determination of impurities and alloying elements in zinc and zinc alloys by arc/spark atomic emission spectrometry.

The term 'informative' has been used in this Standard to define the application of the appendix to which it applies. An 'informative' appendix is only for information and guidance.



CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	4
3 PRINCIPLE	4
4 DEFINITIONS	4
5 APPARATUS	4
6 SAMPLING	4
7 PROCEDURE	4
8 PRECISION	7
9 ACCEPTANCE OF ANALYTICAL RESULTS	7
10 TEST REPORT	8
APPENDIX A FLOWSHEET ON THE PROCEDURE FOR THE ACCEPTANCE OF ANALYTICAL VALUES FOR TEST SAMPLES.....	9

STANDARDS AUSTRALIA

Australian Standard

Zinc and zinc alloys— Determination of impurities and alloying elements— Atomic emission spectrometric method

1 SCOPE

This Standard specifies a method for the determination of impurities and alloying elements in zinc and zinc alloys by arc/spark atomic emission spectrometry. The method is applicable to the following elements in the concentration ranges shown below:

Element	Concentration range %
Aluminium	0.0001 – 30
Antimony	0.002 – 1.3
Arsenic	0.004 – 1.7
Bismuth	0.0001 – 0.02
Cadmium	0.0001 – 2.0
Cerium	0.0002 – 0.1
Chromium	0.0001 – 0.2
Cobalt	0.0003 – 0.3
Copper	0.0001 – 10
Indium	0.0001 – 0.3
Iron	0.0002 – 1.3
Lanthanum	0.0002 – 0.1
Lead	0.0002 – 1.5
Magnesium	0.0002 – 3.0
Manganese	0.0003 – 0.2
Nickel	0.0005 – 1.0
Silicon	0.0003 – 0.5
Silver	0.0001 – 0.1
Sodium	0.0001 – 0.1
Thallium	0.0001 – 0.1
Tin	0.0002 – 0.5
Titanium	0.0001 – 0.2
Vanadium	0.0003 – 0.2