

Australian Standard[®]

**ALUMINIUM ORES—
DETERMINATION OF ALUMINIUM,
SILICON, IRON, TITANIUM AND
PHOSPHORUS CONTENTS—
WAVELENGTH DISPERSIVE
X-RAY FLUORESCENCE
SPECTROMETRIC METHOD**

This Australian standard was prepared by Committee MN/3, Aluminium Ores. It was approved on behalf of the Council of the Standards Association of Australia on 6 July 1982 and published on 18 October 1982.

The following interests were represented on the committee responsible for the preparation of this standard:

- CSIRO, Division of Mineral Chemistry
- CSIRO, Division of Soils
- Producers of aluminium ores
- Processors of aluminium ores
- Producers of aluminium products

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

| |
|--------------------------------|
| First published 1982 |
|--------------------------------|

This standard was issued in draft form for comment as DR 81218.

PREFACE

This standard was prepared by the Association's Committee on Aluminium Ores under the direction of the Minerals Standards Committee. It is the first standard of its type in which an absolute method has been prepared for the analysis of a material by X-ray fluorescence spectrometry.

X-ray fluorescence spectrometry is in common use for in-house control of the quality of aluminium ore. The method contained in this standard is similar to that used in many laboratories analysing aluminium ores by X-ray fluorescence spectrometry.

The standard has been prepared to enable X-ray fluorescence methods to be specified in contracts.

The results of the test program have shown that the X-ray fluorescence method compares favourably with the results obtained using traditional wet chemical methods.

The committee organized an inter-laboratory test program to obtain information on the repeatability and reproducibility of the method. The following laboratories participated in the test program:

Analabs Pty Ltd
 The Australian Mineral Development Laboratories
 Australian National University, School of Geology
 The Broken Hill Proprietary Co. Ltd, Central Research Laboratories
 Bureau of Mineral Resources, Geology and Geophysics
 CSIRO, Division of Soils
 CSR Central Laboratory
 Government Chemical Laboratories, Western Australia
 Macquarie University, School of Earth Sciences
 Queensland Alumina Limited
 SGS Australia Ltd
 University of Adelaide, School of Geology
 The Zinc Corporation, Limited

CONTENTS

| | <i>Page</i> |
|---|-------------|
| CLAUSE | |
| 1 Scope and Application | 4 |
| 2 Referenced Documents | 4 |
| 3 Principle | 4 |
| 4 Reagents and Materials | 4 |
| 5 Apparatus | 6 |
| 6 Sampling and Samples | 6 |
| 7 Preparation of Specimens Including Loss on Fusion Determination . . . | 6 |
| 8 X-ray Fluorescence Measurement of Specimens | 10 |
| 9 Preliminary Check and Calculations | 11 |
| 10 Calculation of Results | 13 |
| 11 General Treatment of Results | 15 |
| 12 Test Report | 16 |
| APPENDICES | |
| A Preparation of a Monitor Specimen | 17 |
| B Computer Program for Data Manipulation | 19 |

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

ALUMINIUM ORES—DETERMINATION OF ALUMINIUM, SILICON, IRON, TITANIUM AND PHOSPHORUS CONTENTS—WAVELENGTH DISPERSIVE X-RAY FLUORESCENCE SPECTROMETRIC METHOD

1 SCOPE AND APPLICATION.

1.1 Scope. This standard sets out a method for the determination of the contents of aluminium, silicon, iron, titanium, and phosphorus (expressed as the oxides Al_2O_3 , SiO_2 , Fe_2O_3 , TiO_2 , and P_2O_5) in aluminium ores by wavelength dispersive X-ray fluorescence spectrometry. The method has been designed to cope with the high and variable loss on ignition of aluminium ores.

1.2 Application. The method is applicable to all normal aluminium ores regardless of mineralogical type. The concentration range covered for each of the components is given in Table 1.

TABLE 1
RANGE OF APPLICATION OF THE METHOD

| Component | Concentration range percent |
|-------------------------|-----------------------------|
| Al_2O_3 | 30—65 |
| SiO_2 | 1—25 |
| Fe_2O_3 | 2—50 |
| TiO_2 | 0.5—8 |
| P_2O_5 | 0.02—5 |
| Loss on ignition | 10—35 |

2 REFERENCED DOCUMENTS. The following documents are referred to in this standard:

| | |
|-------------|---|
| AS 2563 | Wavelength Dispersive X-ray Fluorescence Spectrometers—Methods of Test for Determination of Precision |
| AS XXXX | Aluminium Ores—Determination of Hygroscopic Moisture in Analytical Samples—Gravimetric Method* |
| BS 4237 | Report on Reproducibility of Methods of Chemical Analysis Used in the Iron and Steel Industry |
| ISO/DP 6137 | Aluminium Ores—Methods of Sampling |
| ISO/DP 6140 | Aluminium Ores—Preparation of Samples |

3 PRINCIPLE. The specimen on which X-ray fluorescence measurements are made is prepared by incorporating the test portion of the aluminium ore sample, via fusion, into a borate glass disc using a quench pressing procedure. By using such a specimen, particle size effects, which constitute a major problem when a compacted test portion (briquette) is used, are eliminated.

X-ray fluorescence measurements are based on the 'line only' principle. Backgrounds are not measured on each specimen, but are determined on several blank specimens at the line positions.

Calibration is carried out using pure chemicals. Final results are obtained after matrix corrections for interelement effects.

Hygroscopic moisture is determined separately on the laboratory sample in accordance with AS XXXX, but loss on fusion is determined as part of the preparation of the glass specimen that is used for X-ray fluorescence analysis.

4 REAGENTS AND MATERIALS.

4.1 General. During the analysis, only reagents of recognized high purity shall be used.

NOTE: Some reagents of sufficient purity, in particular aluminium oxide, are undesirable because of their hygroscopic nature. Select a reagent with a very low water absorption capacity.

4.2 Silicon dioxide (SiO_2), nominally 99.999 percent SiO_2 .

4.3 Aluminium oxide (Al_2O_3), nominally 99.999 percent Al_2O_3 .

4.4 Synthetic Calibration Sample.**4.4.1 Reagents.**

4.4.1.1 Silicon dioxide (SiO_2) (4.2).

4.4.1.2 Aluminium oxide (Al_2O_3) (4.3).

4.4.1.3 Iron(III) oxide (Fe_2O_3), nominally 99.999 percent Fe_2O_3 .

4.4.1.4 Titanium dioxide (TiO_2), nominally 99.999 percent TiO_2 .

NOTE: Phosphorus is a common impurity in TiO_2 and a reagent low in phosphorus must be selected. The selected reagent should be checked as even nominally high purity reagents can be highly contaminated, e.g. a 99.999 percent TiO_2 grade reagent has been found to contain about 0.5 percent P_2O_5 .

4.4.1.5 Ammonium dihydrogen orthophosphate ($\text{NH}_4\text{H}_2\text{PO}_4$).

4.4.1.6 Calcium carbonate (CaCO_3).

4.4.2 Preparation. The masses of the reagents used in preparing the synthetic calibration sample are given in Table 2. Prior to weighing, however, the iron (III) oxide and titanium dioxide shall be heated at 1000°C for a minimum of 1 h, while the ammonium dihydrogen orthophosphate and calcium carbonate shall be dried at 105°C for a similar time. Since aluminium oxide and silicon dioxide can retain water at 1000°C , they shall be heated at 1200°C for a minimum of 2 h. The cooling of all reagents shall be carried out in a desiccator with self-indicating silica gel desiccant.

* In course of preparation as DR 82025.