

Under Revision See DR 91117

K/
C
oal

Superseded by AS 1038.1-1992

AS 1038, Part 1—1980
UDC [662.66+662.74]: 643.812-2

: 620.116

Australian Standard 1038, Part 1—1980

METHODS FOR THE ANALYSIS AND TESTING OF COAL AND COKE Part 1—TOTAL MOISTURE IN HARD COAL



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



b

THE FOLLOWING INDUSTRIAL, SCIENTIFIC AND GOVERNMENTAL organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian Coal Association
Australian Institute of Energy
Australasian Institute of Mining and Metallurgy
Bureau of Steel Manufacturers of Australia
Coal Preparation Societies of N.S.W. and Queensland
Confederation of Australian Industry
Department of Minerals and Energy, Victoria
Department of Mineral Resources , N.S.W.
Department of National Development
Electricity Supply Association of Australia
Institution of Engineers, Australia
Joint Coal Board
Queensland Coal Board
Royal Australian Chemical Institute
Universities

This standard, prepared under the direction of Committee CH/15, Coal and Coke, was approved by the Chemical Standards Board on behalf of the Council of the Standards Association of Australia on 11 March 1980, and was published on 1 June 1980.

To keep abreast of progress in industry, Australian Standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by listings in the SAA monthly journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 78073.

AUSTRALIAN STANDARD

**METHODS FOR THE
ANALYSIS AND TESTING OF
COAL AND COKE**

**Part 1
TOTAL MOISTURE IN
HARD COAL**

AS 1038, Part 1—1980

First published (as AS K152, Part 1)..... 1965
AS 1038, Part 1 first published..... 1980

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 1907 X



PREFACE

This standard was prepared by the Association's Committee on Coal and Coke under the direction of the Chemical Standards Board. It replaces AS K152, Part 1—1965 which was the endorsement of BS 1016:Part 1:1957, but which was withdrawn when BS 1016:Part 1:1957 was revised in 1973.

This standard is based on, and is technically identical with ISO 589—Hard Coal—Determination of Total Moisture. Basically there is little difference between the methods specified in the 1965 edition and those in this revised edition. However the 1965 edition specified separate methods for coal of ½ inch and 6 BS mesh size whereas the methods specified herein are applicable to coals of 3 mm maximum particle size except for the method of drying in air which used coals with a maximum particle size of about 20 mm.

The standard contains three methods for the determination of the total moisture content of hard coal, viz direct volumetric method, drying in nitrogen, and drying in air. It requires reference to the following Australian standard:

AS 1676 Methods for the Sampling of Hard Coal

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1980

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

SPECIFICATION	<i>Page</i>
1 Scope	4
2 Application	4
3 Definitions	4
4 Principle	4
5 Samples	5
6 Direct Volumetric Method (Method A)	5
7 Drying in Nitrogen (Method B)	7
8 Drying in Air (Method C)	9
9 Calculation and Reporting of Total Moisture	9
10 Precision of the Method	10
11 Reporting of Results	10
 APPENDIX A. NITROGEN PURIFICATION TRAIN	 11

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
METHODS FOR THE ANALYSIS AND TESTING OF
COAL AND COKE

PART 1—TOTAL MOISTURE IN HARD COAL

1 SCOPE. This standard sets out three methods for the determination of the total moisture content of hard coal. The methods are as follows:

- (a) Direct Volumetric Method (Method A).
- (b) Drying in Nitrogen (Method B).
- (c) Drying in Air (Method C).

2 APPLICATION. Methods A and B are applicable to all hard coals. Method C is applicable only to hard coals which are known not to be susceptible to significant oxidation.

3 DEFINITIONS. For the purpose of this standard, the following definitions apply:

3.1 Total moisture—the moisture in the coal as sampled.

3.2 Free moisture—the moisture which is lost by the coal sample in attaining equilibrium with the air to which it is exposed.

3.3 Moisture in air-dried coal—the moisture in the coal sample after it has attained equilibrium with the air to which it is exposed.

4 PRINCIPLE.

4.1 Method A (Applicable to all hard coals). The sample is heated in a flask under reflux conditions with boiling toluene. The moisture from the coal is entrained by the toluene vapour and carried to a condenser fitted with a graduated receiver. The water then separates in the receiver, to form the lower layer, while the excess toluene is returned to the distillation flask by means of an overflow. The moisture in the coal is calculated from the mass of the sample and the volume of water collected.

4.2 Method B (Applicable to all hard coals). The sample is heated in an oven at a temperature of 105°C to 110°C in a current of nitrogen and the moisture calculated from the loss in mass.