

Australian Standard[®]

**ALUMINIUM AND ALUMINIUM
ALLOYS—
INGOTS AND CASTINGS**

This Australian Standard was prepared by Committee MT/3, Aluminium and Aluminium Alloys. It was approved on behalf of the Council of the Standards Association of Australia on 12 July 1988 and published on 3 October 1988.

The following interests are represented on Committee MT/3:

Aluminium Development Council
Architectural Aluminium Fabricators Federation of Australia
Confederation of Australian Industry
Department of Defence
Metal Trades Industry Association of Australia
Railways of Australia Committee
Royal Australian Institute of Architects
Society of Automotive Engineers— Australasia

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 87075.

Australian Standard®

**ALUMINIUM AND ALUMINIUM
ALLOYS—
INGOTS AND CASTINGS**

AS H49 first published 1950
(endorsement of BS 1490:1949 without amendment)
Second edition 1962.
AS H61 first published 1961.
AS H49 — 1962 and AS H61 — 1961 revised,
amalgamated and redesignated AS 1874 — 1977.
Second edition 1988.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 5212 3

PREFACE

This Standard was prepared by the Association's Committee on Aluminium and Aluminium Alloys to supersede AS 1874—1977.

During the preparation of this Standard, the Committee considered the following Standards issued by the International Organization for Standardization (ISO):

- ISO/R115 *Classification and composition of unalloyed aluminium ingots for remelting.*
- ISO/2378 *Aluminium alloy chill castings—Reference test bar.*
- ISO/2379 *Aluminium alloy sand castings—Reference test bar.*
- ISO/3522 *Cast aluminium alloys—Chemical composition and mechanical properties.*

The Standard is not compatible with ISO Standards, because Australian practice follows North American practice.

In this Standard, modifications to existing designations have been introduced and these are as follows:

Alloy designation — the second prefix letter now indicates structure pre-modification, rather than primary or secondary metal usage.

Temper designation — T2 temper has been deleted.

The relationship between alloys is illustrated in Appendix D.

In preparing this Standard, consideration was taken of the publication issued by The Aluminium Development Council of Australia (Limited), viz, *Aluminium standards and data, aluminium ingots and castings*.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

| | <i>Page</i> |
|--|-------------|
| 1 SCOPE | 4 |
| 2 REFERENCED DOCUMENTS | 4 |
| 4 DESIGNATION | 4 |
| 4 DEFINITIONS | 4 |
| 5 FREEDOM FROM DEFECTS | 4 |
| 6 RECLAMATION AND REPAIR OF CASTINGS | 4 |
| 7 SHAPE AND DIMENSIONS OF CASTINGS | 5 |
| 8 CHEMICAL COMPOSITION | 5 |
| 9 MECHANICAL PROPERTIES OF CASTINGS | 5 |
| 10 ADDITIONAL INSPECTION REQUIREMENTS FOR CASTINGS | 5 |
| 11 PROVISION AND PREPARATION OF TEST SAMPLES | 5 |
| 12 PREPARATION OF TEST PIECES | 5 |
| 13 MECHANICAL TESTS | 5 |
| 14 RETESTS | 5 |
| 15 IDENTIFICATION | 10 |
| 16 INTERPRETATION OF SPECIFIED LIMITING VALUES | 10 |
| APPENDICES | |
| A PURCHASING GUIDELINES | 11 |
| B ALLOY DESIGNATION | 15 |
| C TEMPER DESIGNATION | 16 |
| D RELATED COMPOSITION SPECIFICATIONS | 17 |

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

ALUMINIUM AND ALUMINIUM ALLOYS—INGOTS AND CASTINGS

1 SCOPE. This Standard specifies requirements for aluminium ingots and aluminium alloy ingots and castings.

NOTES:

- Guidelines to purchasers on requirements that are to be specified by the purchaser and those that are to be agreed on at the time of enquiry and order are given in Appendix A.
- Related composition specifications are given in Appendix D.

2 REFERENCED DOCUMENTS. The following Standards are referred to in this Standard.

AS

| | |
|------|--|
| 1391 | Methods for tensile testing of metals |
| 2062 | Methods for non-destructive penetrant testing of products and components |
| 2612 | Aluminium and aluminium alloys—Sampling and preparation of solid samples for optical emission spectrometry |
| 2706 | Numerical values—Rounding and interpretation of limiting values |
| B8 | Methods for the colouring and marking of foundry patterns |

BS

| | |
|------|--|
| 1728 | Methods for the analysis of aluminium and aluminium alloys |
|------|--|

ASTM

| | |
|-----|--|
| E34 | Chemical analysis of aluminium and aluminium alloys Methods for emission spectrochemical analysis |
|-----|--|

3 DESIGNATION.

3.1 Material designation. The material designation of aluminium ingots and aluminium alloy ingots and castings, as given in Table 1, shall be in accordance with Appendix B.

3.2 Temper designation. The temper designation, as given in Table 2, shall be in accordance with Appendix C, and shall follow the material designation, the two being separated by a dash.

Examples of complete designation: AA 301-T6, CA 401-F1.

4 DEFINITIONS. For the purpose of this Standard, the following definitions apply.

4.1 Annealing—thermal treatment to soften metal by removal of strain hardening resulting from cold working, by recrystallization and by coalescing precipitates from the solid solution.

4.2 Artificial ageing—a thermal treatment of an alloy at above room temperature to produce strengthening by precipitation of soluble constituents from the supersaturated solid solution.

Also known as 'precipitation heat treatment'.

4.3 Ingot—a metal product prepared in a suitable form for remelting.

4.4 Natural ageing—strengthening of an alloy by spontaneous precipitation of soluble constituents from a super-saturated solid solution at room temperature.

4.5 Permanent mould casting—a metal product prepared by introducing molten metal by gravity or low pressure into a mould constructed of durable material, usually iron or steel, and allowing it to solidify.

4.6 Pressure die casting—a metal product produced by introducing molten metal by high pressure into a mould constructed of a durable metal, usually steel, and allowing it to solidify.

4.7 Sand casting—a metal product produced by pouring molten metal into a sand mould and allowing it to solidify.

4.8 Solution heat treatment—a process in which an alloy is heated to a suitable temperature and is held at this temperature long enough to allow soluble constituents to enter into solid solution where they are retained in a super-saturated state after quenching.

4.9 Stabilizing—a thermal treatment used to promote stability under service conditions in, for example, dimensions, mechanical properties, structure or internal stress.

4.10 Temper—designates a state after processing (for example, by mechanical and thermal treatments) required to produce characteristic physical and mechanical properties in a metal or an alloy.

5 FREEDOM FROM DEFECTS.

5.1 Ingots. Ingots shall be free from dross, slag and other harmful contamination.

5.2 Castings. Castings shall be clean and free from defects detrimental to their subsequent processing and end use.

Notwithstanding that castings have been passed as complying with this Standard, if faults in manufacture are revealed in subsequent processing of the castings, they may then be deemed not to comply.

6 RECLAMATION AND REPAIR OF CASTINGS. Rectification of defects in castings shall be permitted, provided that subsequent processing and usefulness of the castings are not impaired. Repair or reclamation of castings shall be permitted subject to the written approval of the purchaser and the purchaser's acceptance of the proposed repair methods (see Paragraph A6, Appendix A).

If castings have been subjected to non-destructive testing, they shall be re-examined in the area of the repair following any rectifying operation performed on the castings.