

Australian Standard[®]

Alumina

**Part 3: Determination of alpha alumina
content by X-ray diffraction**



This Australian Standard® was prepared by Committee MN-009, Alumina and Materials used in Aluminium Production. It was approved on behalf of the Council of Standards Australia on 28 July 2010.

This Standard was published on 28 September 2010

The following are represented on Committee MN-009:

- Australasian Institute of Mining and Metallurgy
 - Australian Aluminium Council
 - Mineral Council of Australia
 - The Royal Australian Chemical Institute
-

This Standard was issued in draft form for comment as DR AS 2879.3.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting **www.standards.org.au**

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at **mail@standards.org.au**, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

Alumina

**Part 3: Determination of alpha alumina
content by X-ray diffraction**

Originated as AS 2879.3—1991.
Second edition 2010.

COPYRIGHT

© Standards Australia Limited

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968.

Published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 978 0 7337 9686 9

PREFACE

This Standard was prepared by the Standards Australia Committee MN-009, Alumina and Materials used in Aluminium Production, to supersede AS 2879.3—1991, *Alumina, Part 3: Determination of alpha alumina content by X-ray diffraction*.

The term ‘informative’ has been used in this Standard to define the application of the appendix to which it applies. An ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS.....	4
3 PRINCIPLE	4
4 REAGENTS.....	4
5 APPARATUS	5
6 PROCEDURE.....	5
7 CALCULATION AND EXPRESSION OF RESULTS.....	7
8 PRECISION.....	7
9 TEST REPORT.....	8
APPENDIX A RESULTS OF INTERLABORATORY TEST PROGRAM	9

STANDARDS AUSTRALIA

Australian Standard
Alumina**Part 3: Determination of alpha alumina content by X-ray diffraction****1 SCOPE**

This Standard sets out an X-ray diffraction method for the determination of the alpha alumina content of smelter grade alumina. The method is applicable to smelter grade alumina containing alpha phase at levels up to 50%. The percentage by mass of alpha alumina is determined on an 'as received' basis.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

2850 Chemical analysis—Inter-laboratory test programs—For determining precision of analytical method(s)—Guide to the planning and conduct.

4538 Guide to the sampling of alumina

4538.2 Part 2: Preparation of samples

H.P. Klug and L.E. Alexander. *X-ray diffraction procedures for polycrystalline and amorphous materials*. 2nd ed. Wiley, New York. 1974.

V.E. Burke, R. Jenkins and D.K. Smith. *A practical guide for preparation of specimens for X-ray fluorescence and X-ray diffraction analysis*. John Wiley and Sons, New York. 1998.

3 PRINCIPLE

The integrated peak areas of the (012) and (116) lattice plane reflections (nominal d spacing 0.348 to 0.160 nm) are measured for the test sample and a 100% alpha alumina standard. The ratio between the net peak area intensities for the test sample and for the standard is determined and the alpha alumina content calculated from this ratio.

4 REAGENTS**4.1 General**

During the analysis, only reagents of recognized analytical reagent grade and only distilled water, or water of equivalent purity, shall be used.

4.2 Hydrochloric acid (10% m/V)

Not necessary if a commercial 100% calibration standard (4.4) is to be used.

4.3 Smelter grade alumina

Not necessary if a commercial 100% calibration standard (4.4) is to be used.