

Under Revision DR 92178 Dup

Superseded by AS 2207-1994

AS 2207—1980

UDC 620.179.16:621.791.05 669.14

Australian Standard 2207—1980

METHODS FOR THE ULTRASONIC TESTING OF FUSION WELDED JOINTS IN STEEL



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



THE FOLLOWING SCIENTIFIC, INDUSTRIAL AND GOVERNMENTAL ORGANIZATIONS and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian Atomic Energy Commission
Australian Institute for Non-Destructive Testing
Australian Welding Institute
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Department of Defence
Department of Labour and Industry, N.S.W.
Department of Labour and Industry, Victoria
Electricity Supply Association of Australia
Institute of Australian Foundrymen (N.S.W. Division)
National Association of Testing Authorities
Railways of Australia Committee
Society of Automotive Engineers—Australasia

This standard, prepared by Committee MT/7, Non-destructive Testing of Metals and Materials, was approved on behalf of the Council of the Standards Association of Australia on 27 March 1980, and was published on 1 July 1980.

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by listings in the SAA monthly journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

AUSTRALIAN STANDARD

**METHODS FOR THE
ULTRASONIC TESTING
OF FUSION WELDED JOINTS
IN STEEL**

AS 2207—1980

First issued (as AS B261, Part i) 1968
AS 2207 first published 1979
Second edition..... 1980

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**



ISBN 0 7262 1942 8

PREFACE

This edition of this standard was prepared by the Association's Committee on Non-destructive Testing to replace the 1979 edition which was a revision of AS B261, Part 1—1968.

During the preparation of the 1979 edition the committee considered the testing methods written into overseas standards, and practices which have evolved in the field of non-destructive testing in Australia, including the following standards:

JIS Z2344	Ultrasonic Testing of Metals by the Pulse Echo Technique
BS 3889	Methods for Non-destructive Testing of Pipes and Tubes Part 1A—Ultrasonic Testing of Ferrous Pipes (excluding Cast)
AS 1710	Method for Ultrasonic Testing of Carbon and Low Alloy Steel Plate, and Classification of Quality

Consideration was also given to recommendations of the British Welding Institute and to technical literature on the subject, especially the work of Mr C. Abrahams of the United Kingdom. Acknowledgement is made of the assistance received from these sources.

The standard covers the use of pulse-echo ultrasonic testing equipment under direct contact conditions. It describes various test methods (using ultrasonic sound waves) which may be specified by manufacturers, inspecting authorities, or purchasers for the testing of welded structures.

The standard has been arranged in a new format and contains methods specified in more detail than previously. New methods have been introduced for the sizing of discontinuities based on a 20 dB intensity drop system.

Details and examples are given for the use of reflectivity diagrams for both normal and angle probes. A nomograph has also been included for different probe sizes when determining compensation for curvature.

Additional guidelines have also been introduced for use by purchasers, designers and testing authorities.

The standard has been written to include standard test methods. Methods which use grass, natural discontinuities or corner reflectors as reference or

calibration standards are considered to be non-preferred methods and have not been included because they cannot be related back to a 1.5 mm side-drilled hole because the response obtained may not be consistent.

The successful application of ultrasonic testing depends upon the technical competence of the testing personnel and on their ability to interpret test results. It is essential that testing personnel be conversant with the test equipment and be capable of demonstrating to the satisfaction of interested parties their technical competence and interpretive ability (see also Appendix A).

It is emphasized that diagnosis of the nature of discontinuities located by ultrasonic testing can be made only by consideration of both metallurgical and ultrasonic factors. Consideration should therefore be given to the method of welding, and the type, position and probable distribution of any discontinuities likely to be present. The procedure also depends upon the fact that a suitable design is essential, cooperation between designers and non-destructive testing specialists at an early stage is recommended.

It should be noted that facilities for non-destructive testing are afforded by laboratories registered by the National Association of Testing Authorities, Australia, for the field and class of testing covered by this standard.

To avoid unnecessary rejection of satisfactory welds this edition introduces a 20 percent threshold limit for Level 1 testing. Level 4 testing has been amended to provide for a threshold cut-off at 20 percent of the evaluation sensitivity.

To avoid possible confusion in the interpretation of requirements for surface preparation the requirements have been more carefully outlined.

Procedures for the testing of fillet welds in lap joints and web/flanges have also been updated.

This standard may require reference to the following Australian standards:

AS 1554	SAA Code for Welding in Building
AS 1929	Glossary of Terms Used in Non-destructive Testing
AS 2083	Calibration Blocks and their Method of Use in Ultrasonic Testing
AS Z5	Glossary of Metal Welding Terms

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1979

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>		<i>Page</i>
SECTION 1. SCOPE AND GENERAL		SECTION 5. METHODS OF TEST	
1.1 Scope	4	5.1 General	9
1.2 Application....	4	5.2 Methods of Test	9
1.3 Definitions	4	5.3 Procedures for the Evaluation of Discontinuities	14
SECTION 2. EQUIPMENT AND CALIBRATION		5.4 Optional Variations to Levels 1, 2, and 3 Testing	14
2.1 General	5	5.5 Procedures for Sizing Using 20 dB Drop	14
2.2 Presentation	5	5.6 Record of Test Results	15
2.3 Assessment of Horizontal and Vertical Linearity	5	SECTION 6. TEST REPORT	
2.4 Gain Control	5	6.1 Test Report	19
2.5 Frequency Range	5	APPENDICES	
2.6 Probes....	5	A Guidelines for Purchasing, Design and Testing Authorities	20
2.7 Resolution	5	B Guidance on Ultrasonic Testing of Welds	23
2.8 Couplants	5	C Alternative Methods for Establishing Sensitivity	27
2.9 Stability	5	D Methods for the Determination of Attenuation and Transfer Losses	29
SECTION 3. SENSITIVITY		E Factors Influencing Probe Selection	31
3.1 General	6	F Welding Terminology and Symbols	32
3.2 Reference Block	6	G Identification of Discontinuities	34
3.3 Scanning Sensitivity	6	H Record of Results	36
3.4 Evaluation Sensitivity	6	J Compensation for Convex Curvature	37
3.5 Preparation of Distance Amplitude Correction Curves	6	K Use of Reflectivity Diagrams	39
SECTION 4. PREPARATION OF TEST SURFACES			
4.1 General Requirements	8		
4.2 Additional Surface Requirements	8		

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

METHODS FOR THE ULTRASONIC TESTING OF FUSION WELDED JOINTS
IN STEEL

SECTION 1. SCOPE AND GENERAL

1.1 SCOPE. This standard sets out methods for manual ultrasonic testing of full or partial penetration, fusion welded joints in steels of thickness not less than 6 mm, using A-scan presentation.

This standard precludes the testing of longitudinal welds where—

- (a) radius of curvature on fabrications is less than 125 mm; and
- (b) the ratio of thickness to outside diameter on tubular fabrications over 250 mm diameter exceeds 0.22.

NOTES:

1. The methods described in this standard assume that ultrasonic testing personnel can interpret indications given by a test and can distinguish between cracks and other discontinuities.
2. Supplementary information required to establish appropriate test methods is set out in Appendix A.

1.2 APPLICATION. Procedures described in this standard enable the test operator to determine the location, size and subsequent identification of weld discontinuities in seven different types of weld configurations designated by letter as follows:

<i>Weld designation*</i>	<i>Description</i>	<i>Test method designation</i>
BCD	Butt weld—double preparation—complete penetration	A
BCS	Butt weld—single preparation	B
TC	Tee butt weld—complete penetration	C
TP	Tee butt weld— incomplete penetration	D
TT	Tee butt weld— cruciform joint	E
T (C or P)	Butt weld—set through (including nozzles)	F
C (C or P)	Butt weld—set on (including nozzles)	G

NOTE: The examination of other weld types may be derived from the seven weld types specified.

The actual method to be used and the sentencing of discontinuities shall be in accordance with the relevant product specification, application code, contract or order.

Levels 1, 2 and 3 specify a threshold sensitivity below which no discontinuities other than cracks are reported.

Above the threshold for Level 1 all discontinuities are sized for length and height using a beam profile method.

Above the threshold for Levels 2 and 3 all discontinuities are evaluated for length only using a beam profile method. For these levels the threshold sensitivity is constant irrespective of thickness.

Level 4 testing uses a number of reference levels which vary with metal thickness and requires the evaluation of discontinuities with a reflectivity equal to or greater than 20 percent of the reference level.

Level 5 testing may involve the use of a higher or lower evaluation sensitivity than those specified in this standard.

1.3 DEFINITIONS. For the purpose of this standard the terms and definitions given in AS 1929 and AS Z5 apply (see Appendix F for symbols and notations).

*Aligned with AS 1554.