

S 1038,
Part 7

~~REFERENCE COPY~~
~~INFORMATION CENTRE~~
~~STANDARDS AUSTRALIA~~

WITHDRAWN:

19970405

AS 1038, Part 7—1981

UDC [662.664.662.74]:543.84

*del Revision
DR96270, DR96271 (in part)*

[662.66 + 662.74] 0.2
620.16

SUPERSEDED BY:

AS 1038.6.1-1997

AS 1038.6.2-1997

AS 1038.6.3.1-1997

AS 1038.6.3.2-1997

Australian Standard 1038, Part 7—1981

METHODS FOR THE ANALYSIS AND TESTING OF COAL AND COKE

Part 7—ULTIMATE ANALYSIS OF COKE



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



THE FOLLOWING INDUSTRIAL, SCIENTIFIC AND GOVERNMENTAL organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian Coal Association
Australian Institute of Energy
Australasian Institute of Mining and Metallurgy
Bureau of Steel Manufacturers of Australia
Coal Preparation Societies of NSW and Queensland
Confederation of Australian Industry
Department of Minerals and Energy, Victoria
Department of Mineral Resources and Development
Department of National Development
Electricity Supply Association of Australia
Institution of Engineers, Australia
Joint Coal Board
Queensland Coal Board
Royal Australian Chemical Institute
Universities

This standard, prepared under the direction of Committee MN/1, Coal and Coke, was approved on behalf of the Council of the Standards Association of Australia on 12 November 1980, and was published on 1 March 1981.

To keep abreast of progress in industry, Australian Standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by listings in the SAA monthly journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 79114.

AUSTRALIAN STANDARD

**METHODS FOR THE
ANALYSIS AND TESTING
OF COAL AND COKE**

**Part 7
ULTIMATE ANALYSIS
OF COKE**

AS 1038, Part 7—1981

First published (as AS K152, Part 7) ...1965
AS 1038, Part 7 first published1981



**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 2100 7

PREFACE

This standard was prepared by the Association's Committee on Coal and Coke as part of the process of revision and metrication of standards for the analysis and testing of coal and coke. It replaces AS K152, Part 7—1965, which had been withdrawn.

Whereas AS K152, Part 7 was BS 1016: Part 7: 1959 endorsed subject to Australian Amendment No 1, this standard is based on BS 1016: Part 7: 1977. The major alteration from AS K152, Part 7 is the deletion of the Liebig method for the determination of carbon and hydrogen as this method is little used now.

This standard requires reference to the following standards:

- | | |
|---------|--|
| AS 1038 | Methods for the Analysis and Testing of Coal and Coke
Part 4—Proximate Analysis of Coke
Part 8—Chlorine in Coal and Coke
Part 16—Reporting of Results |
| AS 1152 | Test Sieves |
| AS 1898 | Methods for the Sampling of Coke |
| AS 2165 | Burettes and Bulb Burettes |
| AS 2167 | Straight Pipettes |
| BS 1016 | Methods for the Analysis and Testing of Coal and Coke
Part 13—Tests Special to Coke |
| BS 1752 | Laboratory Sintered or Fritted Filters |

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1981

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

STANDARDS ASSOCIATION OF AUSTRALIA**Australian Standard
METHODS FOR THE ANALYSIS AND TESTING
OF COAL AND COKE****PART 7—ULTIMATE ANALYSIS OF COKE**

1 SCOPE. This standard sets out methods for determining carbon, hydrogen, nitrogen and sulphur in the analysis sample of coke.

2 SAMPLES. The coke used shall be the analysis sample ground to pass a 212 μm test sieve complying with AS 1152, taken and prepared in accordance with AS 1898.

3 DETERMINATION OF CARBON AND HYDROGEN.

3.1 Principle. A known mass of coke is burned at a temperature of 1350°C in a rapid current of oxygen, so that all the carbon is converted to carbon dioxide and all the hydrogen to water. Chlorine and oxides of sulphur are retained in the apparatus by silver gauze. The water formed is absorbed by magnesium perchlorate and the carbon dioxide by soda asbestos or soda lime.

The value for hydrogen is corrected for that present as moisture in the sample.

3.2 Reagents.

3.2.1 General. All reagents shall be of analytical reagent quality unless otherwise specified. Distilled or deionized water shall be used throughout.

3.2.2 Special reagents.

3.2.2.1 Magnesium perchlorate (dried), - 1.18 mm + 0.71 mm.

3.2.2.2

(a) Soda asbestos, - 2.80 mm + 1.40 mm and - 1.70 mm + 1.18 mm, preferably self-indicating; or

(b) soda lime, - 2.0 mm + 1.2 mm, self-indicating.

3.2.2.3 Aluminium oxide, finely divided, approximately 0.1 mm particle size. Heat the aluminium oxide to above 800°C before use.

3.2.2.4 Sodium borate solution (0.025 mol/L).

3.2.2.5 Screened indicator solution, prepared as follows:

(a) Dissolve 0.2 g methyl red in 10 mL ethanol solution (300 mL/L). Add 1 g sodium hydroxide and heat the mixture at 40°C until solution is complete. Cool, and dilute to 100 mL with water.