

Under Revision See
DR93178

AS 2269—1979
UDC 674-419.32

Superseded by AS/NZS 2269:1994

Australian Standard 2269—1979

STRUCTURAL PLYWOOD

[Title allocated by Defence Cataloguing Authority:
PLYWOOD (Structural Use)]



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



THE FOLLOWING SCIENTIFIC, INDUSTRIAL AND GOVERNMENTAL organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian Council of Furniture Manufacturers
Australian Institute of Building
Commonwealth and State Forestry Departments
Confederation of Australian Industry
CSIRO, Division of Building Research
Department of Defence
Department of Transport
Lending Institutions
Plywood Association of Australia
Railways of Australia Committee
Royal Australian Institute of Architects
Sawmilling and Timber Associations

This standard, prepared by Committee TM/5, Plywood, was approved on behalf of the Council of the Standards Association of Australia on 29 June 1979, and was published on 1 October 1979.

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or revised editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by monthly listings in the SAA Monthly Information Sheet. Information on the Annual List and the SAA Monthly Information Sheet may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 78051.

AUSTRALIAN STANDARD

STRUCTURAL PLYWOOD

AS 2269—1979

First issued (as AS 085 and AS 089) . 1969/1973
Revised and issued as AS 2269 1979 ✓
Reprinted (incorporating Corrigendum)..... 1984

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 1743 3



22 MAY 1987

PREFACE

This standard was prepared by the Association's Committee on Plywood as a revision, metrication and consolidation of AS O85—1969, Pinus Structural Plywood, and AS O89—1973, Structural Plywood—1600f Stress Grade and 1.55E Stiffness Grade, both of which it accordingly supersedes.

The standard is intended primarily to meet the needs of constructional and industrial users of plywood and the manufacturers of plywood.

Plywood manufactured to the standard is suitable for use in permanent structures.

The plywood may be of either hardwood or softwood veneers or a combination of both. The quality of the veneers is judged in the finished sheet. Two veneer qualities are described, one requires an essentially solid face and the other permits open defects. The quality of the plywood is judged by the quality of the face and back veneers.

The stress grades apply for the lower of the two veneer qualities and are determined by—

- (a) identification of the species;
- (b) determination of the veneer density; or
- (c) mechanical stress grading of the whole finished sheet of plywood.

For designs incorporating the use of plywood specified in this standard, the structural grades will have the basic working stresses and elastic moduli set out in Table 4.2. These basic working stresses are applied in accordance with procedures set out in AS 1720, SAA Timber Engineering Code.

Particular end uses may require SAA consideration of treatment with preservatives, overlays and so on.

This standard requires reference to the following Australian standards:

- | | |
|---------|--|
| AS 1148 | Nomenclature of Commercial Timbers Imported into Australia |
| AS 1604 | Preservative-treated Sawn Timber, Veneer and Plywood |
| AS 1613 | Colour for Marking Stress Graded Timber |
| AS 1720 | SAA Timber Engineering Code |
| AS 2097 | Methods for Sampling Veneer and Plywood |
| AS 2098 | Methods of Test for Veneer and Plywood |
| | .1—Moisture Content of Veneer and Plywood |
| | .2—Bond Quality of Plywood (Chisel Test) |
| | .3—Bond Quality and Strength of Scarf Joints in Plywood |
| | .4—Dimensions of Sheets of Veneer and Plywood |
| | .6—Depth of Peeler Checks in Veneer and Plywood |
| | .7—Density of Veneer and Plywood |

- AS 2193 **Methods for Calibration and Grading of Force-measuring Systems of Testing Machines**
- AS 2270 **Plywood and Blockboard for Interior Use**
- AS 2271 **Plywood and Blockboard for Exterior Use**
- AS 2289 **Glossary of Terms Used in the Plywood Industry**
- AS K88 **Synthetic Resin Adhesives for Plywood (Phenolic and Aminoplastic)**
- AS O1 **Glossary of Terms Used in Timber Standards**
- AS O2 **Nomenclature of Australian Timbers**

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1979

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>
SECTION 1. SCOPE AND GENERAL REQUIREMENTS	
1.1 Scope	5
1.2 Application	5
1.3 Interpretation of Terms	5
1.4 Grades of Structural Plywood	5
1.5 Dimensions and Shape	6
1.6 Moisture Content	6
1.7 Finish	7
1.8 Joints in Sheets	7
1.9 Immunization and Preservative Treatment	7
1.10 Identification	7
SECTION 2. REQUIREMENTS FOR VENEER	
2.1 General Requirements for All Veneers	9
2.2 Veneer Qualities for Structural Plywood Sheets	9
SECTION 3. MANUFACTURING REQUIREMENTS	
3.1 Joints in Veneer	11
3.2 Joints in Plywood Sheets	11
3.3 Bonding Between Plies	11
3.4 Assembly of Plywood	12
SECTION 4. STRESS GRADING OF STRUCTURAL PLYWOOD SHEETS	
4.1 General	13
4.2 Veneers of Identified Species	13
4.3 Veneers of Determined Density	13
4.4 Mechanically Stress Graded Structural Plywood Sheets	13
APPENDICES	
A Sampling, Testing and Acceptance	15
B Determination of Deflection in Bending of Plywood Sheets (Stress Grading)	16
C Physical and Mechanical Data for Standard Structural Ply- wood Constructions	18
D Stress Grades for Veneer Quality D of Identified Species	20
E Information to be Supplied with Enquiries and Orders	22
F Storage and Handling of Structural Plywood	23

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard for STRUCTURAL PLYWOOD

SECTION 1. SCOPE AND GENERAL REQUIREMENTS

1.1 SCOPE. This standard specifies requirements for the construction, manufacture, grading and finishing of stress and surface grades of structural plywood. It specifies veneer qualities, bond quality, joints, dimensional tolerances, moisture content and basic working stresses.

The standard prescribes three alternative methods for the determination of stress grades for structural plywood, viz—

- (a) species identification;
- (b) density determination; and
- (c) mechanical stress-grading of the finished sheet of plywood.

Two surface grades, based on veneer quality of the face and back veneers, and one bond quality, viz Type A bond, are prescribed.

Appendices describe sampling, testing and acceptance, stress grading of plywood sheets, physical and mechanical data of structural plywood, stress grades for veneer of individual species, and information to be supplied with enquiries and orders.

1.2 APPLICATION. The specification for any grade of structural plywood shall consist of the general requirements given in Section 1, together with the relevant requirements for veneers given in Section 2 and the manufacturing requirements given in Section 3.

1.3 INTERPRETATION OF TERMS. The terms used in this standard shall be interpreted in accordance with AS 2289 and AS O1.

1.4 GRADES OF STRUCTURAL PLYWOOD.

1.4.1 General. Structural plywood shall be graded according to surface quality and stress grade.

1.4.2 Surface Grades. The surface grades shall be Grade C and Grade D and shall correspond respectively to Quality C veneer and Quality D veneer in accordance with Clause 2.2.

NOTE: Grade C provides for a solid face, whereas Grade D allows open defects.