

A/
/C
Concrete

WITHDRAWN: 19980905

SUPERSEDED BY:

AS 1012, Part 3—1983

AS 1012.3.1-1998
AS 1012.3.2-1998

UDC Use as Pt 1
AS 1012.3.3-1998
AS 1012.3.4-1998

Australian Standard 1012, Part 3—1983



METHODS OF TESTING CONCRETE

METHODS FOR THE DETERMINATION OF PROPERTIES RELATED TO THE CONSISTENCE OF CONCRETE



**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**



Incorporated by Royal Charter

D

This Australian standard was prepared by Committee BD/42; Methods of Testing Concrete. It was approved on behalf of the Council of the Standards Association of Australia on 20 December 1982 and published on 5 April 1983.

The following interests are represented on Committee BD/42:

Association of Consulting Engineers, Australia
Confederation of Australian Industry
Cement and Concrete Association of Australia
CSIRO, Division of Building Research
Department of Transport and Construction
Department of Public Works, N.S.W.
National Association of Australian State Road Authorities
National Association of Testing Authorities, Australia
National Ready Mixed Concrete Association of Australia
University of New South Wales

To keep abreast of progress in industry, Australian Standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by listings in the SAA monthly journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

First published	1971
Second edition	1976 ✓
Third edition	1983

This standard was issued in draft form for comment as DR 82056. ✓

ISBN 0 7262 2892 3

PREFACE

This edition of this standard was prepared by the Association's Committee on Methods of Testing Concrete as part of an ongoing revision of the AS 1012 series of standards on the testing of concrete. It supersedes AS 1012, Part 3—1976.

The main alteration to Method 1 — Slump Test has been to limit its application to a nominal aggregate size of 40 mm. The procedures have been clarified and diagrams of collapse and shear slumps have been included.

Method 2 — Compacting Factor Test has been only slightly altered by relating the time for the test for concrete mixed in the laboratory to the completion of mixing, rather than the addition of the mixing water. The procedure has also been clarified.

The procedure for Method 3 — Vebe Test has been altered so that the mould is now filled in three layers. This follows proposed changes to BS 1881.

A new method, Compactibility Index, has been included in this edition. It is intended to provide a field consistence test for nil-slump concretes, such as those used in kerb extrusion machines.



© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1983

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

-7 APR 1983

CONTENTS

	<i>Page</i>
SECTION 1. METHOD 1 — SLUMP TEST	
1.1 Scope and Referenced Documents	5
1.2 Apparatus	5
1.3 Sampling	6
1.4 Procedure	6
1.5 Measurement of Slump	7
1.6 Records	7
1.7 Report	7
SECTION 2. METHOD 2 — COMPACTING FACTOR TEST	
2.1 Scope and Referenced Documents	10
2.2 Apparatus	10
2.3 Sampling	11
2.4 Procedure	11
2.5 Compacting Factor....	12
2.6 Records	12
2.7 Report	14
SECTION 3. METHOD 3 — VEBE TEST	
3.1 Scope and Referenced Documents	15
3.2 Apparatus	15
3.3 Sampling	16
3.4 Procedure	16
3.5 Vebe Value	17
3.6 Records	17
3.7 Report	18
SECTION 4. METHOD 4 — COMPACTIBILITY INDEX	
4.1 Scope and Referenced Documents	21
4.2 Principle....	21
4.3 Apparatus	21
4.4 Sampling	21
4.5 Procedure	21
4.6 Compactibility Index	22
4.7 Records	22
4.8 Report	22

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

METHODS OF TESTING CONCRETE

PART 3 — METHODS FOR THE DETERMINATION OF PROPERTIES RELATED TO THE CONSISTENCE OF CONCRETE

SECTION 1. METHOD 1 — SLUMP TEST

1.1 SCOPE AND REFERENCED DOCUMENTS.

1.1.1 Scope of Section. This Section sets out the method for determining the slump of concrete, when the nominal size of aggregate does not exceed 40 mm.

1.1.2 Referenced Documents. The following standards are referred to in this Section:

AS 1012 Methods of Testing Concrete
 Part 1 — Method for Sampling Fresh Concrete
 Part 2 — Method for Mixing Concrete in the Laboratory.

1.2 APPARATUS.

1.2.1 Mould. The mould shall be a hollow frustum of a cone manufactured from galvanized steel sheet not less than 1.5 mm thick, the bottom and the top of the mould being open and at right-angles to the axis of the cone. The mould shall be provided with suitable footpieces and handles and its internal surface shall be smooth. The internal dimensions of the mould shall be as follows:

Bottom diameter:	200 ± 5 mm
Top diameter:	100 ± 5 mm
Vertical height:	300 ± 5 mm.

NOTES:

1. A suitable mould is illustrated in Fig. 1.1.
2. Attachments to the mould preferably should be welded. If rivets are used in the construction of the mould, they must be countersunk flush on the inside of the cone. To facilitate the lifting of the mould in a vertical direction, suitable guide attachments may be provided.

1.2.2 Rod. The rod used for compacting concrete in the mould shall be a metal rod 16 ± 1 mm in diameter, approximately 600 mm long and having at least one end tapered for a distance of approximately 25 mm to a spherical shape having a radius of approximately 5 mm.

NOTE: The rod may be extended with a handle of plastics conduit, provided that the overall length does not exceed 1000 mm.

1.2.3 Scoop.