

Australian Standard™

Methods for impact tests on metals

Part 3: Charpy U-notch and keyhole notch

This Australian Standard was prepared by Committee MT-006, Mechanical Testing of Materials. It was approved on behalf of the Council of Standards Australia on 15 August 2003 and published on 19 September 2003.

The following are represented on Committee MT-006:

Australasian Railway Association
Australian Aluminium Council
Australian Industry Group
Bureau of Steel Manufacturers of Australia
CSIRO Measurement Laboratory
CSIRO Telecommunications and Industry Physics
Institute of Materials Engineering Australasia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 03162.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 1544.3—2003

Methods for impact tests on metals

Part 3: Charpy U-notch and keyhole notch

RECONFIRMATION NOTICE

Technical Committee MT-009 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 20 March 2017.

The following are represented on Technical Committee MT-009:

Australasian Institute of Surface Finishing
Australian Chamber of Commerce and Industry
Australian Industry Group
Australian Steel Institute
Bureau of Steel Manufacturers of Australia
Galvanizers Association of Australia
Galvanizing Association of New Zealand
New Zealand Metal Roofing Manufacturers

NOTES

Australian Standard™

Methods for impact tests on metals

Part 3: Charpy U-notch and keyhole notch

Originated as AS B188.3—1964.
Previous edition AS 1544.3—1975.
Second edition 2003.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5043 5

PREFACE

This Standard was prepared by the Standards Australia Committee MT-006, Mechanical Testing of Metals, to supersede AS 1544.3—1975, *Methods for impact tests on metals, Part 3: Charpy U-notch and keyhole notch*.

The objective of this Standard is to specify a method for testing toughness in metals by impact testing.

This Standard is Part 3 of a series of Standards on the methods for impact testing of metals. The series comprises the following methods:

AS

- 1544 Methods for impact tests on metals
- 1544.1 Part 1: Izod
- 1544.2 Part 2: Charpy V-notch
- 1544.3 Part 3: Charpy U-notch and keyhole notch
- 1544.4 Part 4: Calibration of the testing machine
- 1544.5 Part 5: Assessment of fracture surface appearance of steel

The term ‘normative’ has been used in this Standard to define the application of the appendix to which it applies. A ‘normative’ appendix is an integral part of a standard.

CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 REFERENCED DOCUMENTS.....	5
3 DEFINITIONS.....	5
4 TESTING MACHINE.....	6
5 TEST PIECE.....	9
6 PROCEDURE.....	11
7 REPORT.....	13
APPENDICES	
A INSTALLATION, CALIBRATION AND MAINTENANCE OF THE TESTING MACHINE.....	14
B RECORD OF TEST RESULTS.....	17

FOREWORD

The Charpy U-notch and keyhole notch impact tests are pendulum type single-blow impact tests in which the test piece, U-notched or keyhole notched in the middle and supported at both ends as a simple beam, is broken by a falling pendulum which strikes the test piece opposite the notch. The energy absorbed, as determined by the subsequent rise of the pendulum, is a measure of impact strength or notch toughness.

The satisfactory operation of a pendulum impact testing machine is dependent on factors which include the design, the foundation, the accuracy of construction of machine components, the degree of wear, and the friction-free movement of the pendulum.

During a test, all the absorbed energy indicated by the machine is attributed to the fracturing of the test piece. However, it is known that there are other mechanisms by which small amounts of energy may be absorbed. It is suspected that items such as test piece supports, the machine foundation and frame work, the pendulum and striker, ejection and drag of the broken test piece cause some degree of energy absorption. This energy is not determined, as suitable methods and apparatus have not yet been developed for measuring energy absorption by these individual items.

STANDARDS AUSTRALIA

Australian Standard Methods for impact tests on metals

Part 3: Charpy U-notch and keyhole notch

1 SCOPE

This Standard specifies the conditions for performing the Charpy U-notch and keyhole notch impact test on metals. It also includes requirements for the installation of the testing machine, its initial and periodic calibration, and recommendations for its maintenance by the user.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

- 1544 Methods for impact tests on metals
- 1544.4 Part 4: Calibration of the testing machine
- 1544.5 Part 5: Assessment of fracture surface appearance of steel

ISO

- 83 Steel—Charpy impact test (U-notch)
- 148 Steel—Charpy impact test (V-notch)

ASTM

- E23 Methods for notched bar impact testing of metallic materials

3 DEFINITIONS

For the purpose of this Standard, the definitions below apply.

3.1 Centre of percussion

That point in a pendulum at which a blow, delivered in a tangential direction, will cause no reaction at the centre of rotation.

3.2 Initial potential energy

The energy theoretically available in a pendulum-type impact testing machine when the pendulum is returned from its striking position to its initial release position.

3.3 Length of pendulum

The distance from the axis of rotation of the pendulum to the impact point of the pendulum, on a standard test piece.

3.4 Point of impact

The midpoint of the line of contact between the striking edge and the test piece.

3.5 Sample

A portion of material or a group of items selected from a batch or consignment by a sampling procedure.