

Australian Standard™

**Procedures for acceptance testing of
refractory products**

Part 1: Batch procedure



This Australian Standard was prepared by Committee MN-007, Refractories and Refractory Materials. It was approved on behalf of the Council of Standards Australia on 15 June 2001 and published on 1 August 2001.

The following interests are represented on Committee MN-007:

Australasian Ceramic Society
Australasian Institute of Mining and Metallurgy
Australian Aluminium Council
Bureau of Steel Manufacturers of Australia
Cement Industry Federation
CSIRO—Manufacturing Science and Technology
Refractories Manufacturers Association of Australia
University of Wollongong

Additional interests participating in the preparation of this Standard:

CSIRO—Mathematical and Information Sciences

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

Australian Standard™

**Procedures for acceptance testing of
refractory products**

Part 1: Batch procedure

Originated as AS 2497—1981.
Revised and designated AS 2497.1—2001.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 3956 3

PREFACE

This Standard was prepared by the Standards Australia Committee MN-007, Refractory and Refractory Materials as a revision of AS 2497—1981, *Sampling procedures for acceptance testing of shaped refractory products* to extend its scope to include all refractory products. The Standard provides a practical guide to manufacturers and users of refractory products on sampling for acceptance testing.

This Standard is Part 1 of a series and relates to batch sampling procedures. Part 2 will cover sequential sampling procedures.

The content and format of the original edition of AS 2497 were derived from a study of typical practical sampling problems taken from the records of large industrial users and suppliers and were decided on after undertaking a study of the provisions of all relevant national and international Standards* and draft Standards available to the Committee.

It was considered that relevant ISO Standards on refractory products were limited in scope and prescriptive. On the other hand the use of general Australian, other national and international Standards on sampling methods is daunting, particularly for users, because of the size of the Standards and the lack of practical examples.

This Standard utilizes general standards on sampling methods and applies them to the refractory industry.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

Statements expressed as mandatory terms in notes to tables are deemed to be requirements of this Standard.

* Specific references are given in Appendix A.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE.....	4
1.2 APPLICATION	4
1.3 REFERENCED DOCUMENTS.....	4
1.4 DEFINITIONS	4
1.5 NOTATION.....	6
SECTION 2 METHODS	
2.1 VARIABLES AND ATTRIBUTES.....	7
2.2 PRACTICAL CONSIDERATIONS.....	7
2.3 GUIDE TO CHOICE OF METHODS	9
2.4 SUGGESTIONS FOR APPROPRIATE AQL, INSPECTION LEVEL, PRODUCER'S RISK, LQ, CONSUMER'S RISK AND SPECIFICATION LIMIT..	10
SECTION 3 RECOMMENDED SAMPLING PLANS	
3.1 SAMPLING INSPECTION BY VARIABLES—METHOD 1.....	13
3.2 SAMPLING INSPECTION BY ATTRIBUTES—METHOD 2.....	15
SECTION 4 ALTERNATIVE SAMPLING PLANS	
4.1 SAMPLING INSPECTION BY VARIABLES—METHOD 1A.....	19
4.2 SAMPLING INSPECTION BY ATTRIBUTES—METHOD 2A.....	22
SECTION 5 SAMPLING COSTS	
5.1 SAMPLING COST CONSIDERATIONS FOR VARIABLES AND ATTRIBUTES.....	26
5.2 USE OF COST INFORMATION (AS 1399 AND WETHERILL AND CHIU).....	26
SECTION 6 REPORT ON SAMPLING	28
APPENDICES	
A REFERENCE DOCUMENTS	29
B TABLE OF DEFINITIONS	30
C USE AND FUNCTIONS OF THE OC CURVE	31
D TABLES FOR INSPECTION BY VARIABLES.....	34
E SAMPLING AND SAMPLING TECHNIQUES	37
F TABLES FOR INSPECTION BY ATTRIBUTES.....	40
G LIST OF SYMBOLS	43

STANDARDS AUSTRALIA**Australian Standard****Procedures for acceptance testing of refractory products****Part 1: Batch procedure****SECTION 1 SCOPE AND GENERAL****1.1 SCOPE**

This Standard sets out the methodology for the acceptance testing of refractory products based on minimum quality levels associated with an agreed specification.

The Standard is suitable for shaped or unshaped products, raw materials or for a product in an intermediary phase. This Standard is applicable to all situations where a minimum quality level, as opposed to a mean quality level, is required for harm minimization.

This Standard does not cover the varied quality control methods used to meet performance requirements.

1.2 APPLICATION

The Standard recommends guiding principles to assist both purchasers and suppliers of refractory products in preparing sampling plans that will enable them to determine within practical limits whether or not the product complies with pre-set specifications. For a given set of conditions there will usually be several possible plans, a choice between them being made on the grounds of simplicity or cost.

1.3 REFERENCED DOCUMENTS

The documents referred to in this Standard are listed in Appendix A.

1.4 DEFINITIONS

For the purposes of this Standard, the definitions below apply.

NOTE: See also Appendix B and AS 2780.

1.4.1 Acceptable quality level (AQL)

A quality level which, in a sampling plan, corresponds to a specified but relatively high probability of acceptance. It is the maximum percent defective that, for purpose of sampling inspection, can be considered satisfactory as a process average.

1.4.2 Batch or lot (inspection)

A quantity of some commodity from which a sample is to be drawn and inspected to determine compliance with the acceptability criteria. (This may differ from a quantity of some commodity designated as a batch or lot from other purposes, e.g. for shipment. Other Standards may define batch and lot separately.) Each batch is assumed, as far as practicable, to consist of material or items of a single type, grade, class, size and composition, and to have been manufactured under essentially the same conditions at essentially the same time. It may therefore be necessary to subdivide a mixed consignment into homogeneous batches.