

AS 3680—1989

Australian Standard[®]

**Polyethylene sleeving for ductile
iron pipelines**

This Australian Standard was prepared by Committee WS/16, Cast Iron Pressure Pipes and Fittings. It was approved on behalf of the Council of Standards Australia on 10 July 1989 and published on 11 December 1989.

The following interests are represented on Committee WS/16:

Board of Works, Melbourne
Brisbane City Council
Confederation of Australian Industry
Department of Housing and Construction
Department of Local Government, Qld
Engineering and Water Supply Department, S.A.
Hunter Water Board
Institution of Engineers, Australia
Metal Trades Industry Association of Australia
Plastics Institute of Australia
Public Works Department, N.S.W.
Rural Water Commission of Victoria
Water Authority of Western Australia
Water Board, Sydney

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 88072 (in part).

AS 3680—1989

Australian Standard[®]

**Polyethylene sleeving for ductile
iron pipelines**

First published as AS 3680—1989.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 5875 X

PREFACE

This Standard was prepared by the Standards Australia Committee on Cast Iron Pressure Pipes and Fittings, and is based on current practices used in protecting underground ductile iron pipes and fittings from corrosion in aggressive soils.

This Standard applies to tubular or flat polyethylene film suitable for field application for the protection of buried ductile iron and grey iron pipes and fittings.

CONTENTS

	<i>Page</i>
FOREWORD	3
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 SLEEVING MATERIAL COMPOSITION	4
5 SLEEVING DIMENSIONS	4
6 SLEEVING PERFORMANCE REQUIREMENTS	4
7 STRAPPING AND BINDING EQUIPMENT	5
8 MARKING	5
APPENDICES	
A METHOD FOR TESTING TENSILE PROPERTIES OF POLYETHYLENE FILM	6
B METHODS FOR TESTING IMPACT RESISTANCE OF POLYETHYLENE FILM	8
C ADHESIVE TAPE, STRAP, AND BUCKLE REQUIREMENTS	9
D OUTDOOR TESTING OF POLYETHYLENE FILM	10
E PURCHASING GUIDELINES	11

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

FOREWORD

Polyethylene film was first used as a corrosion protection device for buried cast iron pipes in the U.S.A in the early 1950s; it has proved to be an effective method of controlling corrosion in aggressive soils and is now used for this purpose throughout the world.

The purpose of the loose polyethylene sleeving is to prevent contact between the pipeline and adjacent soils, thus providing a non-aggressive environment for the pipeline and minimizing corrosion. Free flow of ground water within the sleeving is not acceptable and would not be expected to occur with properly installed sleeving. The effectiveness of the sleeving is not impaired by the presence of condensate or small amounts of water which may be trapped within the sleeve.

STANDARDS AUSTRALIA

Australian Standard

Polyethylene sleeving for ductile iron pipelines

1 SCOPE. This Standard specifies requirements for materials for loose polyethylene sleeving intended for the corrosion protection of ductile and grey iron pipelines when installed underground.

NOTES:

- Guidelines for the application of polyethylene sleeving to ductile iron pipelines and fittings are given in AS 3681.
- Guidelines for purchasing polyethylene sleeving are given in Appendix E.

2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard.

AS

- 1326 Polyethylene (polythene) film for packaging and allied purposes
- 1327 Standard environments for conditioning and testing plastics materials
- 1635 Methods of testing pressure sensitive adhesive tape
- 1635.3.1 Method 3.1: Adhesion strength
- 1635.5.1 Method 5.1: Breaking strength
- 2102 External micrometers
- 2193 Methods for calibration and grading of force-measuring systems of testing machines
- 2280 Ductile iron pressure pipes and fittings
- 2400 SAA Packaging Code
- 2400.12 Part 12: Adhesive closing and sealing tapes
- 3681 Guidelines for the application of polyethylene sleeving to ductile iron pipelines and fittings
- CK24 Code of practice for outdoor weathering of plastics in the Australian environment
- CK24.1 Part 1: Commercial products
- ASTM
- D 1709 Test method for impact resistance of polyethylene film by the free-falling dart method
- D 1922 Test method for propagation tear resistance of plastic film and thin sheeting by pendulum method

3 DEFINITIONS. For the purpose of this Standard, the definitions below apply.

3.1 Loose polyethylene sleeving—polyethylene film usually in tube form, used to encase pipe or fittings but which is not bonded to the surface.

3.2 Layflat tube—a tubular form of polyethylene film which has been flattened for handling and storage.

3.3 Nominal size (DN)—a numerical designation of size which is common to all components in a pipeline system other than components designated by outside diameters or by thread size. It is a convenient round number for reference purposes and is only loosely related to manufacturing dimensions.

NOTE: It is designated by DN followed by a number.

3.4 Impact failure load (F_{50})—the missile mass in grams, estimated statistically, at which 50% of the specimens would fail in the specified test.

4 SLEEVING MATERIAL COMPOSITION. Sleeving shall be of non-regenerated polyethylene. The polymer shall have a maximum nominal melt flow index of 1.0, and density not less than 915 kg/m³ or greater than 930 kg/m³, complying with AS 1326.

A highly dispersed ultra-violet stabilizer shall be present in the film. When exposed to natural ultra-violet radiation of a level equivalent to 7 weeks exposure at Alice Springs (see AS CK24.1 for equivalence of sunshine hours) the physical properties defined in Clause 6 shall be retained.

The colour of the film should contrast with black pipe.

5 SLEEVING DIMENSIONS.

5.1 General. Sleeving shall be supplied in the form of layflat tubing complying with AS 1326.

5.2 Width. Table 1 gives the recommended layflat tube width for each size of pipe. Tolerance on width shall comply with AS 1326.

TABLE 1
RECOMMENDED LAYFLAT WIDTH OF POLYETHYLENE SLEEVING FOR VARIOUS SIZES OF PIPE

Nominal size (complying with AS 2280)	Layflat tube width
	mm
DN 80	350
DN 100	350
DN 150	425
DN 200	525
DN 225	635
DN 250	635
DN 300	725
DN 375	875
DN 450	1 100
DN 500	1 100
DN 600	1 270
DN 750	1 500

5.3 Thickness. Nominal film thickness shall be not less than 200 micrometres. Tolerance on thickness shall comply with AS 1326.

6 SLEEVING PERFORMANCE REQUIREMENTS.

NOTE: Performance requirements refer to weathered film complying with Clause 4.

6.1 Ultimate tensile strength. When tested in accordance with Appendix A, the breaking load of the film shall not be less than 50 N in either machine or transverse directions.

6.2 Elongation. When tested in accordance with Appendix A, the elongation shall be not less than 1000% in either machine or transverse directions.

6.3 Impact resistance. When tested in accordance with Appendix B, the impact resistance of the film shall be not less than 900 g.