

SUPERSEDED BY

^{Dup}
AS 1615 - 1983

AS 1615 — 1980
UDC 615.473

Australian Standard
1615 — 1980

SINGLE-USE NEEDLES (STERILE)
FOR INSULIN INJECTION



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



e

THE FOLLOWING SCIENTIFIC, INDUSTRIAL AND GOVERNMENTAL ORGANIZATIONS and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian Chamber of Commerce
Australian Dental Standards Laboratory
Australian Diabetes Society
Australian Medical Association
Commonwealth and State Departments of Health
Confederation of Australian Industry
Diabetes Federation of Australia
Federated Pharmaceutical Service Guild of Australia
Hospitals and Hospital Associations
New South Wales Government Stores Department

This standard, prepared by Committee MD/2, Hypodermic Equipment for Insulin Injection, was approved on behalf of the Council of the Standards Association of Australia on 21 April 1980, and was published on 1 June 1980.

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by monthly listings in the SAA journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 77101.

AUSTRALIAN STANDARD

**SINGLE-USE NEEDLES (STERILE)
FOR INSULIN INJECTION**

AS 1615—1980

First published	1974
Second edition	1980

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR STREET, NORTH SYDNEY, N.S.W.**



ISBN 0 7262 1941 X

PREFACE

This standard was prepared under the direction of the Medical Materials and Equipment Standards Committee, to supersede AS 1615—1974.

Unlike the 1974 edition, this standard specifies only one size of needle, 0.45 mm × 13 mm (SWG 26 × $\frac{1}{2}$ in). New appendices deal with tests for particulate contamination, extractable metals, pyrogens, toxicity and sterility.

Facilities for testing for compliance with this standard are available at the Australian Dental Standards Laboratory, 240 Langridge Street, Abbotsford, Victoria, 3067.

This standard makes reference to the following standards:

- AS 1077 Single-use 1 mL Syringes (Sterile) for the Injection of 100 Units per Millilitre Insulin (U - 100)
 - AS 1094 Single-use Syringes (Sterile) for General Medical Use
 - AS 1157 Methods of Testing Materials for Resistance to Fungal Growth Part 7 — Resistance of Papers and Paper Products to Surface Fungal Growth
 - AS 1386 Cleanrooms and Work-stations
 - AS 1444 Wrought Alloy Steels of the AISI-SAE H and Standard Steel Types
 - AS 1600 Conical Fittings with 6 percent (Luer) Taper for Hypodermic and Other Surgical Equipment
 - AS 2134 Code of Practice for the Chemical Analysis of Materials by Flame Atomic Absorption Spectroscopy
 - AS G18 Wrought Alloy Steels of the BS 970 En Series Type
- and to the European Pharmacopoeia, the British Pharmacopoeia, and the United States Pharmacopoeia.

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1980
Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>
SPECIFICATION	
1 Scope	4
2 Description of Needle	4
3 Definitions	4
4 Requirements for Needle Tube	4
5 Requirements for Hub	4
6 Joint of Needle Tube with Hub	5
7 Dead Space	5
8 Extractable Metals	5
9 Pyrogens	5
10 Toxicity	5
11 Method of Sterilization	5
12 Sterility	5
13 Particulate Contamination	5
14 Packing	5
15 Labelling	6
APPENDICES	
A Method of Testing Needles for Resistance to Corrosion	7
B Method for Testing Stiffness of Needle	8
C Method for Testing Resistance of Needle to Bending	9
D Method for Testing Elastic Recovery of Needle	11
E Method of Testing Hub for Cleanliness	13
F Method for Testing Watertightness of Joint Between Needle Tube and Hub	14
G Method for Testing Strength of Joint Between Needle Tube and Hub	15
H Method for Determining Dead Space in Needles	16
J Method for Determining Extractable Metals in Needles	17
K Method of Testing Needles for Pyrogens	18
L Method of Testing Needles for Toxicity	18
M Method of Testing Needles for Sterility	19
N Method of Testing Needles for Particulate Contamination	22
O Assessment of Compliance	24

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
for
SINGLE-USE NEEDLES (STERILE) FOR INSULIN INJECTION

1 SCOPE. This standard specifies requirements for sterilized individually packed hypodermic needles intended for use once only solely for the injection of insulin. The needle tubes are 0.45 mm in nominal external diameter and 13 mm in length.* The needles have the 6 percent (Luer) fitting.

NOTE: Advisory information on sampling and assessing for compliance with this standard is given in Appendix O.

2 DESCRIPTION OF NEEDLE. The essential components of the needle are the needle tube and the hub. One end of the needle tube is bonded in the hub; the other end of the needle tube is bevelled and sharpened to form the point. The hub is hollow, forming a socket into which the nozzle of a syringe can be fitted. The space enclosed by the wall of the needle tube is termed the lumen.

3 DEFINITIONS. For the purpose of this standard, the following definitions apply:

3.1 Unit—a needle with any sheath attached in accordance with Clause 14.1 and any attached hub cover, as illustrated in Fig. 1.

3.2 Unit pack—a pack containing a single unit.

3.3 Multiple pack—a pack, not being a store pack, containing two or more unit packs.

3.4 Store pack—a pack containing one or more multiple packs.

3.5 Water—purified water of the British Pharmacopoeia.

3.6 Needle sheath—the removable protective cover.

4 REQUIREMENTS FOR NEEDLE TUBE.

4.1 Composition. The needle tube shall be made of stainless steel which is either—

- (a) one of the martensitic steels specified for the En 56 series in AS G18 or one of the steels specified in Table 1.3 of AS 1444; or
- (b) one of the austenitic steels specified for the En 58 series in AS G18 or one of the steels specified in Table 1.2 of AS 1444.

4.2 Appearance. When the needle is examined without magnification and with magnification of about $10\times$ —

- (a) the needle tube shall appear straight, cylindrical, and of uniform wall thickness;
- (b) the outside surface of the needle shall appear smooth and clean and shall exhibit no corrosion, pitting, tool marks, sinks, voids, or stress marks;

- (c) the inside surface of the needle tube shall exhibit no corrosion, no extraneous matter other than a film of lubricant, and no obstruction to the flow of liquid; and
- (d) the pointed end of the needle tube shall appear sharp and strong, shall exhibit smooth sharpened surfaces on at least three aspects, and shall exhibit no barbs, hooks, feathered edges or other defects.

4.3 Resistance to Corrosion. When the needle is tested in accordance with Appendix A, the needle tube shall not show signs of corrosion.

4.4 Dimensions.

- (a) The length of the needle tube (dimension A in Fig. 1) shall be not less than 12 mm and not more than 14 mm.
- (b) The external diameter of the needle tube shall be not less than 0.43 mm and not more than 0.47 mm.
- (c) The internal diameter of the needle tube shall be not less than 0.25 mm.
- (d) The angle of the point (angle θ in Fig. 2) shall be not greater than 15 degrees and not less than 9 degrees.

4.5 Mechanical Properties.

4.5.1 Stiffness. When the needle is tested in accordance with Appendix B, the deflection of the needle tube shall not exceed 0.20 mm.

4.5.2 Resistance to bending. When the needle is tested in accordance with Appendix C, the needle tube shall not fracture.

4.5.3 Elastic recovery. When the needle is tested in accordance with Appendix D, the angle of permanent set of the needle tube shall not exceed 1 degree.

5 REQUIREMENTS FOR HUB.

5.1 Composition. The hub of the needle shall be made of material which does not affect the therapeutic activity of insulin when the needle is used to inject any preparation of insulin.

5.2 Appearance. When the needle is examined with a magnification of about $10\times$ —

- (a) the surfaces of the hub shall exhibit no sinks, voids or stress marks, no detached or detachable material, no extraneous matter and no obstruction to the flow of liquid through the needle;
- (b) the socket shall appear coaxial with the needle tube; and
- (c) any projection of the needle tube into the socket shall not exceed 1.5 mm in length.

* Formerly 26 SWG \times $\frac{1}{2}$ in.