

Australian Standard™

**Masonry cement**

This Australian Standard was prepared by Committee BD-010, Cement. It was approved on behalf of the Council of Standards Australia on 13 December 2002 and published on 16 January 2003.

---

The following are represented on Committee BD-010:

Ash Development Association of Australia  
Association of Consulting Engineers Australia  
Australasian Slag Association  
Australian Pre-mixed Concrete Association  
Austroads  
Cement & Concrete Association of Australia  
Cement Industry Federation  
Concrete Institute of Australia  
CSIRO Manufacturing and Infrastructure Technology  
Housing Industry Association  
Institute of Engineers Australia  
University of New South Wales

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

*This Standard was issued in draft form for comment as DR 98633.*

# Australian Standard™

## Masonry cement

Originated as AS A152—1969.  
Previous edition AS 1316—1972.  
Second edition 2003.

### **COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5022 2

## PREFACE

This Standard was prepared by Standards Australia Committee BD-010, Cement, to supersede AS 1316—1972.

The objective of this Standard is to provide manufactures and users of masonry cement with specifications covering materials, composition, sampling, testing, physical requirements, packing and marking for masonry cement intended for use in mortars for masonry construction in conjunction with masonry units of clay, calcium silicate, concrete and square dressed natural stone.

This Standard incorporates the following major changes to AS 1316—1972:

- (a) In line with Standards Australia policy of producing performance-based Standards, masonry cements are specified in terms of their performance, wherever possible.
- (b) An attempt has been made to closely align this Standard with developments in AS 3700, *Masonry structures*, particularly in adopting the same masonry mortar classification.
- (c) The revision of AS 1316—1972 produced two separate Standards; a specification for masonry cement (this Standard), and a suite of test methods for masonry cement published separately as part of the AS/NZS 2350 series.

## CONTENTS

	<i>Page</i>
FOREWORD .....	4
1 SCOPE .....	5
2 REFERENCED DOCUMENTS .....	5
3 MATERIALS .....	5
4 MASONRY CEMENT TYPES AND COMPOSITION .....	6
5 SAMPLING AND TESTING .....	6
6 REQUIREMENTS .....	6
7 PACKING, MARKING AND DELIVERY OF BAGGED MASONRY CEMENT .....	7

## FOREWORD

Masonry cement is a finely ground mixture of portland cement clinker, calcium sulfate, and suitable inorganic materials such as hydrated lime as defined by AS 1672.1—1997, *Limes and limestones*, Part 1: *Limes for building*, and mineral additions, as defined by AS 3972—1997, *Portland and blended cements*. Suitable air-entraining agents or plasticizers, or both, may also be incorporated.

Masonry cement is intended for use in mortars for masonry construction in conjunction with masonry units of clay, calcium silicate, concrete and square dressed natural stone. When mixed with fine aggregates (sand) it produces a smooth, plastic and cohesive mortar characterized by a lower rate of strength development than that of general purpose portland cement. Hence, it may not be suitable for structural brickwork or for special purpose mortars where high strength is required although its strength may be increased by gauging it with portland cement. For normal masonry construction, however, the lower rate of strength development is an advantage as shrinkage, thermal and other movements in the masonry can be better accommodated in the mortar joints and unsightly cracking prevented. Masonry cement is not intended for use in any form of structural concrete (plain, reinforced or prestressed), floors or foundation work.

## STANDARDS AUSTRALIA

### Australian Standard Masonry cement

#### 1 SCOPE

This Standard specifies requirements for masonry cement, a hydraulic cement intended for use in mortars for masonry construction in conjunction with masonry units of clay, calcium silicate, concrete and square dressed natural stone.

This Standard does not provide for all the requirements that may be needed in specific applications of masonry cement, e.g., high strength mortars.

NOTE: Autoclaved aerated concrete units (AAC) are laid in thin bed mortars that are proprietary, purpose-made mortars.

#### 2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

##### AS

- |        |  |
|--------|--|
| 1478   | Chemical admixtures for concrete, mortar and grout—Admixtures for concrete   |
| 1672   | Limes and limestones   |
| 1672.1 | Part 1: Limes for building   |
| 2349   | Method of sampling portland and blended cements                              |
| 3582   | Supplementary cementitious material for use with portland and blended cement |
| 3582.1 | Part 1: Fly ash  |
| 3582.2 | Part 2: Slag—Ground granulated iron blast-furnace                            |
| 3700   | Masonry structures   |
| 3972   | Portland and blended cements   |

##### AS/NZS

- |         |   |
|---------|---|
| 2350    | Methods of testing portland, blended and masonry cements        |
| 2350.1  | Method 1: Sampling and sample preparation                       |
| 2350.4  | Method 4: Setting time of portland and blended cements          |
| 2350.11 | Method 11: Compressive strength of portland and blended cements |
| 2350.16 | Method 16: Determination of air content of masonry cement       |
| 2350.17 | Method 17: Determination of soundness of masonry cement         |
| 2350.18 | Method 18: Determination of water retention of masonry cement   |

#### 3 MATERIALS

##### 3.1 Portland cement clinker

Portland cement clinker shall comply with AS 3972.

##### 3.2 General purpose portland cement

General purpose portland cement shall comply with AS 3972.

##### 3.3 General purpose blended cement

General purpose blended cement shall comply with AS 3972.

##### 3.4 Fly ash

Fly ash shall comply with AS 3582.1.