

Australian/New Zealand Standard™

Characterization of structural timber

Part 1: Test methods



AS/NZS 4063.1:2010

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee TM-001, Timber Structures. It was approved on behalf of the Council of Standards Australia on 28 October 2009 and on behalf of the Council of Standards New Zealand on 30 October 2009.

This Standard was published on 23 June 2010.

The following are represented on Committee TM-001:

A3P
Association of Consulting Engineers Australia
Australian Building Codes Board
Australian Timber Importers' Federation
Australian Wood Panels Association
BRANZ
CSIRO Manufacturing & Materials Technology
Curtin University of Technology
Department of Primary Industries and Fisheries Queensland
Engineered Wood Products Association of Australasia
Engineers Australia
Frame and Truss Manufacturers Association Australia
Glued Laminated Timber Association of Australia
Master Builders Australia
Monash University
New Zealand Timber Industry Federation
Scion
Timber Queensland
University of Auckland
University of Technology, Sydney
Wood Processors Association

Additional Interests:

Mr Bruce Hutchings

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR 08192.

Australian/New Zealand Standard™

Characterization of structural timber

Part 1: Test methods

Originated as AS/NZS 4063:1992
Revised, in part, and redesignated as AS/NZS 4063.1:2010.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 476, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6140

ISBN 978 0 7337 9336 3

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee TM-001, Timber Structures, to supersede (in part) AS/NZS 4063:1992, *Timber—Structural—products—Strength and stiffness evaluation*.

The objective of this Standard is to specify requirements for testing rectangular sections of sawn solid timber of commercial structural size to provide data for the determination of characteristic values for structural design. It specifies the test methods only. Design characteristic values are determined as specified in Part 2 of the AS/NZS 4063 series using the test results generated by the test methods specified in this Standard.

This Standard is based on ISO 13910, *Structural timber—Characteristic values of strength-graded timber—Sampling, full-size testing and evaluation*, and modified to form the AS/NZS 4063 series, *Characterization of structural timber*, which comprises the following parts:

AS/NZS

4063 *Characterization of structural timber*

4063.1 Part 1: Test methods (this Standard)

4063.2 Part 2: Determination of characteristic values

The test methods for bending, beam shear and tension and compression parallel to grain included in this Standard have been adapted from ISO 13910, and are similar to the methods described in AS/NZS 4063:1992. Notable modifications include the following:

- (a) The practice of calculating and reporting a nominal modulus of rupture (bending failure stress) as the basis for determination of a characteristic value in bending has been discontinued. This Standard now requires the modulus of rupture to be calculated using the estimated bending moment at the failure point. This change reflects the expectations of designers that a characteristic value in bending represents a minimum 5-th percentile breaking stress at each and every point along the length of a beam.
- (b) The length of the test piece for determination of compression strength has been increased to account for the longer lengths commonly used in service, an example of which is wall framing. The test method allows for the test piece to be tested in shorter length segments.

This Standard also includes test methods for determination of characteristic values for properties not previously included in AS/NZS 4062:1992. These additional test methods have been adapted from various sources. Other test methods for which there is limited experience of their application are included in an informative appendix.

The term ‘informative’ has been used in this Standard to define the application of the appendix to which it applies. An ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 APPLICATION	4
1.3 NORMATIVE REFERENCES	4
1.4 DEFINITIONS	4
1.5 SYMBOLS AND ABBREVIATED TERMS.....	5
SECTION 2 TEST METHODS	
2.1 GENERAL	7
2.2 STANDARD TEST CONDITIONS	7
2.3 DENSITY	7
2.4 BENDING STRENGTH AND APPARENT MODULUS OF ELASTICITY	8
2.5 TENSION STRENGTH PARALLEL TO GRAIN	9
2.6 COMPRESSION STRENGTH PARALLEL TO GRAIN	10
2.7 BEAM SHEAR STRENGTH	10
2.8 BEARING STRENGTH PERPENDICULAR TO GRAIN	11
2.9 BEARING STRENGTH PARALLEL TO GRAIN.....	12
2.10 MODULUS OF RIGIDITY IN TORSION	14
2.11 TEST REPORT	14
APPENDIX A OTHER TEST METHODS	16
BIBLIOGRAPHY	21

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Australian/New Zealand Standard
Characterization of structural timber

Part 1: Test methods

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard specifies test methods for measuring the structural properties of rectangular sections sawn solid timber of commercial structural size.

NOTE: The test methods specified in this Standard may be adapted to measure the structural properties of rectangular sections of other structural timber materials and the properties or capacities and rigidities, as appropriate, of non-rectangular sections, such as round timber (or poles) and composite sections such as I-sections.

1.2 APPLICATION

The data obtained from the test methods specified in this Standard are to be used in AS/NZS 4063.2.

NOTE: The test methods given in this Standard may be used to provide data for other purposes.

1.3 NORMATIVE REFERENCES

The following are the normative documents referenced in this Standard:

AS

4063 Characterization of structural timber

4063.2 Part 2: Determination of design characteristic values

AS/NZS

1080 Timber—Methods of test

1080.1 Part 1: Moisture content

1.4 DEFINITIONS

For the purposes of this Standard, the following terms and definitions apply.

1.4.1 Sample piece

A full length piece of timber from the reference population as manufactured.

1.4.2 Stress-graded timber

Timber that has been graded for assignment of a stress grade.

1.4.3 Test piece

A segment cut from a sample piece for the purpose of testing to measure a specific structural property.

1.4.4 Depth, d

The greater cross-sectional dimension of a rectangular section sample piece or test piece, measured perpendicular to the major principal axis X-X, as illustrated in Figure 1.