

AS 2875/Amdt 1/1987-11-02

STANDARDS ASSOCIATION OF AUSTRALIA
Incorporated by Royal Charter

AMENDMENT No 1

to

AS 2875—1986

**ALLOY STEEL CYLINDERS FOR COMPRESSED GASES—
SEAMLESS—0.1 kg TO 500 kg**

CORRECTION

The 1986 edition of AS 2875 is corrected as follows; the amendment should be inserted in the appropriate place.

SUMMARY: This amendment applies to Table C1.

Published on 2 November 1987.

30 OCT 1987

AUSTRALIAN STANDARD

**ALLOY STEEL CYLINDERS FOR
COMPRESSED GASES—
SEAMLESS—
0.1 kg to 500 kg**

AS 2875—1986

First published (as AS B114)	1960
AS 2875 first published	1986

*To be verified
[June 1986]*

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.

ISBN 0 7262 4188 1



29 MAY 1986

PREFACE

This standard was prepared by the Association's Committee on Gas Cylinders. It supersedes AS B114—1960, Alloy Steel Cylinders for the Storage and Transport of Permanent Gases and High Pressure Liquefiable Gases.

Changes introduced in this standard include the following:

- (a) Requirements are now expressed in SI units.
- (b) Type 4 chemical composition has been aligned with Code Mn and MnH steel of BS 5045, Part 1. This is because no gas cylinders are known to have been made from the previous Type A composition, but a steel to the composition now specified is available in Australia. Corresponding changes to heat treatment temperatures have been made.
- (c) The maximum permissible stress (f) at the hydrostatic test pressure has been increased from 90 percent to 95 percent of the nominal yield which for calculation purposes gives a value for f of 570 MPa. This increase was agreed to following a submission that drew the following conclusions:
 - (i) The change will result in a cylinder wall that for cylinders for permanent gases is thicker than that required by U.S. specification DOT 3AA, to which there are millions of cylinders that are giving satisfactory service.
 - (ii) The change will result in a cylinder wall that for cylinders for liquefiable gases is thicker than that required by BS 5045, Part 1, to which there are millions of cylinders that are giving satisfactory service.
- (d) Hydrostatic and pulsation type tests are included.
- (e) The impact test has been omitted as it was considered to be not relevant for the thicknesses involved and the conditions of use in Australia.

The hydrostatic and pulsation type tests may be waived where the design is that already used for a cylinder accepted as complying with AS B114. For cylinders of a new design, as judged by the Inspecting Authority, all the type testing requirements are to apply.

The term 'new design' is not yet defined, but the following features are considered to be relevant and may be adopted for such a definition by the Inspecting Authorities:

- (i) Manufacture in a different factory.
- (ii) Manufacture by a different process.
- (iii) Manufacture from steel of different nominal chemical compositions.
- (iv) A different heat treatment.
- (v) A base profile or base thickness change relative to the cylinder diameter and calculated minimum wall thickness.
- (vi) A length increase of the cylinder of more than 50 percent (cylinders with an L/D ratio less than 3 must not be used as reference cylinders for any new design with an L/D ratio greater than 3).
- (vii) A diameter change of more than 5 percent.
- (viii) An increase in hydraulic test pressure that requires a change in design wall thickness.

Notwithstanding (viii) above, it is considered that where a gas cylinder is to be used in a lower pressure duty than that for which design approval has been given, it is not to be deemed as being of new design.

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1986

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 STEEL	4
5 DESIGN	5
6 MANUFACTURE	5
7 HEAT TREATMENT	5
8 TESTING	5
9 RECORD AND TEST CERTIFICATE(S)	6
10 MARKING	6
11 PREPARATION FOR DESPATCH	7
 APPENDICES	
A SUGGESTED MINIMUM INFORMATION TO BE SUPPLIED BY THE PURCHASER	8
B DESIGN AND BATCH TESTS SPECIFIED IN THIS STANDARD	9
C TENSILE TEST PIECE	11
D METHODS FOR DERIVING THE PERCENTAGE INCREASE OF WATER CAPACITY AFTER HYDROSTATIC TYPE TEST RUPTURE	12
E SUGGESTED FORM OF MANUFACTURER'S CERTIFICATE	14

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

for

ALLOY STEEL CYLINDERS FOR COMPRESSED GASES—
SEAMLESS—0.1 kg to 500 kg

1 SCOPE. This standard specifies requirements for the steel, design, manufacture, testing, and marking of seamless gas cylinders manufactured from alloy steel, of water capacity not less than 0.1 kg and not greater than 500 kg.

NOTE: Appendix A lists the suggested minimum information that should be supplied by the purchaser when ordering gas cylinders covered by this standard.

2 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

AS 1050	Methods for the Analysis of Iron and Steel
AS 1213	Iron and Steel—Methods of Sampling
AS 1391	Methods for Tensile Testing of Metals
AS 2030.1	SAA Gas Cylinders Code, Part 1—Cylinders for Compressed Gases Other than Acetylene
AS 2337	Gas Cylinder Test Stations
AS 2505.1	Methods for Bend and Related Testing of Metals, Part 1—Sheet, Strip and Plate
AS K1	Methods for the Sampling and Analysis of Iron and Steel
BS 5045	Transportable Gas Containers Part 1—Seamless Steel Containers
ISO 2566/1	Steel—Conversion of Elongation Values, Part 1—Carbon and Low Alloy Steels

3 DEFINITIONS. For the purpose of this standard, the definitions given in AS 2030.1, and the following definition apply:

Inspector—a person, acceptable to the Inspecting Authority, who ensures and certifies that all the

inspections specified herein have been carried out and that the cylinders comply with all the requirements of this standard.

4 STEEL.

4.1 Steelmaking process. The steel shall be made by the open hearth, basic oxygen, or an electric furnace process. The steelmaker should supply to the cylinder manufacturer a certificate showing the process of steel manufacture.

NOTES:

1. The basic oxygen process means the process of making steel in a basic converter blown with commercially pure oxygen.
2. Additional refining by vacuum-arc-remelt (VAR), electroslag-refining (ESR) or vacuum degassing is permitted.

4.2 Chemical analysis. A chemical analysis of the steel from each ladle shall be made to determine the proportions of the specified elements. The method of sampling shall be in accordance with AS 1213, and the analysis procedures shall be not less accurate than the procedures specified in AS 1050 and AS K1, as appropriate.

The chemical analysis of the steel shall comply with Table 1, and the steelmaker should supply to the cylinder manufacturer a certificate showing the chemical analysis of elements listed in Table 1.

4.3 Identification. Steel sections shall be individually identified for record purposes.

4.4 Steelmaker's inspection facilities. Facilities for inspection of the steel at the steelmaker's works shall be afforded to the representative of the cylinder manufacturer.

TABLE 1
CHEMICAL ANALYSIS

Element	Analysis, percent					
	Min.	Max.	Min.	Max.	Min.	Max.
	Steel type					
	A*		B		C	
Carbon	—	0.40	—	0.35	0.27	0.35
Silicon	0.10	0.35	0.10	0.40	0.10	0.40
Manganese	1.30	1.70	0.40	0.80	0.50	0.70
Nickel	—	—	—	0.50†	2.30	2.80
Chromium	—	—	0.80	1.20	0.50	0.80
Molybdenum	—	—	0.15	0.25	0.40	0.70
Sulphur	—	0.050	—	0.050	—	0.050
Phosphorus	—	0.050	—	0.050	—	0.050

* Identical to Code Mn and MnH of BS 5045, Part 1.

† As a residual.