AS 4459.11—1997
ISO 10545-11:1994
Reconfirmed 2017

Australian Standard®

Methods of sampling and testing ceramic tiles

Part 11: Determination of crazing resistance for glazed tiles

[ISO title: Ceramic tiles, Part 11: Determination of crazing resistance for glazed tiles]

This Australian Standard was prepared by Committee BD/44, Fixing of Ceramic Tiles. It was approved on behalf of the Council of Standards Australia on 28 February 1997 and published on 5 June 1997.

The following interests are represented on Committee BD/44:

Adhesives and Sealants Manufacturers Association of Australia

The Association of Consulting Engineers Australia

Australian Chamber of Commerce and Industry

Australian Stone and Terrazzo Association

Australian Stone Industry Association

Australian Tile Council

Ceramic Tile Manufacturers Association

Construction, Forestry, Mining and Energy Union

CSIRO, Division of Building, Construction and Engineering

Department of Fair Trading, N.S.W.

Master Builders Australia

New South Wales TAFE Commission

N.S.W. Tile Industry Training Committee

This Standard was issued in draft form for comment as DR 96084.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 4459.11—1997

Methods of sampling and testing ceramic tiles

Part 11: Determination of crazing resistance for glazed tiles

RECONFIRMATION NOTICE

Technical Committee BD-044 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 21 January 2016.

The following are represented on Technical Committee BD-044:

Australian Industry Group
Australian Stone Advisory Association
Australian Tile Council
Ceramic Tile Manufacturers Association of Australia
Institute of Building Consultants
Master Builders Australia
Master Glazed Wall & Floor Tile Layers Association of SA
Plastics and Chemicals Industries Association
Property Council of Australia
Surface Coatings Association Australia

NOTES

Australian Standard®

Methods of sampling and testing ceramic tiles

Part 11: Determination of crazing resistance for glazed tiles

First published as AS 4459.11—1997.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7337 1083 2

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee BD/44, Fixing of Ceramic Tiles. It is identical with and has been reproduced from ISO 10545-11:1994, *Ceramic tiles*, Part 11: *Determination of crazing resistance for glazed tiles*, and is the result of a consensus among the representatives on the Joint Committee that it be produced as an Australian Standard.

The Standard is one of a series of methods of sampling and testing ceramic tiles that are currently under development.

For the purpose of this Australian Standard, the ISO/IEC text should be modified as follows:

(a) *Terminology* The words 'Australian Standard' should replace the words 'International Standard' wherever they appear.

(b) *Decimal marker* A full point should be substituted for a comma where it appears as a decimal marker.

(c) *References* The references to International Standards should be replaced by references to the following Australian Standards:

Reference to International Standard or other Publication		*Australian Standard*
ISO		AS
13006	Ceramic tiles— Definitions, classification, characteristics and marking	—

CONTENTS

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10545-11 was prepared by Technical Committee ISO/TC 189, *Ceramic tile*.

ISO 10545 consists of the following parts, under the general title *Ceramic tiles:*

— *Part 1: Sampling and basis for acceptance*

— *Part 2: Determination of dimensions and surface quality*

— *Part 3: Determination of water absorption, apparent porosity, apparent relative density and bulk density*

— *Part 4: Determination of modulus of rupture and breaking strength*

— *Part 5: Determination of impact resistance by measurement of coefficient of restitution*

— *Part 6: Determination of resistance to deep abrasion for unglazed tiles*

— *Part 7: Determination of resistance to surface abrasion for glazed tiles*

— *Part 8: Determination of linear thermal expansion*

— *Part 9: Determination of resistance to thermal shock*

— *Part 10: Determination of moisture expansion*

— *Part 11: Determination of crazing resistance for glazed tiles*

— *Part 12: Determination of frost resistance*

— *Part 13: Determination of chemical resistance*

— *Part 14: Determination of resistance to stains*

— *Part 15: Extraction of lead and cadmium from glazed tiles*

— *Part 16: Determination of colour differences*

— *Part 17: Determination of coefficient of friction*

Methods of sampling and testing ceramic tiles

Part 11: Determination of crazing resistance for glazed tiles

1 Scope

This part of ISO 10545 defines a test method for determining the crazing resistance of all glazed ceramic tiles except when the crazing is an inherent decorative feature of the product.

NOTE 1 ISO 13006:—, *Ceramic tiles — Definitions, classification, characteristics and marking* (to be published), provides property requirements for tiles and other useful information on these products.

2 Definition

For the purposes of this part of ISO 10545, the following definition applies.

2.1 craze: Crack, showing as a fine hairline, limited to the glazed surface of a tile.

3 Principle

Determination of the resistance to the formation of crazes by subjecting whole tiles to steam at high pressure in an autoclave, then examination of the tiles for crazes after applying a stain to the glazed faces.

4 Apparatus

4.1 Autoclave, of sufficient internal volume to accommodate five tiles with adequate separation. Ideally, the steam is fed from an external source in order to maintain a pressure of (500 ± 20) kPa, that is, a steam temperature of (159 ± 1) °C for 2 h.

Alternatively, a directly heated autoclave may be used.

5 Test specimens

5.1 A minimum of five whole tiles shall be tested.

5.2 Exceptionally large tiles may be cut into pieces for enclosure in the autoclave, but all pieces shall be tested. The cut pieces shall be as large as possible.

6 Procedure

6.1 First examine the tiles for visible defects by viewing them with the naked eye (or with the aid of spectacles if usually worn) from a distance of 25 cm to 30 cm under an illumination of approximately 300 lx. All test specimens shall be free from crazing at the commencement of the test. The methylene blue solution described in 6.3 may be used to detect pretest crazing. Except in the case of freshly fired tiles being tested as part of a routine in-house quality assurance programme, the tile shall be prepared by reheating to (500 ± 15) °C at a rate not greater than 150 °C/h and with a soak of not less than 2 h.

6.2 Place the test specimens in the autoclave (4.1) in such a way that there is air space between them. Raise the pressure in the autoclave gradually for a period of 1 h until it reaches (500 ± 20) kPa, (159 ± 1) °C, and maintain this pressure for 2 h. Then turn off the steam source (or the heat supply in the case of directly heated autoclaves), allow the pressure to fall as rapidly as possible to atmospheric and cool the test specimens in the autoclave for 0,5 h. Bring the test specimens into the laboratory atmosphere, place them singly on a