

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 22: Higher rank coal—Mineral  
matter and water of constitution**

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 12 November 1999 and published on 10 January 2000.

---

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy  
Australian Coal Association  
Australian Coal Preparation Society  
Australian Institute of Energy  
Bureau of Steel Manufacturers of Australia  
CSIRO, Division of Energy and Technology  
Coalfield Geology Council of New South Wales  
Department of Mines and Energy, Queensland  
Electricity Supply Association of Australia  
Institution of Engineers, Australia  
Minerals Council of Australia  
University of Newcastle  
University of New South Wales  
University of Queensland

---

#### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for the improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, PO Box 1055, Strathfield, NSW 2135.

---

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 22: Higher rank coal—Mineral matter and water of constitution**

Originated as AS 1938.22—1983.  
Second edition 1992.  
Third edition 2000.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
PO Box 1055, Strathfield, NSW 2135, Australia

ISBN 0 7337 3075 2

## PREFACE

This Standard was prepared by the Standards Australia Committee MN/1, Coal and Coke, to supersede AS 1038.22—1992.

This revision confirms the methods for the determination of mineral matter in coal and for the determination of water of constitution.

Editorial changes have been made to bring the Standard into line with current style.

---

## CONTENTS

	<i>Page</i>
FOREWORD .....	3
1 SCOPE.....	5
2 REFERENCED DOCUMENTS .....	5
3 DEFINITIONS .....	6
4 SAFETY .....	6
5 SAMPLE.....	6
6 DETERMINATION OF MINERAL MATTER BY RADIO-FREQUENCY OXYGEN PLASMA OXIDATION.....	6
7 DETERMINATION OF MINERAL MATTER BY AIR OXIDATION AT 370°C.....	10
8 CALCULATIONS .....	12
9 WATER OF CONSTITUTION .....	14
10 USE OF MINERAL MATTER (PERCENT) AND WATER OF CONSTITUTION (PERCENT) IN DRY, MINERAL MATTER-FREE BASIS CALCULATIONS ...	15
11 REPORTING OF RESULTS.....	16
12 PRECISION .....	16
13 TEST REPORT.....	17
APPENDICES	
A APPLICABILITY OF MINERAL MATTER METHODS TO LOWER RANK COALS .....	18
B STATISTICAL DATA FOR THE DETERMINATION OF MINERAL MATTER AND WATER OF CONSTITUTION IN COAL .....	19

## FOREWORD

The organic material of coal is associated with mineral and other inorganic matter that has been deposited or formed within the coal. These constituents provide the ash obtained on combustion of the coal; however, the mineral matter-to-ash ratios are variable between and within seams. Accordingly, the mineral matter content of coal should be known if coal analyses are to be converted to the dry, mineral matter-free basis (i.e. organic coal basis).

Methods of calculating the mineral matter of coal from the percentage ash and other analyses have been specified for British coals in BS 1016.100:1994, *Methods for analysis and testing of coal and coke*, Part 100: *General introduction and methods for reporting results*. These equations are derived from the mineral compositions and associations found in British coals and are not always appropriate for Australian coals\*†‡.

ISO 602:1983, *Coal—Determination of mineral matter*, specifies a method for the direct determination of mineral matter using an acid demineralization procedure. The stated repeatability of this method is relatively poor, and figures for reproducibility are not given. Inherent in this determination is the necessity to make corrections for ash, insoluble pyrite and absorbed hydrochloric acid. Furthermore, the method may yield anomalous results on certain low rank coals§.

The direct determination of mineral matter (and associated water of constitution) in Australian coals has been investigated by Brown et al.‡, who describe the following procedures for the determination of mineral matter:

- (a) Air oxidation at 370°C of the coal substance.
- (b) Acid demineralization similar to that specified in ISO 602.
- (c) A combined procedure in which a hydrochloric acid extraction of carbonate, sulfate and phosphate minerals is followed by oxidation at 370°C.

Other methods for the determination of mineral matter are as follows:

- (i) Low-temperature oxidation (at approximately 150°C) of the coal substance with a radio-frequency (RF) excited oxygen plasma§.
- (ii) Low-temperature air oxidation at 370°C, with direct gravimetric determination of combined water\*\*.

\* BROWN, H.R., DURIE, R.A. and SCHAFER, H.N.S. The inorganic constituents in Australian coals. I—The direct determination of the total mineral-matter content. *Fuel*, 1959, 38, 295-308.

† BROWN, H.R., DURIE, R.A. and SCHAFER, H.N.S. The inorganic constituents in Australian coals. II—Combined acid-digestion-low-temperature oxidation procedure for determination of total mineral-matter content, water of hydration of silicate minerals and composition of carbonate minerals. *Fuel*, 1960, 39, 59-70.

‡ BROWN, N.A., CALLCOTT, T.G., and KIROV, N.Y. Notes on mineral matter in Australian Coals. Paper A6, Symposium on Australian fuels and their utilization, Newcastle, N.S.W. August 1959. Published by the Australian Membership of the Institute of Fuel.

§ FRAZER, F.W. and BELCHER, C.B. Quantitative determination of the mineral-matter content of coal by a radiofrequency-oxidation technique. *Fuel*, 1973, 52, 41-46.

\*\* BROWN, N.A., BELCHER, C.B. and CALLCOTT, T.G. Mineral matter in N.S.W. coke-making coals; composition, determination and effects. *J. Inst. Fuel*, 1965, 38, 198-206.