

Australian Standard[®]

**Methods for the analysis and
testing of coal and coke**

**Part 3: Proximate analysis of
higher rank coal**

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 13 February 1989 and published on 11 August 1989.

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Industry Research Laboratories
Australian Institute of Energy
Bureau of Steel Manufacturers of Australia
Coal Preparation Society of N.S.W.
Coal Preparation Society of Queensland
Confederation of Australian Industry
CSIRO, Division of Coal Technology
Department of Minerals and Energy, N.S.W.
Department of Mines, Qld
Department of Primary Industries and Energy
Electricity Supply Association of Australia
Institution of Engineers, Australia
Joint Coal Board
National Association of Testing Authorities, Australia
Queensland Coal Board
Royal Australian Chemical Institute
Standing Committee on Coalfield Geology of New South Wales
University of New South Wales

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 88019.

Australian Standard[®]

**Methods for the analysis and
testing of coal and coke**

**Part 3: Proximate analysis of
higher rank coal**

First published as part of AS CK2.III—1949.
Revised and redesignated AS K152.3—1965
(being BS1016: Part 3:1957 endorsed with amendment).
Second edition 1968.
AS K152.3—1968 withdrawn 1978.
Revised and redesignated AS 1038.3—1979.
Second edition 1989.

PREFACE

This Standard was prepared by the Standards Australia Subcommittee on Coal Evaluation under the supervision of the Committee on Coal and Coke and the direction of the Minerals Standards Board to supersede AS 1038.3-1979, *Methods for the analysis and testing of coal and coke, Part 3: Proximate analysis of hard coal*.

The differences from the previous edition are as follows:

- (a) The vacuum-drying method for moisture determination has been excluded.
- (b) The direct gravimetric method for moisture determination has been modified to use a flow-through tube for heating the sample.
- (c) The two methods for ash determination (single-furnace and two-furnace) have been combined to give a single method, with the option of using either one or two furnaces.

The differing temperature regimes, previously used, have been eliminated.

- (d) This Standard has been subdivided into the following sections:

Section 1 Scope and general requirements

Section 2 Determination of moisture in the analysis sample

Clause 2.2—Direct gravimetric method

Clause 2.3—Indirect gravimetric method

Section 3 Determination of ash

Section 4 Determination of volatile matter.

These subdivisions will allow easier future revision of Part 3 and enable reference to be made to specific procedures used, e.g. the determination of moisture. However this Standard is to be considered as a total document and each section should be read in conjunction with the other sections.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SECTION 1. SCOPE AND GENERAL	
1.1 SCOPE	4
1.2 REFERENCED DOCUMENTS	4
1.3 DEFINITIONS	4
1.4 SAFETY	4
1.5 SAMPLE	4
1.6 REPORTING OF RESULTS	4
1.7 PRECISION	4
1.8 TEST REPORT	4
SECTION 2. DETERMINATION OF MOISTURE IN THE ANALYSIS SAMPLE	
2.0 INTRODUCTION	5
2.1 SCOPE OF SECTION	5
2.2 DETERMINATION OF MOISTURE IN THE ANALYSIS SAMPLE— DIRECT GRAVIMETRIC METHOD	5
2.3 DETERMINATION OF MOISTURE IN THE ANALYSIS SAMPLE— INDIRECT GRAVIMETRIC METHOD	6
SECTION 3. DETERMINATION OF ASH	
3.0 INTRODUCTION	12
3.1 SCOPE OF SECTION	12
3.2 PRINCIPLE	12
3.3 APPARATUS	12
3.4 PROCEDURE	12
3.5 CALCULATION OF RESULTS	12
SECTION 4. DETERMINATION OF VOLATILE MATTER	
4.0 INTRODUCTION	13
4.1 SCOPE OF SECTION	13
4.2 PRINCIPLE	13
4.3 REAGENT	13
4.4 APPARATUS	13
4.5 PROCEDURE	14
4.6 CALCULATION OF RESULTS	14

STANDARDS AUSTRALIA

Australian Standard

Methods for the analysis and testing of coal and coke

Part 3: Proximate analysis of higher rank coal

SECTION 1. SCOPE AND GENERAL

1.1 SCOPE. This Standard sets out methods for the determination of moisture, ash and volatile matter on the analysis sample of higher rank coal in order to obtain its proximate analysis. Fixed carbon is calculated by difference.

1.2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard:

AS	
1038	Methods for the analysis and testing of coal and coke
1038.16	Part 16: Acceptance and reporting of results
2096	Classification and coding systems for Australian coals
2243	Safety in laboratories
2418	Glossary of terms relating to solid mineral fuels
2508	Safe storage and handling information cards for hazardous materials
2646	Sampling of solid mineral fuels
2646.6	Part 6: Hard coal—Preparation of samples
2706	Numerical values—Rounding and interpretation of limiting values

1.3 DEFINITIONS. For the purpose of this Standard, the definitions in AS 2418, and those below, apply.

1.3.1 Higher rank coal (as defined in AS 2096)—coal having a gross specific energy of 21 MJ/kg or greater on an ash-free moist basis *and* a gross specific energy of 27 MJ/kg or greater on a dry, ash-free basis.

1.3.2 Proximate analysis—the analysis of coal expressed in terms of moisture, ash, volatile matter and fixed carbon in the analysis sample.

1.3.3 Moisture in the analysis sample—the moisture in the analysis sample of coal after it has attained equilibrium with the laboratory atmosphere to which it has been exposed.

1.3.4 Ash—the inorganic matter remaining after the coal has been incinerated to constant mass under standard conditions.

1.3.5 Volatile matter—the loss in mass, less that due to moisture, that occurs when the coal is heated out of contact with air under standard conditions.

1.3.6 Fixed carbon—a calculated figure obtained by subtracting the sum of the percentages of moisture, ash and volatile matter in the analysis sample, from 100.

1.4 SAFETY. For information on laboratory safety, reference should be made to the relevant parts of AS 2243 and AS 2508.

1.5 SAMPLE.

1.5.1 General. The sample shall be the analysis sample prepared to a nominal top size of 212 μm . Sample preparation procedures are described in AS 2646.6.

1.5.2 Equilibration of the sample. The moisture content of the analysis sample shall be equilibrated with the laboratory atmosphere by exposure in a thin layer on a tray. Exposure time shall be kept to a minimum. The sample shall be thoroughly mixed immediately before analysis.

1.6 REPORTING OF RESULTS. The results, the means of duplicate determinations for moisture, ash and volatile matter, shall be reported to the nearest 0.1 percent, rounded in accordance with AS 2706. The difference between 100 and the sum of the three results shall be reported as 'fixed carbon'.

For the calculation of results to bases other than 'air-dry', refer to AS 1038.16.

1.7 PRECISION. The values for repeatability and reproducibility should not exceed those given in Table 1.1. Otherwise, reference shall be made to AS 1038.16.

TABLE 1.1
PRECISION FOR MOISTURE, ASH AND
VOLATILE MATTER

Property	Repeatability % absolute	Reproducibility, % absolute
Moisture (air-dry): < 5% ≥ 5%	0.1 2.5% of mean	See Note
Ash (dry): < 10% ≥ 10% ≤ 20% > 20%	0.10 0.15 0.20	0.15 0.25 0.30
Volatile matter (dry): < 10% ≥ 10%	0.2 0.2	0.5 1.0

NOTE: For the moisture determinations, the results obtained will depend on the humidity conditions in the different laboratories. Since these conditions will vary, it is not practical to quote limiting values for reproducibility.

1.8 TEST REPORT. The test report shall contain the following information:

- Complete identification of the sample tested.
- Reference to this Australian Standard, i.e. AS 1038.3, and the particular method(s) used (e.g. Clause 2.2).
- Results of the determinations carried out for moisture, ash, volatile matter and fixed carbon, together with the relevant analysis basis (e.g. air-dry; dry, ash-free), as appropriate.