

PPA ED.

Australian Standard®

---

**Polybutylene pipe systems**

**Part 2: Polybutylene (PB) pipe for hot and cold water applications**

---



**AS/NZS 2642.2:1994**  
**Polybutylene (PB) pipe for hot and cold water applications**  
*(In Professional Package 61A)*

11pp DD  
Specifies materials, dimensions and performance requirements for polybutylene pipe for hot and cold water applications, including domestic, industrial and agricultural purposes. Applies to pipes of up to 125 mm nominal outside diameter with a wall thickness no greater than 15 mm but does not apply to a wall thickness of less than 1.6 mm.

*Committee PL3. Supersedes AS 2642.2—1989.  
Draft for Comment DR 92037. Publication date  
1994-01-17. ISBN 0 7262 8555 2.*



This Australian Standard was prepared by Committee PL/3, Polybutylene Pipe Systems. It was approved on behalf of the Council of Standards Australia on 4 May 1989 and published on 13 November 1989.

---

The following interests are represented on Committee PL/3:

Confederation of Australian Industry  
Engineering and Water Supply Department, S.A.  
Hunter District Water Board  
Melbourne and Metropolitan Board of Works  
Plastics Institute of Australia  
Water Board, Sydney  
Water Resources Commission, Qld

---

*Review of Australian Standards.* To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard®

---

**Polybutylene pipe systems**

**Part 2: Polybutylene (PB) pipe for  
hot and cold water applications**

---

First published as AS 2642.2—1984.  
Second edition 1989.

## PREFACE

This Standard was prepared by the Standards Australia Committee on Polybutylene Pipe Systems, acting under the authority of the Plastics Standards Board to supersede the 1984 edition. It is one of a series relating to polybutylene pipe systems; other Standards in the series are AS 2642.1, *Polybutylene (PB) pipe extrusion compounds*, and AS 2642.3, *Mechanical jointing fittings for use with polybutylene (PB) pipes for hot and cold water applications*.

Polybutylene pipe can be used with either plastics fittings or metallic fittings, provided that they are in accordance with AS 2642.3. Requirements set out therein cover compatibility with pipe, toxicity, resistance to leakage and pull-out, as well as thermal and pressure cycling tests.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia:

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

## CONTENTS

	<i>Page</i>
FOREWORD .....	4
1 SCOPE .....	5
2 REFERENCED DOCUMENTS .....	5
3 DEFINITIONS .....	5
4 HOOP STRESS .....	6
5 CLASSIFICATION AND DESIGNATION .....	6
6 WORKING PRESSURE ACCORDING TO TEMPERATURE RATING .....	6
7 COMPOSITION .....	6
8 GENERAL REQUIREMENTS .....	6
9 PERFORMANCE REQUIREMENTS .....	6
10 PACKAGING .....	10
11 MARKING .....	10
APPENDICES	
A DETERMINATION OF COMPLIANCE OF A LOT .....	11
B METHOD FOR DETERMINING THE DIMENSIONS OF PIPE .....	12
C LONG-TERM PRESSURE TEST .....	13
D ELONGATION TEST .....	17
E SHORT-TERM PRESSURE TEST .....	20
F LIGHT TRANSMISSION .....	22

## FOREWORD

The hydrostatic design stresses of the pipes specified in this Standard have been determined by the application of a safety factor of 1.8 to the extrapolated 100 000-hour long-term hydrostatic stress value, which is based on a minimum stress regression line.

The wall thicknesses for the pipes specified in this Standard are based on the Lamé formula<sup>1</sup>, which takes into account the hydrostatic design stress of the material and the working pressure and diameter of the pipes.

The equations used to calculate wall thickness are as follows:

$$T_{\min} = \frac{D_{m \max}}{2} \left[ 1 - \sqrt{\left( \frac{S/P - 1}{S/P + 1} \right)} \right]$$

$$T_{\max} = 1.10T_{\min} + 0.1$$

where

$T_{\min}$  = minimum wall thickness, in millimetres

$D_{m \max}$  = maximum mean outside diameter, in millimetres

$S$  = hydrostatic design stress of 7.6 MPa at 20°C.

$P$  = working pressure at 20°C, in megapascals

$T_{\max}$  = maximum wall thickness, in millimetres.

---

<sup>1</sup> Popov, E.P., *Mechanics of Materials*, Prentice Hall, Englewood-Cliffs New Jersey, 2nd Ed. 1976.

## STANDARDS AUSTRALIA

### Australian Standard Polybutylene pipe systems

#### Part 2: Polybutylene (PB) pipe for hot and cold water applications

**1 SCOPE.** This Standard specifies materials, dimensional and performance requirements for polybutylene pipe for hot and cold water applications including domestic, industrial and agricultural purposes.

In the interests of serviceability of the pipe, and irrespective of the calculated minimum wall thickness, this Standard does not apply to a wall thickness of less than 1.6 mm. The Standard applies to pipes of up to 125-mm nominal outside diameter with a wall thickness no greater than 15 mm.

##### NOTES:

1. Polybutylene undergoes a crystalline transition after it has cooled from the molten state. As a consequence pipe manufactured to this Standard will not have achieved its full strength until 10 d after the date of manufacture, i.e. the date stamped on the pipe. Precautions should be taken to ensure that pipe is not released from the manufacturer's control prematurely and installed before gaining full strength.
2. Polybutylene pipe manufactured in accordance with this Standard is considered suitable for use in situations exposed to sunlight, direct or indirect, only if it is stabilized against ultraviolet degradation. One effective method of stabilization is by the addition of between 2 percent and 3 percent carbon black.
3. Polybutylene pipe manufactured in accordance with this Standard is intended to be used with fittings complying with AS 2642.3. Joining polybutylene pipe by means of solvent cement is not satisfactory.
4. Advisory information on alternative methods of determining compliance of a 'lot' with this Standard is given in Appendix A.
5. Type tests specified in Clauses 8.1, 8.2, 8.3, 9.2, 9.3, and 9.4 are type tests performed to assess compliance of finished product with this Standard, however it may also be convenient for product manufacturers to use those tests for quality control purposes during manufacture.

**2 REFERENCED DOCUMENTS.** The following Standards are referred to in this Standard:

AS	
1199	Sampling procedures and tables for inspection by attributes
1349	Bourdon tube pressure and vacuum gauges
1399	Guide to AS 1199, Sampling procedures and tables for inspection by attributes
1821-23	Suppliers Quality Systems
1984	Vernier callipers
2000	Guide to AS 1821-23—Suppliers quality systems
2101	Internal micrometers (including stick micrometers)
2102	External micrometers
2490	Sampling procedures and charts for inspection by variables for percent defective

2642	Polybutylene pipe systems
2642.1	Part 1: Polybutylene (PB) pipe extrusion compounds
2642.3	Part 3: Mechanical jointing fittings for use with polybutylene (PB) pipes for hot and cold water applications
3900	Quality systems—Guide to selection and use
3901	Quality system for design/development, production, installation and servicing
3902	Quality systems for production and installation
3903	Quality systems for final inspection and test
3904	Quality systems—Guide to quality management and quality system elements
ASTM D 1708	Standard test method for tensile properties of plastics by use of microtensile specimens
BS 6920	Suitability of non-metallic products for use in contact with water intended for human consumption with regard to their effect on the quality of the water

**3 DEFINITIONS.** For the purpose of this Standard, the definitions below apply.

**3.1 Hoop stress**—the stress in a pipe or fitting under pressure acting tangentially to the perimeter of a transverse section.

**3.2 Long-term hydrostatic stress**—the continuously applied hoop stress which is estimated will cause failure at a specified temperature and time.

**3.3 Hydrostatic design stress**—the estimated hoop stress due to internal hydrostatic pressure that can be applied continuously at a specified temperature with a high degree of certainty that failure will not occur. It is obtained by the application of a safety factor to the extrapolated 100 000-hour long-term hydrostatic stress value.

**3.4 Working pressure**—the maximum pressure that can be sustained by the type and class of pipe or fitting for its estimated useful life under the anticipated working conditions.

**3.5 Test pressure**—the pressure applied internally to pipes or fittings when being tested for strength and watertightness.

**3.6 Reference curve**—the curve obtained by connecting the points 7.2 MPa at 0.1 h, 6.8 MPa at 170 h and 4.1 MPa at 100 000 h, for a failure stress-time graph plotted on log/log graph paper.

**3.7 Pipe material temperature**—the average temperature estimated as applying through the full wall thickness.