

Australian/New Zealand Standard™

**Methods of test for pulp and paper**

**Method 515: Measurement of diffuse radiance factor (diffuse reflectance factor)—Indoor daylight conditions (ISO brightness)**



## **AS/NZS 1301.515:2017**

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 5 February 2017 and by the New Zealand Standards Approval Board on 7 March 2017.  
This Standard was published on 1 May 2017.

---

The following are represented on Committee PK-019:

Appita  
Monash University  
New Zealand Paper Forum  
Scion

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at [www.saiglobal.com](http://www.saiglobal.com) or Standards New Zealand web site at [www.standards.govt.nz](http://www.standards.govt.nz) and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of Standards Australia or the New Zealand Standards Executive at the address shown on the back cover.

---

*This Standard was issued in draft form for comment as DR AS/NZS 1301.515:2016.*

---

# Australian/New Zealand Standard™

## Methods of test for pulp and paper

### Method 515: Measurement of diffuse radiance factor (diffuse reflectance factor)—Indoor daylight conditions (ISO brightness)

Originated as AS/NZS 1301.462s:2005.  
Revised and redesignated as AS/NZS 1301.515:2017.

#### **COPYRIGHT**

© Standards Australia Limited

© The Crown in right of New Zealand, administered by the New Zealand Standards Executive

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, PO Box 1473, Wellington 6140.

## PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper, to supersede AS/NZS 1301.462s:2005, *Methods of test for pulp and paper, Method 462s: Measurement of diffuse blue reflectance factor (ISO brightness) of pulp, paper and paperboard*.

The objective of this Standard is to specify a method for measuring the diffuse blue reflectance factor (ISO brightness) of pulps, papers and boards.

This Standard is identical with, and has been reproduced from ISO 2470-1:2016, *Paper, board and pulps—Measurement of diffuse blue reflectance factor—Part 1: Indoor daylight conditions (ISO brightness)*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) In the source text ‘this part of ISO 2470’ should read ‘this Australian/New Zealand Standard’.
- (b) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard</i>		<i>Australian/New Zealand Standard</i>	
ISO		AS/NZS 1301	Methods of test for pulp and paper
186	Paper and board—Sampling to determine average quality	1301.417	Method 417s: Sampling to determine average quality
2469	Paper, board and pulps—Measurement of diffuse radiance factor (diffuse reflectance factor)	1301.510	Method 510: Measurement of diffuse radiance factor (diffuse reflectance factor)
3688	Pulps—Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness)	1301.466s	Method 466s: Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness)
		AS/NZS ISO	
7213	Pulps—Sampling for testing	7213	Pulps—Sampling for testing

Only normative references that have been adopted as Australian or Australian/New Zealand Standards have been listed.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annex to which they apply. A ‘normative’ annex is an integral part of a Standard, whereas an ‘informative’ annex is only for information and guidance.

## CONTENTS

<b>1</b>	<b>Scope</b> .....	<b>1</b>
<b>2</b>	<b>Normative references</b> .....	<b>1</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>1</b>
<b>4</b>	<b>Principle</b> .....	<b>2</b>
<b>5</b>	<b>Apparatus</b> .....	<b>2</b>
	5.1 Reflectometer .....	2
	5.2 Reference standards for calibration of the instrument and the working standards .....	3
	5.3 Working standards .....	3
<b>6</b>	<b>Sampling and conditioning</b> .....	<b>3</b>
<b>7</b>	<b>Preparation of test pieces</b> .....	<b>3</b>
<b>8</b>	<b>Procedure</b> .....	<b>4</b>
<b>9</b>	<b>Expression of results</b> .....	<b>4</b>
<b>10</b>	<b>Test report</b> .....	<b>4</b>
	<b>Annex A (normative) Spectral characteristics of instruments for measuring ISO brightness</b> .....	<b>6</b>
	<b>Annex B (normative) UV calibration service</b> .....	<b>8</b>
	<b>Annex C (informative) Precision</b> .....	<b>10</b>
	<b>Bibliography</b> .....	<b>11</b>

## INTRODUCTION

The diffuse reflectance factor (radiance factor) depends on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This part of ISO 2470 is therefore intended to be read in conjunction with ISO 2469 which defines the geometric characteristics of the instrument and also defines the photometric calibration procedure to be adopted.

The definition of ISO brightness is historically linked to the Zeiss Elrepho instrument having, as a light source, an incandescent lamp which excites fluorescence to only a limited extent. It is specified here that, in instruments of the abridged spectrophotometer or filter colorimeter type, the UV content of the illumination be adjusted to conform to the CIE illuminant C as defined by a fluorescent reference standard having an assigned value of ISO brightness as described in [Annex B](#). Only if this is done can the property measured on a fluorescent material be called ISO brightness.

## AUSTRALIAN/NEW ZEALAND STANDARD

**Methods of test for pulp and paper**

## Method 515:

**Measurement of diffuse radiance factor (diffuse reflectance factor)—  
Indoor daylight conditions (ISO brightness)****1 Scope**

This part of ISO 2470 specifies a method for measuring the diffuse blue reflectance factor (ISO brightness) of pulps, papers and boards.

This part of ISO 2470 is limited in its scope to white and near-white pulps, papers and boards. The measurement can only be made in an instrument in which the ultraviolet energy level of the illumination has been adjusted to correspond to the CIE illuminant C<sup>[6]</sup> using a fluorescent reference standard. The CIE illuminant C is taken to be representative of indoor daylight conditions because it contains a suitable proportion of UV radiation.<sup>[9]</sup>

**NOTE** The property called D65 brightness is measured with an instrument adjusted to correspond with CIE standard illuminant D65,<sup>[4]</sup> which has a much higher UV content than that specified in this part of ISO 2470. The measurement of D65 brightness is described in ISO 2470-2.<sup>[2]</sup>

**2 Normative references**

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ISO 3688, *Pulps — Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness)*

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories*

ISO 7213, *Pulps — Sampling for testing*

**3 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

**3.1****diffuse radiance factor** $\beta$ 

ratio of the diffusely reflected radiance of a body in a given direction to that of the perfect reflecting diffuser under specified conditions of irradiation

Note 1 to entry: For fluorescent (luminescent) materials, the specified conditions of irradiation in this part of ISO 2470 are CIE illuminant C and the diffuse radiance factor is strictly the total radiance factor,  $\beta$ , which is the sum of two components, the reflected radiance factor,  $\beta_R$ , and the luminescent radiance factor,  $\beta_L$ , so that:

$$\beta = \beta_R + \beta_L$$