

Australian Standard®

**Pressure-sensitive adhesive tape—
Glossary of terms**

This Australian Standard was prepared by Committee PK/10, Pressure Sensitive Adhesive Tapes. It was approved on behalf of the Council of Standards Australia on 4 August 1993 and published on 20 December 1993.

The following interests are represented on Committee PK/10:

Australian Chamber of Commerce and Industry
Australian Institute of Packaging
Commercial Services Group, N.S.W.
Packaging Council of Australia

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 88140.

AS 1230—1993

Australian Standard®

**Pressure-sensitive adhesive tape—
Glossary of terms**

First published as AS Z16—1961.
Revised and redesignated AS 1230—1978.
Second edition 1993.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 8481 5

PREFACE

This Standard was prepared by the Standards Australia Committee on Pressure Sensitive Adhesive Tapes to supersede AS 1230—1978, *Glossary of terms for pressure sensitive adhesive tapes*. The Standard is one of a series dealing with pressure-sensitive adhesive tapes, the others in the series being as follows:

AS

1599 Pressure sensitive adhesive packaging tapes

1602 Pressure sensitive adhesive filmic tapes for general office applications

1635 Methods of testing pressure sensitive adhesive tape

This Standard is intended to complement the other Standards in the series, by defining terms peculiar to, and commonly used in relation to, the construction and use of pressure-sensitive adhesive tapes.

This Standard should be used in conjunction with AS 2400.1, *Packaging*, Part 1: *Glossary of packaging terms*.

In the preparation of this Standard, reference was made to the glossary of terms appearing in *Metric Test Methods for Pressure-sensitive Tapes*, 8th edition, 1986, issued by the Pressure-sensitive Tape Council, 1800 Pickwick Ave, Glenview, Illinois 60025, U.S.A.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard
Pressure-sensitive adhesive tape—
Glossary of terms

| Term | Definition |
|---|--|
| abrasion resistance | The ability of a tape to withstand rubbing and still function satisfactorily. |
| acetate cellulose acetate | A transparent film which is used to provide non-yellowing and easy tear characteristics, for various reasons, in tape backings. |
| acrylic | A synthetic polymer with excellent ageing characteristics that can be used as either a single component adhesive, or a coating or saturant, depending upon composition. |
| adhesion | <i>See</i> AS 2400.1 |
| adhesion build-up | An increase in the peel adhesion value of a pressure-sensitive tape after it has been allowed to dwell on the applied surface. |
| adhesion to backing | <i>See</i> AS 2400.1 |
| adhesive (pressure-sensitive) | <i>See</i> AS 2400.1 |
| adhesive residue | Adhesive that is pulled away from the tape and remains on the surface to which the tape was applied. |
| adhesive transfer offsetting pick-off | <i>See</i> AS 2400.1 |
| adhesive transfer tape | Pressure-sensitive adhesive tape with no backing or carrier coated onto a suitable liner. |
| ageing | <i>See</i> AS 2400.1 |
| artificial accelerated | The change in characteristics of a tape, either in strip or roll form, which occurs under artificial conditions which simulate the principal effects of extended natural ageing. |
| backcoat | Coating applied to the outside surface of the tape to enable it to be written on by pen, pencil, marking pen, or other writing tools. |
| backing | <i>See</i> AS 2400.1 |
| backsize | <i>See</i> AS 2400.1 |