

AS 3672

AS 3672—1989

Withdrawn TAS Oct. 1999

Australian Standard®

Wrought steel threaded pipe fittings

E

This Australian Standard was prepared by Committee WS/4, Steel Pipes and Fittings—Water and Gas. It was approved on behalf of the Council of Standards Australia on 8 February 1989 and published on 14 April 1989.

The following interests are represented on Committee WS/4:

Australian Gas Association
Confederation of Australian Industry
Metal Trades Industry Association of Australia
Public Works Department, New South Wales
Water Resources Commission, Queensland

Additional interests participating in preparation of this Standard:

Water Authority of Western Australia

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

Australian Standard®

Wrought steel threaded pipe fittings

First published as AS 3672—1989.

PREFACE

This Standard was prepared by Standards Australia's Committee on Steel Pipes and Fittings—Water and Gas in response to a request from Standards Australia's Committee on the National Plumbing and Drainage Code.

In the preparation of this Standard, reference was made to BS 1740.1:1971, *Specification for wrought steel pipe fittings (screwed BS 21R series thread)*, and the assistance gained from this source is acknowledged.

This Standard does not indicate the services for which the threaded pipe fittings are appropriate. Where the use of threaded pipe fittings is not controlled by by-laws or regulations, reference should be made to the appropriate code of practice or application Standard. If the application is for pressure purposes, reference should be made to AS CB18, *SAA Pressure Piping Code—Part 1: Ferrous piping*.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 DEFINITIONS	3
4 MATERIALS	3
5 THREADED ENDS OF FITTINGS	3
6 METHOD OF SPECIFYING OUTLETS	3
7 PRESSURE/TEMPERATURE RATINGS	3
8 DIMENSIONS AND TOLERANCES	4
9 LEAK TIGHTNESS	4
10 GALVANIZING	5
11 MARKING	5
APPENDICES	
A INFORMATION TO BE SUPPLIED WITH ORDER	18

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Wrought steel threaded pipe fittings

1 SCOPE. This Standard specifies requirements for welded, forged and machined wrought steel threaded pipe fittings of DN 6 to DN 150 inclusive (nominal size), threaded in accordance with AS 1722.1, for use with steel tubes and tubulars as specified in AS 1074.

NOTE: Guidelines on requirements that should be specified by the purchaser or agreed upon at the time of enquiry or order are given in Appendix A.

2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard.

AS

1074 Steel tubes and tubulars for ordinary service

1650 Galvanized coatings

1722 Pipe threads of Whitworth form

1722.1 Part 1: Sealing pipe threads

1722.2 Part 2: Fastening pipe threads

BS

3894 Methods for converting elongation values for steel

Part 1: Carbon and low alloy steels

3 DEFINITIONS. For the purpose of this Standard, the definitions below apply.

3.1 Fitting—a connecting piece, of one or more parts.

3.2 Nominal size (DN)—a numerical designation of size that is common to all components in a piping system other than components designated by outside diameters or by thread size. It is a convenient round number for reference purposes and is only loosely related to manufacturing dimensions.

NOTE: Nominal size is designated by the letters DN followed by a number, e.g. DN 32.

3.3 Fastening thread—a thread for fittings (or parts of a fitting) requiring simple mechanical assembly.

NOTE: Fastening pipe thread is specified in AS 1722.2 and its use in this Standard is covered by G series threads.

3.4 Sealing pipe thread—a thread for fittings requiring pressure tightness through the mating of the threads, with or without the use of thread sealants, at the same time providing mechanical assembly.

NOTE: Sealing pipe thread is specified in AS 1722.1 and its use in this Standard is covered by RP, R and RC series threads.

3.5 Chamfer—machined or cast surface in the form of a cone at the entrance of a thread to assist assembly and prevent damage to the start of the thread.

3.6 Reinforcement—additional material on the outside diameter of an internally threaded fitting in the form of a band or bead.

3.7 Rib—local and axially aligned additional material on the outside or inside of a fitting for assistance in manufacturing or assembly.

3.8 Run—the principal axially aligned outlet of a fitting having two outlets or more.

3.9 Branch—side outlet(s) of a tee, pitcher tee or cross.

3.10 Centre to face dimension—the distance between the central axis and the face of an outlet of an angularly disposed outlet.

4 MATERIALS. The steel from which the fittings are made shall show on test a tensile strength of from 330 MPa to 470 MPa and a percentage elongation on a gauge length of $5.65 \sqrt{S_0}$ of not less than 20 percent where S_0 is the original cross-sectional area of the test piece.

NOTE: Where other gauge lengths are used the corresponding elongation on $5.65 \sqrt{S_0}$ can be obtained as shown in BS 3894: Part 1.

Where fittings are welded during manufacture, the steel shall show on analysis not more than 0.06 percent of sulfur and not more than 0.06 percent of phosphorus.

5 THREADED ENDS OF FITTINGS.

5.1 General dimensions. All dimensions for the threaded ends of fittings shall be in accordance with Figure 1.

5.2 Internal and external threads. Except where noted, internal threads on the ends of fittings shall be parallel (series RP) and external threads shall be taper (series R) and both threads shall comply with the appropriate requirements of AS 1722.1.

NOTE: For pressure duty, fittings complying with the requirements of this Standard are not suitable for use with G series threads as specified in AS 1722.2 since no mechanical face exists upon which a sealing device may act.

5.3 Alignment. The axes of screw threads shall be coincident with the true axes of the fittings within 1 in 200 on the run and 1 in 125 on the branch.

6 METHOD OF SPECIFYING OUTLETS.

6.1 Equal fittings. Where all outlets are of the same nominal size, they shall be specified by that one nominal size irrespective of the number of outlets.

6.2 Unequal fittings. When outlets are of differing nominal sizes they shall be specified as follows:

- Fittings having two outlets, the larger outlet shall be specified first.
- Tees having two nominal sizes, the first shall apply to both ends of the run, the second to the branch.

7 PRESSURE/TEMPERATURE RATINGS. All threaded pipe fittings shall be suitable for operation at the maximum permissible working pressures within the temperature ranges as given in Table 1. Intermediate pressure ratings at temperatures between 120°C and 300°C shall be obtained by linear interpolation.