

Australian Standard[®]

**Carbon steel and carbon-manganese
steels—Forgings (ruling section 300 mm
maximum)**



This Australian Standard® was prepared by Committee MT-001, Iron and Steel. It was approved on behalf of the Council of Standards Australia on 24 April 2007. This Standard was published on 22 May 2007.

The following are represented on Committee MT-001:

- Australasian Railway Association
 - Australian Building Codes Board
 - Australian Foundry Institute
 - Australian Industry Group
 - Australian Steel Institute
 - Bureau of Steel Manufacturers Australia
 - Institute of Materials Engineering Research Australia
 - New Zealand Heavy Engineering Research Association
-

This Standard was issued in draft form for comment as DR 06608.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting **www.standards.org.au**

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at **mail@standards.org.au**, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

**Carbon steel and carbon-manganese
steels—Forgings (ruling section 300 mm
maximum)**

Originated as AS G30—1970.
Previous edition AS 1448—1981.
Third edition 2007.
Reissued incorporating Amendment No. 1 (January 2008).

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 8247 7

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-001, Iron and Steel, to supersede AS 1448—1981, *Carbon steel and carbon-manganese steels—Forgings (ruling section 300 mm maximum)*.

This Standard incorporates Amendment No. 1 (January 2008). The changes required by the Amendment are indicated in the text by a marginal bar and amendment number against the clause, note, table, figure or part thereof affected.

After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian, rather than an Australian/New Zealand Standard.

The objective of this Standard is to specify the general technical delivery requirements for carbon steels and carbon-manganese steel forgings for general engineering purposes with ruling sections up to and including 300 mm.

The objective of this revision is to update the referenced documents and to apply current style.

In the selection of steel, one of the most important considerations is whether the mechanical properties required can be obtained from the steel in the size and shape at the time of heat treatment. That portion which is most important from the point of view of the mechanical properties obtained by heat treatment is referred to as the 'ruling section', and the ruling section should always be expressed in terms of the diameter of an equivalent round bar (see BS 5046, *Method for the estimation of equivalent diameters in the heat treatment of steels*). The specifications in Table 5 state that the maximum diameter of round bar, i.e. the limiting ruling section, in which the mechanical properties specified may be obtained. The designer should select steel which will give the desired properties in the actual ruling section at the time of heat treatment. It should be noted that forgings larger than 150 mm ruling section should not, except in special circumstances, be supplied in the as-forged condition.

The term 'informative' has been used in this Standard to define the application of the appendix to which it applies. An 'informative' appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS.....	4
3 DESIGNATION.....	5
4 STEELMAKING PROCESS	6
5 CONDITION OF FORGINGS ON DELIVERY	6
6 CHEMICAL COMPOSITION	6
7 FREEDOM FROM DEFECTS.....	7
8 AUSTENITE GRAIN SIZE	7
9 MANUFACTURING TOLERANCES.....	8
10 MECHANICAL PROPERTIES	8
11 PROVISION OF TEST SAMPLES FOR MECHANICAL TESTING	8
12 PREPARATION OF TEST PIECES	9
13 MECHANICAL TESTS.....	9
14 RETESTS	9
15 IDENTIFICATION.....	9
16 ROUNDING OF RESULTS OBTAINED BY INSPECTION AND TESTING	9
 APPENDICES	
A PURCHASING GUIDELINES.....	13
B MEANS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD	15

STANDARDS AUSTRALIA

Australian Standard**Carbon steel and carbon-manganese steels—Forgings (ruling section 300 mm maximum)****1 SCOPE**

This Standard specifies requirements for carbon steel and carbon-manganese steel forgings for general engineering purposes with ruling section up to and including 300 mm. The Standard provides for the supply of forgings on the following basis:

- (a) Chemical composition only, as specified in Tables 1 to 4.
- (b) Chemical composition as specified in Tables 1 to 4, and hardness or other mechanical properties in any heat-treated condition, as negotiated at the time of enquiry and/or order.
- (c) Chemical composition and mechanical properties in the normalized or normalized and tempered condition as specified in Table 5.

NOTES:

- 1 For guidance on purchasing requirements refer to Appendix A.
- 2 To demonstrate a means of compliance to the Standard refer to Appendix B.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

1065	Non-destructive testing—Ultrasonic testing of carbon and low alloy steel forgings
1171	Non-destructive testing—Magnetic particle testing of ferromagnetic products, components and structures
1199	Sampling procedures for inspection by attributes
1199.0	Part 0: Introduction to the ISO 2859 attribute sampling systems
1199.1	Part 1: Sampling schemes indexed by acceptance quality limits (AQL) for lot-by-lot inspection
1391	Metallic materials—Tensile testing at ambient temperature
1544	Methods for impact tests on metals
1544.2	Part 1: Charpy V-notch
1733	Methods for the determination of grain size in metals
1816	Metallic materials—Brinell hardness test
1816.1	Part 1: Test method (ISO 6506-1:2005, MOD)
1817	Metallic materials—Vickers hardness test
1817.1	Part 1: Test methods (ISO 6507-1:1997, MOD)
2062	Non-destructive testing—Penetrant testing of products and components
2706	Numerical values—Rounding and interpretation of limiting values
5016	Metallic materials—Conversion of hardness values