

SUPERSEDED BY:

AS 3719.2-1998

AS 3719.2—1990

Under Revision see DR97180CF

(Technically equivalent to ISO 797-1973)

Australian Standard®

Aluminium and aluminium alloys

**Part 2: Determination of silicon—
Gravimetric method**

CC



STANDARDS AUSTRALIA



This Australian Standard was prepared by Committee CH/10, Analysis of Metals. It was approved on behalf of the Council of Standards Australia on 2 January 1990 and published on 11 June 1990.

The following interests are represented on Committee CH/10:

Aluminium Development Council
Australian Lead Development Association
Bureau of Steel Manufacturers of Australia
Copper Technical Data Centre
National Association of Testing Authorities
Railways of Australia Committee
Royal Australia Chemical Institute

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 89063. ✓

AS 3719.2—1990

Australian Standard®

Aluminium and aluminium alloys

**Part 2: Determination of silicon—
Gravimetric method**

First published as AS 3719.2—1990.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY NSW
ISBN 0 7262 6123 8

PREFACE

This Standard was prepared by the Standards Australia Committee on the Analysis of Metals under the direction of the Chemical Standards Board. This Standard is technically equivalent to ISO 797—1973, *Aluminium and aluminium alloys—Determination of silicon—Gravimetric method*. It is Part 2 of a series of Standards for the chemical analysis of aluminium and aluminium alloys.

The Committee organized an inter-laboratory test program to obtain information on the repeatability and reproducibility of the method. The following laboratories participated in the test program to provide the data given in Table 2:

Tomago Aluminium Co Pty Ltd
Boyne Smelters Pty Ltd
Comalco Aluminium (Bell Bay) Limited
Alcoa of Australia Ltd
Pasminco Metals/BHAS Pty Ltd
Sims Metal Ltd
Department of Defence, Materials Research Laboratories

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 PRINCIPLE	4
4 REAGENTS	4
5 APPARATUS	4
6 SAMPLING	4
7 PROCEDURE	5
8 CALCULATION	6
9 PRECISION	6
10 ACCEPTANCE OF ANALYTICAL VALUES	7
11 TEST REPORT	7
APPENDICES	
A SPECIAL MODIFICATION FOR ALUMINIUM-SILICON ALLOYS (SILICON CONTENT GREATER THAN 3%) AND ALUMINIUM-MAGNESIUM ALLOYS	8
B SPECIAL MODIFICATION FOR ALUMINIUM ALLOYS CONTAINING TIN OR ANTIMONY	9

STANDARDS AUSTRALIA**Australian Standard
Aluminium and aluminium alloys****Part 2—Determination of silicon—Gravimetric method**

1 SCOPE. This Standard sets out a gravimetric method for the determination of silicon in aluminium and aluminium alloys. This method is applicable to the determination of silicon in aluminium and aluminium alloys in the range 0.30% to 8%. The method does not apply completely to the following special cases, for which it is modified as described in Appendix A or Appendix B:

- (a) Aluminium-silicon alloys (silicon content greater than 3%) and aluminium-magnesium alloys (see Appendix A).
- (b) Aluminium alloys containing tin or antimony (see Appendix B).

2 REFERENCED DOCUMENTS.**AS**

- 2612 Aluminium and aluminium alloys—Sampling and preparation of solid samples for optical emission spectrometry
- 2850 Chemical analysis—Interlaboratory test programs—For determining precision of analytical method(s)—Guide to the planning and conduct

3 PRINCIPLE. After pretreatment with sodium hydroxide, the sample is acidified with perchloric acid and the silica dehydrated, filtered, dried, calcined and weighed. The silica is then volatilized using hydrofluoric acid, and the silicon determined by the difference in mass between the residue and the calcined silica.

4 REAGENTS.

4.1 General requirements. Except where otherwise specified, only reagents of recognized analytical grade and distilled water or water of an equivalent purity shall be used.

4.2 Solids.**4.2.1 Sodium hydroxide pellets.****4.3 Solutions.****4.3.1 Hydrobromic acid (ρ_{20} 1.49 g/mL).**

4.3.2 Hydrochloric acid (50 mL/L). Dilute 5 mL of hydrochloric acid (ρ_{20} 1.16 g/mL) to 100 mL with water.

4.3.3 Hydrofluoric acid (ρ_{20} 1.15 g/mL).**4.3.4 Nitric acid (ρ_{20} 1.42 g/mL).****4.3.5 Perchloric acid (ρ_{20} 1.54 g/mL).**

NOTE: Perchloric acid (ρ_{20} 1.67 g/mL) may also be used. 100 mL of perchloric acid (ρ_{20} 1.54 g/mL) is equivalent to 79 mL of perchloric acid (ρ_{20} 1.67 g/mL).

4.3.6 Perchloric acid (350 mL/L). Dilute 35 mL of perchloric acid (4.3.5) to 100 mL with water.

4.3.7 Sulfuric acid (500 mL/L). Add 50 mL of sulfuric acid (ρ_{20} 1.84 g/mL) to water, cool and dilute to 100 mL.

4.3.8 Bromine water, saturated solution.

4.3.9 Hydrogen peroxide, 6% (V/V). Dilute 17 mL of hydrogen peroxide (36% V/V) to 100 mL with water.

4.3.10 Sodium hydroxide solution (50 g/L). Dissolve 50 g of sodium hydroxide pellets (4.2.1) in water, cool and dilute to 1 L with water. Store in a plastics container.

5 APPARATUS. Ordinary laboratory apparatus is required. The sample dissolution shall be carried out in a basin or beaker inert to sodium hydroxide, e.g. nickel, silver, PTFE, stainless steel, and of approximately 250 mL capacity and having a diameter of between 120 mm and 150 mm.

6 SAMPLING. Samples for analysis shall be obtained from ingots in accordance with the procedure specified in AS 2612.