

~~LOAN COPY~~
INFORMATION CENTRE
STANDARDS AUSTRALIA

Dup.

SUPERSEDED BY:

AS 2780-1999

AS 2780—1985
UDC 666.76(038)

Australian Standard®

2780—1985

under Revision see DR 98192.

**REFRACTORIES AND
REFRACTORY MATERIALS—
GLOSSARY OF TERMS**



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter



This Australian standard was prepared by Committee MN/7, Refractories and Refractory Materials. It was approved on behalf of the Council of the Standards Association of Australia on 17 December 1984 and published on 7 June 1985.

(received in library 10 Sept 1985 - published later)

The following interests are represented on Committee MN/7:

Australian Institute of Mining and Metallurgy
Bureau of Steel Manufacturers of Australia
Cement and Concrete Association of Australia
Commonwealth Scientific and Industrial Research Organization
Electricity Supply Association of Australia
Australian Foundry Institute (N.S.W. Branch)
Institute of British Foundrymen (Australian Branch)
Refractories Manufacturers' Association of Australia
University of New South Wales

Representatives of the following interests also participated in the drafting of this standard:

ACI Technical Centre Pty Ltd
Chemical Laboratories of Dept. of Mineral Resources

Review of Australian Standards. To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all SAA publications will be found in the Catalogue of SAA Publications; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 81294 to 81296, DR 82070 to 82072, DR 83087 to 83091 and DR 83179.

AUSTRALIAN STANDARD

REFRACTORIES AND REFRACTORY MATERIALS— GLOSSARY OF TERMS

AS 2780—1985

First published (as AS R27).....	1970
First published (as AS 2780).....	1985

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.

ISBN 0 7262 3670 5



17 SEP 1985

PREFACE

This standard was prepared by the Association's Committee on Refractories at the request of the refractories industry. It supersedes AS R27—1970, Glossary of Terms Used in the Refractory Industry.

Since the release of the earlier standard the Australian industries manufacturing and using refractories have undergone a great increase in specialization concurrent with changes in technical specifications and requirements for quality control of these products. Thus this standard gives greater detail in the specialized areas of common refractory application such as iron and steel-making, non-ferrous metallurgy, raw materials processing and glass-making. It is felt that for industries not cited the bulk of terms used within those industries is adequately covered by this standard.

The definitions given in this standard are of a general nature and should not be interpreted as fully technical definitions. Where a more complete technical definition is sought, reference may need to be made to other Australian standards such as the AS 1774 series of tests or standards relating to relevant specifications or sampling procedures. However the definitions in this standard are not in conflict with the technical definitions contained within and specific to those other standards.

The source documents for this standard include ISO Recommendation R836, Vocabulary for the Refractories Industry (1968), BS 3446:1962, Glossary of Terms Relating to the Manufacture and Use of Refractory Materials and many industrial reference documents supplied by the industries, councils and associations of the ferrous, non-ferrous and refractories manufacturers and users within Australia.

This standard differs from AS R27 in the broadening of scope, the sectionalizing of contents into specialist areas and in providing a comprehensive and easy-to-use index, not to mention the inclusion of numerous outline diagrams to aid in the clarification of the terms and definitions. The committee believes that in this form it will be a valuable reference to both student and expert alike.

The following standards are referred to in this standard:

- AS 1228 Water-tube Boilers
- AS 1617 Fireclay Refractory Bricks
- AS 1774 Methods for Physical Testing of Refractories and Refractory Materials
 - 1774.1 The Determination of Cold Compressive Strength
 - 1774.3 The Determination of Cold Modulus of Rupture
 - 1774.5 The Determination of Density, Porosity and Water Absorption
 - 1774.6 The Determination of True Density
 - 1774.9 The Determination of Resistance to the Disintegrating Effects of Carbon Monoxide
 - 1774.10 The Determination of Pyrometric Cone Equivalent (Refractoriness)
 - 1774.12 Refractoriness Under Load
 - 1774.13 The Determination of Permanent Dimensional Change After Heating
 - 1774.19 The Determination of Sieve Analysis and Water Content
 - 1774.21 Workability Index of Mouldable Refractories
 - 1774.23* Abradability Index
 - 1774.25 The Determination of Powder Density (Using Rees-Hugill Flask)
 - 1774.27 Modulus of Rupture at Elevated Temperature
 - 1774.28* Preparation of Castables and Mouldables
- AS 1797 Fire-tube, Shell and Miscellaneous Boilers
- AS 2497 Sampling Procedures for Acceptance Testing of Shaped Refractory Products

* In course of preparation.

CONTENTS

	<i>Page</i>
SECTION 1. GENERAL TERMS	4
SECTION 2. RAW MATERIALS AND MINERALS	8
SECTION 3. TYPES OF REFRACTORY MATERIALS	14
SECTION 4. MANUFACTURE	
4.1 Preparation and Shaping	18
4.2 Drying and Firing	21
4.3 Kilns and Kiln Furniture	22
SECTION 5. BRICK SHAPES AND FURNACE DESIGN	
5.1 Brick Shapes	25
5.2 Furnace Design	28
SECTION 6. FERROUS METALLURGY	
6.1 Blast-furnace	30
6.2 Hot-blast Stoves	33
6.3 Mixers and Hot-metal Ladles	35
6.4 Open-hearth Furnace	37
6.5 Converters	39
6.6 Electric Steel Furnace	41
6.7 Steel Casting	43
6.8 Heat-treatment and Reheating Furnaces	47
6.9 Foundry and Smelting of Ores	48
SECTION 7. NON-FERROUS METALLURGY	
7.1 General Terms	51
7.2 Aluminium Industry	52
7.3 Copper/Nickel Industry	53
7.4 Lead Industry	55
7.5 Tin Industry	56
7.6 Zinc Industry	57
SECTION 8. RAW MATERIALS PROCESSING—ROTARY AND SHAFT KILNS (CEMENT, LIME, MAGNESITE, DOLOMITE AND ALUMINA INDUSTRIES)	58
SECTION 9. GLASS INDUSTRY	61
SECTION 10. COKE OVENS	69
SECTION 11. BOILERS	72
SECTION 12. PROPERTIES AND METHODS OF TESTS	73
INDEX	77

STANDARDS ASSOCIATION OF AUSTRALIA

AUSTRALIAN STANDARD

for

REFRACTORIES AND REFRACTORY MATERIALS—GLOSSARY OF TERMS

SECTION 1. GENERAL TERMS

Term	Definition
abrasion	The wearing of a surface by mechanical action between solids (cf. <i>corrosion, erosion, abrasability index, abrasion resistance</i>).
aggregate	A refractory material consisting of particles of various sizes. It is one of the components used in the manufacture of formed or monolithic bodies.
amorphous	Having no crystalline structure.
anisotropic	Refers to crystalline materials for which the physical properties depend upon the direction of the crystal axes.
annealing	The release of internal stress by controlled heating and cooling.
argillaceous	Refers to fine-grade sedimentary materials of the clay type.
arris	The sharp edge formed by the angular contact of two plane or curved surfaces.
bat (batt)	(a) A fired slab of refractory material, generally of thin section, used to support ware in the firing of ceramic products. (b) Reject or broken brick, sometimes used as <i>grog</i> .
batch	(a) The whole of the various constituents making up the mixture for one operation (cf. <i>batch composition</i>). (b) A quantity of material for sampling purposes (refer to AS 2497).
batch composition	The blend of raw materials proportioned in accordance with the basic formula of the product (cf. <i>batch</i>).
binder	(a) A substance added to a granular material to give it green and/or dry strength. (b) A term sometimes used synonymously with the term ' <i>bond</i> ' (see also <i>binder brick</i>).
blending	Mixing together of different-sized grains or materials to obtain a desired texture or composition (cf. <i>grading</i>).
bloating	A permanent expansion resulting from the formation of a gaseous phase (which in turn creates a vesicular texture) that occurs when some types of clay are fired (cf. <i>exfoliation, intumescence</i>).
body	A blend of mixed and moistened raw materials, ready for making into refractory products (cf. <i>mix</i>).
bond	(a) A material that binds together the discrete grains of a mix, sometimes used synonymously with the term ' <i>binder</i> '. (b) The link or force responsible for adhesion between the atoms and/or molecules making up a substance. The nature of the bond possessed by the substance determines its physical properties (cf. <i>ceramic bond, chemical bond</i>).
burning	(a) Heat treatment of calcined raw materials at elevated temperatures. (b) An alternative term for firing (cf. <i>calcination, firing, sintering</i>).
calcination (calcining)	Heat treatment producing physical and/or chemical changes in refractory raw materials, particularly decomposition to hydroxides and carbonates (cf. <i>burning, dead-burned, firing, sintering</i>).
calcine	The product of calcination.
ceramic	A term applicable to products made thermochemically from heat-resistant, non-metallic, inorganic materials (cf. <i>ceramic bond</i>).