

Australian Standard™

**Non-destructive testing—Eddy current  
testing for the detection of surface  
flaws—Ferromagnetic and non-  
ferromagnetic metallic products**



This Australian Standard was prepared by Committee MT-007, Non-destructive Testing of Metals and Materials. It was approved on behalf of the Council of Standards Australia on 24 November 2005.

This Standard was published on 20 December 2005.

---

The following are represented on Committee MT-007:

Australian Railway Association  
Australian Aerospace Non-Destructive Testing Committee  
Australian Industry Group  
Australian Institute for Non-Destructive Testing  
Australian Nuclear Science & Technology Organisation  
Australian Pipeline Industry Association  
Bureau of Steel Manufacturers of Australia  
Engineers Australia  
Industrial Research Limited  
National Association of Testing Authorities Australia  
New Zealand Non-Destructive Testing Association  
TestSafe Australia  
Victorian WorkCover Authority  
Welding Technology Institute of Australia

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.org.au](mailto:mail@standards.org.au), or write to the Chief Executive, Standards Australia, GPO Box 476, Sydney, NSW 2001.

---

*This Standard was issued in draft form for comment as DR 05352.*

Australian Standard™

**Non-destructive testing—Eddy current testing for the detection of surface flaws—Ferromagnetic and non-ferromagnetic metallic products**

Originated as AS 4544.1—1999.  
Revised and redesignated as AS 4544—2005.

**COPYRIGHT**

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 7065 7

## PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standard New Zealand Committee MT-007, Non-destructive Testing of Metals and Materials, to supersede AS 4544.1—1991, *Non-destructive testing—Eddy current testing for the detection of surface flaws*, Part 1: *In non-ferromagnetic metallic products*.

After consultation with shareholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this revision is to include ferrous materials in the method for detecting surface flaws in both non-ferrous and ferrous metals and alloys.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 REFERENCED DOCUMENTS .....	5
3 DEFINITIONS.....	5
4 SAFETY .....	6
5 QUALIFICATION OF NON-DESTRUCTIVE TEST PERSONNEL.....	7
6 FACILITIES CONTROL.....	7
7 PROCEDURE.....	8
8 WRITTEN PROCEDURE REQUIREMENTS .....	11
9 REPORT .....	12
APPENDICES	
A PURCHASING GUIDELINES.....	13
B CALIBRATION STANDARDS .....	14

## FOREWORD

Eddy current inspection is based on the principles of electromagnetic induction and is used to identify or differentiate between a wide variety of physical, structural and metallurgical conditions in electrically conductive ferromagnetic and non-ferromagnetic metals and metal parts. Eddy current inspection can be used for the following purposes:

- (a) To measure or identify such conditions and properties as electrical conductivity, magnetic permeability, heat treatment condition, hardness and physical dimensions.
- (b) To detect seams, laps, cracks, voids and inclusions.
- (c) To sort dissimilar metals and detect differences in their composition, microstructure and other properties.
- (d) To measure the thickness of a non-conductive coating on a conductive metal or the thickness of a non-magnetic metal coating on a magnetic metal.

Because eddy current inspection employs electromagnetic induction, it does not require direct electrical contact with the part being inspected. The method is based on indirect measurement; thus, it is necessary to establish a correlation between the instrument readings and the structural characteristics and serviceability of the parts being inspected.

The inspection coil is an essential part of every eddy current inspection system. Its shape depends to a considerable extent on the purpose of the inspection and on the shape of the part being inspected.

This Standard gives requirements for the inspection of ferromagnetic and non-ferromagnetic materials for surface defects. The eddy current inspection method is most suitable for inspections where the nature of the defect is known so that the inspection system can be optimized for the detection of this defect. The limitation of the eddy current method is that it is not well suited to broad area scanning where various types of defects are sought.

## STANDARDS AUSTRALIA

### Australian Standard

# Non-destructive testing—Eddy current testing for the detection of surface flaws—Ferromagnetic and non-ferromagnetic metallic products

## 1 SCOPE

This Standard specifies requirements for eddy current flaw detection of metals and alloys and includes requirements for the preparation of test procedures, calibration standards and calibration procedures. It covers the inspection of flat and curved surfaces, and bolt holes.

This Standard does not include criteria for acceptance or rejection.

NOTE: Advice and recommendations on information to be supplied by the purchaser at the time of enquiry or order are contained in the purchasing guidelines set out in Appendix A.

## 2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

- |      |  |
|------|--|
| 1171 | Non-destructive testing—Magnetic particle testing of ferromagnetic products, components and structures |
| 1470 | Health and safety at work—Principles and practices   |
| 1929 | Non-destructive testing—Glossary of terms  |
| 2062 | Non-destructive testing—Penetrant testing of products and components                                   |
| 3669 | Non-destructive testing—Qualification and registration of personnel—Aerospace                          |
| 3998 | Non-destructive testing—Qualification and certification of personnel                                   |

## 3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS 1929 and those below apply.

### 3.1 Absolute probe

A probe containing a coil that responds to all electromagnetic properties of the test part.

### 3.2 Array probe

A probe of multiple coils which allows a larger area to be covered in a single pass than is possible with absolute or differential probes.

### 3.3 Coil

One or more turns of a conductor wound to produce a magnetic field when current passes through the conductor.

### 3.4 Coil impedance

The total opposition to current flow through a coil and which is represented by the ratio of the coil voltage to the coil current. This impedance is affected by the material within the magnetic field generated by the coil and is sometimes used to measure eddy current response.