

Australian Standard™

Alumina

**Part 1: Determination of loss of mass at
300°C and 1000°C**

This Australian Standard was prepared by Committee MN/9, Alumina and Materials Used in Aluminium Production. It was approved on behalf of the Council of Standards Australia on 29 February 2000 and published on 26 April 2000.

The following interests are represented on Committee MN/9:

Australasian Institute of Mining and Metallurgy
Australian Aluminium Council
CSIRO Minerals
Minerals Council of Australia
The Royal Australian Chemical Institute

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for the improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, PO Box 1055, Strathfield, NSW 2135.

Australian Standard™

Alumina

Part 1: Determination of loss of mass at 300°C and 1000°C

Originated as AS 2879—1986.
Revised and redesignated as AS 2879.1—2000.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
PO Box 1055, Strathfield, NSW 2135, Australia

ISBN 0 7337 3325 5

PREFACE

This Standard was prepared by the Standards Australia Committee MN/9, Alumina and Materials used in Aluminium Production, as a revision of AS 2879—1986, *Alumina—Determination of loss of mass at 300°C and 1000°C*.

The objective of this revision is to incorporate sample preparation procedures, improve the description of the method and to provide a method for determination of loss of mass by automatic procedures.

The term ‘normative’ has been used in this Standard to define the application of the Appendix to which it applies. A ‘normative’ appendix forms an integral part of the Standard.

CONTENTS

	<i>Page</i>
1 SCOPE.....	3
2 REFERENCED DOCUMENTS.....	3
3 PRINCIPLE.....	3
4 SAFETY.....	3
5 DESICCANTS.....	3
6 APPARATUS.....	4
7 SAMPLE HANDLING AND PREPARATION.....	4
8 PROCEDURE.....	4
9 CALCULATION AND REPORTING OF RESULTS.....	5
10 PRECISION.....	6
11 TEST REPORT.....	6
12 INSTRUMENTAL ANALYSIS.....	7
APPENDIX A THE PROCEDURE AND EFFECT OF SAMPLE HANDLING FOR AIR-EQUILIBRATED SAMPLES.....	10

STANDARDS AUSTRALIA

Australian Standard

Alumina

Part 1: Determination of loss of mass at 300°C and 1000°C

1 SCOPE

This Standard sets out a method for the determination of loss of mass on heating of aluminium oxide at 300°C and further loss of mass on ignition at 1000°C. By industry convention, these mass losses are often referred to as 'moisture' (MOI) and 'loss on ignition' (LOI) respectively.

This method is suitable for calcined alumina in the range 0.2% to 5% loss of mass at 300°C and 0.1% to 2% loss of mass at 1000°C.

This method provides for samples to be treated on an 'as-received' basis for determination of actual MOI and LOI in alumina samples. To improve precision of analysis in cases where 'as-received' results are not required, samples can be 'air-equilibrated' prior to analysis. 'Air-equilibration' can greatly affect MOI results and significantly alter LOI results. The 'air-equilibration' procedure and its effects are discussed in Appendix A.

Instrumental methods are also discussed.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

2243 Safety in laboratories (series)

2850 Chemical analysis—Interlaboratory test programs—For determining precision of analytical method(s)—Guide to the planning and conduct

3 PRINCIPLE

The test portion of aluminium oxide is dried at 300°C for 2 h and the loss of mass is determined by mass difference. The test portion is then ignited at 1000°C for 2 h and the further loss of mass is determined.

4 SAFETY

For information on laboratory safety, reference should be made to the relevant parts of AS 2243.

5 DESICCANTS

One of the following desiccants shall be used:

- (a) Phosphorus pentoxide.
- (b) Activated alumina.
- (c) Magnesium perchlorate.