

Australian Standard™

Non-destructive testing

**Part 2: Radiographic determination of
quality of ferrous castings**



This Australian Standard was prepared by Committee MT-007, Non-destructive Testing of Metals and Materials. It was approved on behalf of the Council of Standards Australia on 6 January 2006.
This Standard was published on 10 February 2006.

The following are represented on Committee MT-007:

Australian Railway Association
Australian Aerospace Non-Destructive Testing Committee
Australian Industry Group
Australian Institute for Non-Destructive Testing
Australian Nuclear Science & Technology Organisation
Australian Pipeline Industry Association
Bureau of Steel Manufacturers of Australia
Engineers Australia
National Association of Testing Authorities Australia
New Zealand Non-Destructive Testing Association
TestSafe Australia
Victorian WorkCover Authority
Welding Technology Institute of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 476, Sydney, NSW 2001.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 3507.2—2006

Non-destructive testing

Part 2: Radiographic determination of quality of ferrous castings

RECONFIRMATION NOTICE

Technical Committee MT-007 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 22 November 2016.

The following are represented on Technical Committee MT-007:

Australasian Thermographers Association
Australian Aerospace Non-Destructive Testing Committee
Australian Institute for Non-Destructive Testing
Australian Nuclear Science & Technology Organisation
AUSTROADS
Bureau of Steel Manufacturers of Australia
Engineers Australia
Institute of Electrical Inspectors
National Association of Testing Authorities Australia
New Zealand Non-Destructive Testing Association
TestSafe Australia
Welding Technology Institute of Australia
WorkSafe Victoria

NOTES

Australian Standard™

Non-destructive testing

Part 2: Radiographic determination of quality of ferrous castings

Originated as part of AS 3507—1987.
Previous edition AS 3507.2—2003.
Second edition 2006.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia
ISBN 0 7337 7245 5

PREFACE

This Standard was prepared by the Australian members of Joint Standards Australia/Standards New Zealand Committee MT-007, Non-destructive Testing of Metals and Materials to supersede AS 3507.2—2003, *Non-destructive testing, Part 2: Radiographic determination of quality of ferrous castings*.

After consultation with shareholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this revision is to change the method of assessment for quality in ferrous castings.

This Standard is one of a series of Standards covering Non-destructive testing Standards. The series comprises the following:

AS

3507 Non-destructive testing

3507.1 Part 1: Guide to radiography for ferrous castings

3507.2 Part 2: Radiographic determination of quality of ferrous castings (this Standard)

The term ‘informative’ has been used in this Standard to define the application of the appendix to which it applies. An ‘informative’ appendix is only for information and guidance.

Statements expressed in mandatory terms in notes to tables are deemed to be requirements of this Standard.

CONTENTS

	<i>Page</i>
FOREWORD.....	4
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	5
1.2 REFERENCED DOCUMENTS	5
1.3 DEFINITIONS	5
SECTION 2 EVALUATION OF DATA	
2.1 DISCONTINUITY TYPES	7
2.2 AREA OF TEST.....	7
2.3 METHOD OF ASSESSMENT	7
2.4 ASSESSMENT OF GAS POROSITY, BLOWHOLES AND INCLUSIONS.....	7
2.5 ASSESSMENT OF MACROSHRINKAGE	10
2.6 ASSESSMENT OF FILAMENTARY SHRINKAGE.....	11
2.7 ASSESSMENT OF HOT TEARS, CRACKS AND UNFUSED CHAPLETS	12
2.8 MULTIPLE DISCONTINUITIES OR MULTIPLE ZONES	12
SECTION 3 CLASSIFICATION OF QUALITY	
3.1 GAS POROSITY AND BLOWHOLES.....	14
3.2 INCLUSIONS	14
3.3 MACRO SHRINKAGE.....	14
3.4 FILAMENTARY SHRINKAGE	14
3.5 HOT TEARS, CRACKS AND UNFUSED CHAPLETS	14
3.6 WELD REPAIR DISCONTINUITIES	14
SECTION 4 ASSESSMENT OF WELD REPAIR DISCONTINUITIES	
4.1 WELD REPAIR.....	17
4.2 WELD REPAIR ASSESSMENT.....	17
SECTION 5 RADIOGRAPHIC VIEWING REQUIREMENTS	
5.1 QUALIFICATIONS AND VISUAL ACUITY OF PERSONNEL.....	18
5.2 EYE ADAPTATION	18
5.3 RADIOGRAPHIC IDENTIFICATION	18
5.4 RADIOGRAPHIC DENSITY.....	18
5.5 RADIOGRAPHIC SENSITIVITY.....	18
5.6 CONDITIONS OF RADIOGRAPHS	18
SECTION 6 INTERPRETATION AND ASSESSMENT	
6.1 INTERPRETATION.....	19
6.2 ASSESSMENT.....	19
SECTION 7 RECORDS AND TEST REPORT	
7.1 RECORDS.....	20
7.2 TEST REPORT	20
SECTION 8 QUALIFICATION OF NON-DESTRUCTIVE EXAMINATION PERSONNEL.....	22
APPENDIX A INFORMATION TO BE SUPPLIED WITH EQUITY AND ORDER	23

FOREWORD

Soundness of castings depends on such factors as size, section, configuration, method of moulding and design of runner and riser systems. These factors, and other aspects such as heat treatment, affect the grain structure and location and orientation of possible discontinuities. These factors have to be considered when choosing the appropriate test method and sensitivity.

Radiographic methods described in AS 3507.1 can be used to determine the size and nature but not necessarily the depth of discontinuities in castings. Each radiographic method can yield a radiograph with a range of sensitivities depending on section thickness.

For convenience in the assessment of integrity of castings, discontinuities in castings have been graded into severity indexes, which vary according to type of discontinuity. The severity index is then converted to a quality class.

Acceptance criteria or acceptable quality classes for discontinuities are normally specified in relevant product Standards or determined by agreement between the contracting parties after due consideration of size, configuration, and service requirements of the casting.

Where alternatives exist, the exact grading should be agreed between customer and contractor, if not covered by the product or application Standard.

Non-destructive testing methods are complementary; it is emphasized that the results of one test should be considered in relation to those obtained by another method. Accordingly, differing interpretations may be advantageously reassessed by alternative methods.

STANDARDS AUSTRALIA

Australian Standard Non-destructive testing

Part 2: Radiographic determination of quality of ferrous castings

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard specifies the method of classification of quality for radiography of steel castings.

1.2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS	
1929	Non-destructive testing—Glossary of terms
2314	Radiography of metals—Image quality indicators (II) and recommendations for their use
3507	Non-destructive testing,
3507.1	Part 1: Guide for radiography for ferrous castings
3998	Non-destructive testing—Qualification and certification of personnel
4738	Metal castings
4738.1	Part 1: Ferrous sand moulded
4749	Non-destructive testing—Terminology of and abbreviations for fusion weld imperfections as revealed by radiography.

1.3 DEFINITIONS

For the purpose of this Standard, in AS 1929, AS 4749 and those definitions given below apply.

1.3.1 Air lock

A cavity formed by the entrapment of air during pouring and solidification.

1.3.2 Blowholes

Gas porosity (see Clause 1.3.6) that is open to the surface of the casting.

1.3.3 Cold shuts

A discontinuity at the surface formed when liquid metal has flowed over previously solidified or oxidized metal, (not fused together).

1.3.4 Cracks

A stress-induced fracture of metal occurring after solidification.

1.3.5 Filamentary shrinkage

A form of shrinkage (see Clause 1.3.12) characterized by extensive branching and interconnected cavities.