

Australian Standard[®]

**Outdoor weathering of plastics in
the Australian environment**

Part 2: Guide for design purposes

This Australian Standard was prepared by Committee PL/10, Methods of Testing Plastics. It was approved on behalf of the Council of Standards Australia on 3 April 1989 and published on 18 August 1989.

The following interests are represented on Committee PL/10:

Bureau of Meteorology
CSIRO, Division of Building, Construction and Engineering
Plastics Institute of Australia
Society of Automotive Engineers
Telecom Australia

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

AS 1745.2—1989

Australian Standard[®]

**Outdoor weathering of plastics in
the Australian environment**

Part 2: Guide for design purposes

First published as AS 1745.2—1975.
Second edition 1989.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 5699 4

PREFACE

This Standard was prepared by the Standards Australia Committee for Methods of Testing Plastics under the direction of the Plastics Standards Board to supersede AS 1745.2—1975.

This Standard is technically equivalent to the previous edition, but the opportunity has been taken to clarify recommended procedures. In this edition 'hours of sunshine' has been replaced by the more precise concept of 'global radiation' as a measure of solar radiation accumulated during outdoor exposure.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 DEFINITIONS	3
4 GUIDELINES FOR THE PREPARATION OF DATA SHEETS	3
5 GUIDELINES FOR THE USE OF DATA SHEETS	4
 APPENDICES	
A SAMPLE DATA SHEET ON WEATHERING PERFORMANCE OF TEST SPECIMENS	8
B METHOD FOR ESTIMATING THE SERVICE LIFE OF A PLASTICS PRODUCT IN OUTDOOR SERVICE, USING AN ILLUSTRATIVE EXAMPLE	10

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS AUSTRALIA

Australian Standard

Outdoor weathering of plastics in the Australian environment

Part 2: Guide for design purposes

1 SCOPE. This Standard sets out the recommended method of accumulating, presenting and using data on the outdoor weathering of plastics taking into account the methods of production, fabrication and installation of the test specimens. The Standard will assist in the selection of suitable plastics materials for the manufacture of commercial products for outdoor use in the Australian environment.

2 REFERENCED DOCUMENTS. The following documents are referred to in this Standard:

AS	
1745	Outdoor weathering of plastics in the Australian environment
1745.1	Part 1: Commercial products
BS	
4618	Recommendations for the presentation of plastics design data Part 1: Mechanical properties

3 DEFINITIONS. For the purpose of this Standard, the definitions given in AS 1745.1 and those below apply.

3.1 Unit manufacturing process—a stage in the process of changing a raw material or an intermediate component into a finished or part-finished product.

3.2 Grade (of a plastics material)—the specific material used in the unit manufacturing process. A grade contains a specific polymer or polymer mixtures and various additives, e.g. plasticizers, colorants. Each grade is regarded as a unique material since any change in composition of the material may affect weathering performance.

NOTE: It is possible to obtain identical colours that have differing weathering characteristics with different pigments.

3.3 Global radiation.

3.3.1 Mean daily global radiation—the mean daily solar irradiation per unit area incident on a horizontal plane at the earth's surface over a stated number of complete years.

NOTE: The units are megajoules per square metre.

3.3.2 Total global radiation—the product of the mean daily global radiation and the number of days duration of exposure.

NOTE: The units are megajoules per square metre.

3.4 Total exposure period—the total period of exposure at the exposure site.

NOTE: This period is recorded in months or days.

3.5 Failure—the point at which the condition of the article is no longer acceptable for continued use.

4 GUIDELINES FOR THE PREPARATION OF DATA SHEETS.

4.1 General. When a new plastics grade has been developed, the eventual market should be critically reviewed, and the unit manufacturing processes likely to be used to produce commercial products from that grade should be established. A list of possible applications and the associated unit production processes used in the manufacture of commercial articles may be drawn up, and a series of suitable tests developed. (See Clause 4.2.)

The result of this review will indicate the data that should be provided in data sheet form for that grade. Where the grade is intended for 'general' application, the exclusion of unlikely applications or unit manufacturing processes could be of assistance in drawing up the list.

Where the grade has been developed for a specific application, the task is much simpler. For example, with an electrical grade for an outdoor switchboard, the minimum data required would relate to changes in the following properties as a result of outdoor exposure:

- Electrical and mechanical properties.
- Dimensional stability.
- Appearance and colour.
- Moisture resistance.

Specimens produced by the unit manufacturing process to be used to make the switchboard should be provided to obtain the data.

4.2 Guidelines for the selection of suitable tests.

4.2.1 Performance tests for material having general application. Tests should be applicable to the material grade and correspond to expected modes of degradation and the selected general performance requirements for the application.

BS 4618 provides useful guidelines for the selection of such tests. The methods used in BS 4618 for characterizing the grades should be used, except that AS 1745.1 should be used in preference to BS 4618: Section 4.2.

At least one test from each of the following categories should be carried out, on exposed and unexposed specimens, to determine changes as a result of outdoor exposure:

- Mechanical properties.
- Appearance.
- Dimensions.
- Electrical properties.
- Biological resistance.