

Australian Standard™

**Methods of test for single sided and
double sided pressure-sensitive
adhesive tape**

Method 1.1: Adhesion—Peel adhesion



This Australian Standard was prepared by Committee PK-025, Packaging Code. It was approved on behalf of the Council of Standards Australia on 8 September 2005.
This Standard was published on 28 October 2005.

The following are represented on Committee PK-025:

Australian Paints Manufacturers' Federation
Canmakers Institute of Australia
Department of Defence
Printing Industries Association of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 476, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 05182.

Australian Standard™

**Methods of test for single sided and
double sided pressure-sensitive
adhesive tape**

Method 1.1: Adhesion—Peel adhesion

Originated as AS Z24.3.1—1968.
Previous edition AS 1635.3.1—1993.
Revised and redesignated as AS 2313.1.1—2005.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 6927 6

PREFACE

This Standard was prepared by the Standards Australia Committee PK-025, Packaging Code to supersede AS 1635.3.1—1993, *Methods of test for pressure-sensitive adhesive tape*, Part 3.1: *Adhesion strength*.

The objective of this edition is to revise the apparatus and materials used in the procedure of the Standard.

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS.....	3
3 REAGENTS.....	3
4 APPARATUS AND MATERIALS.....	3
5 TEST CONDITIONS.....	4
6 PREPARATION OF TEST SPECIMENS.....	4
7 PROCEDURE.....	4
8 CALCULATION	5
9 TEST REPORT.....	5

STANDARDS AUSTRALIA

Australian Standard

Methods of test for single sided and double sided pressure-sensitive adhesive tape

Method 1.1: Adhesion—Peel adhesion

1 SCOPE

This Standard specifies the method for determining the adhesion strength of pressure-sensitive adhesive tape to a stainless steel test panel.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

1683 Methods of test for elastomers

1683.15.2 Method 15.2: Durometer hardness

2193 Calibration and classification of force-measuring systems

3 REAGENTS

3.1 Isopropynol

Reagent grade is required.

NOTE: Acetone, reagent grade may also be used.

4 APPARATUS AND MATERIALS

The following apparatus and materials are required:

- (a) *Tension testing machine*—complying with the requirements of AS 2193 for Grade B machines over suitable load ranges, and having a moving jaw or carriage with a rate of travel of 300 ± 10 mm/min.
- (b) *Stainless steel panel*—approximately 50 mm wide, at least 125 mm long, and approximately 1.5 mm thick and finished in the lengthwise direction to a bright annealed finish with a surface finish of $0.04 \mu\text{m}$.
- (c) *Steel roller (see Figure 1)*—of diameter 80 ± 5 mm and width 45 ± 1 mm, covered with rubber approximately 6 mm thick, and having a durometer hardness of 80 ± 5 Type A degrees (in accordance with AS 1683.15.2).

NOTE: The mass of the roller proper (which applies pressure to the specimen) should be 2.0 ± 0.1 kg. It should be so constructed that the mass of the handle is not added to the mass of the roller during use.

- (d) *Fresh absorbent cleaning material*—these clean materials shall be lint free and contain no soluble additives, e.g. surgical gauze, untreated paper tissue.
- (e) *Specimen cutter*—consisting of a 25 mm thick \times 200 mm long \times 25 mm wide aluminium bar stock. The edges for about 125 mm from one end shall be rounded slightly to form a handle. The width of the bar for 75 mm from the opposite end shall be narrowed to exactly 25 mm minus the thickness of a single razor blade (one of two razor blades used as cutting edges).