

Australian Standard[®]

**METHODS FOR THE
DETERMINATION OF UNIFORM
ELONGATION IN SHEET AND
STRIP METALS**

The following scientific, industrial and governmental organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Aluminium Development Council
Australian Institute of Metals
Bureau of Steel Manufacturers of Australia
Commonwealth Scientific and Industrial Research Organization
Confederation of Australian Industry
Department of Defence
Federal Chamber of Automotive Industries
Metal Trades Industry Association of Australia
National Association of Testing Authorities
Railways of Australia Committee
Society of Automotive Engineers—Australasia
University of Melbourne
University of New South Wales
University of Sydney

This standard, prepared by Committee MT/6, Mechanical Testing of Metals, was approved by the Metal Standards Board on behalf of the Council of the Standards Association of Australia on 18 February 1980, and was published on 1 June 1980.

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 78151.

Australian Standard[®]

**METHODS FOR THE
DETERMINATION OF UNIFORM
ELONGATION IN SHEET AND
STRIP METALS**

First published 1980

Incorporating:
Corrig.—1981

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 1914 2

PREFACE

This standard was prepared by the Association's Committee on Mechanical Testing of Metals at the request of the Metals Standards Board to provide standard methods whereby the formability of sheet and strip metals may be assessed by mechanical testing.

During preparation of this standard the committee considered other methods in use which call for multisectional test pieces, e.g. the 'circle arc' and the 'Sollac' methods, but decided against their inclusion because these methods are not in common use in Australia and because of problems associated with the preparation of test pieces which require unacceptably small tolerances for routine testing purposes, and further, because these methods are more sensitive to errors in parallelism and to errors caused by inhomogeneities in the metal than the methods included.

Methods that involve measurements between gauge marks on a parallel strip test piece which has been strained to the necking point or to the fracture point, have also been excluded because of inhomogeneity of strain causing unacceptable errors in the result.

Provision has been made at this stage for the use of a subsidiary gauge length for use in the testing of products. However, it is expected that the use of subsidiary gauge lengths will not be permitted when the standard is revised.

This standard requires reference to the following Australian standards:

- AS 1391 Methods for Tensile Testing of Metals
 AS 1545 Methods for the Calibration and Grading of Extensometers.

CONTENTS

	<i>Page</i>
METHOD	
1 Scope	3
2 Definitions	3
3 Symbols and Designations	3
4 Principle	3
5 Equipment	3
6 Preparation of Test Pieces	4
7 Test Procedures	4
8 Test Report	5
APPENDICES	
A Notes on Scale Expansion	8
B Notes on the use of Indirect Methods for the Determination of Uniform Elongation	9

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

**METHODS FOR THE DETERMINATION OF UNIFORM ELONGATION IN
SHEET AND STRIP METALS**

FOREWORD

In the testing of metals in accordance with AS 1391 for their forming properties, the strain at maximum force in a tensile test provides valuable information on the formability of the metal, particularly where deformation is predominantly by tensile stresses, as opposed to a combination of tensile and compressive stresses.

The principal difficulty in making accurate measurements of strain at maximum force arises from the fact that, with most ductile metals, the force/extension curve has an extremely flat maximum, so that the strain at maximum force is not easily and precisely identified. This difficulty can be overcome either by using equipment with highly sensitive force measuring ability (direct method), or by using indirect methods which involve measurement of the slope of the tensile curve.

METHOD

1 SCOPE. This standard sets out methods for the determination of uniform elongation in sheet and strip metals. The standard specifically covers the following methods:

- (a) Direct method.
- (b) Indirect methods—
 - (i) Nelson-Winlock method*
 - (ii) Logarithmic-plot method.

2 DEFINITIONS. For the purpose of this standard, the definitions given in AS 1391 and the following apply:

Uniform elongation—the total extension at maximum force, expressed as a percentage of the original gauge length.

True stress—the force per instantaneous cross-sectional area.

True strain—the natural logarithm of the ratio of the deformed gauge length to the original gauge length.

3 SYMBOLS AND DESIGNATIONS. For the purpose of this standard, the symbols and designations given in AS 1391 and the following apply:

- F_i = force at any instant 'i'
= force at e_i
- L_i = gauge length at any instant 'i'
- S_i = cross-sectional area of the test piece at any instant 'i'
- e_i = nominal strain at any instant 'i'
= $(L_i - L_0)/L_0$
- ϵ_i = true strain at any instant 'i'
= $\ln (L_i/L_0)$
= $\ln (1 + e_i)$
- σ_i = true stress at any instant 'i'
= F_i/S_i
- L_m = gauge length at maximum force

e_m = nominal strain at maximum force

ϵ_m = true strain at maximum force

A_m = uniform elongation
= $100 \times e_m$ percent.

4 PRINCIPLE.

4.1 Direct Method. A test piece is strained and changes in force and gauge length are recorded. The extension at maximum force is determined and the uniform elongation calculated.

4.2 Indirect Methods.

4.2.1 Nelson-Winlock method. The instantaneous value of the gradient in the $\ln \sigma_i / \ln \epsilon_i$ curve, measured at the point of maximum force, is numerically equal to the true strain at that point (ϵ_m). The uniform elongation, A_m , can be calculated from the following formula:

$$A_m = 100 ([\exp \epsilon_m] - 1)$$

The gradient of the curve, for some materials, is constant over a substantial portion of the curve up to and including the maximum force being reached. For these materials, the force at a value of strain which is less than the strain at maximum force and which lies within the region of the constant gradient curve is used to determine uniform elongation either by calculation or by the use of tables.

4.2.2 Logarithmic-plot method. The gradient of the $\ln \sigma_i / \ln \epsilon_i$ curve is determined from a logarithmic plot of stress/strain values.

5 EQUIPMENT. The equipment shall be capable of performing tests in accordance with AS 1391. The grade of extensometer (if used) shall be Grade E or better.

* 'Method of Determining the Percentage Elongation at Maximum Load in the Tension Test' by Paul G. Nelson and Joseph Winlock. *ASTM Bulletin*. January 1949.