

^{Dup.}
Superseded by AS 2806.1-1994

AS 2806.1—1985
UDC 622.349.2:620.113

London revision 2012 88208

Australian Standard[®] 2806.1—1985

ALUMINIUM ORES—SAMPLING Part 1—SAMPLING FROM MOVING STREAMS



STANDARDS ASSOCIATION OF AUSTRALIA
Incorporated by Royal Charter



This Australian standard was prepared by Committee MN/3, Aluminium Ores. It was approved on behalf of the Council of the Standards Association of Australia on 6 May 1985 and published on 9 August 1985.

The following interests are represented on Committee MN/3:

Aluminium Ore Producers
CSIRO, Division of Mineral Chemistry
CSIRO, Division of Mineral Physics
Department of Resources and Energy
Superintendent Organizations

Review of Australian Standards. To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all SAA publications will be found in the Catalogue of SAA Publications; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.

Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 83108.

AUSTRALIAN STANDARD

ALUMINIUM ORES—SAMPLING
Part 1
SAMPLING FROM MOVING
STREAMS

AS 2806.1—1985

First published1985

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.

ISBN 0 7262 3827 9



PREFACE

This standard was prepared by the Association's Committee on Aluminium Ores under the direction of the Minerals Standards Board. At present there are no standards for the sampling of aluminium ores although work is continuing on this topic in ISO/TC 129—Aluminium Ores.

This standard has been prepared to formalize the procedures currently in use in the industry.

The other parts of this standard are as follows:

- Part 2—Sampling from Stationary Situations
- Part 3—Preparation of Samples*
- Part 4—Determination of Quality Variation, Precision and Bias*
- Part 5—Determination of Moisture Content of Bulk Material*

*In course of preparation.

CONTENTS

	<i>Page</i>
SPECIFICATION	
1 Scope	3
2 Referenced Documents	3
3 Definitions	3
4 Establishing a Sampling Scheme	4
5 Number of Primary Increments and Sampling Units	5
6 Mass of Gross Samples and Subsamples	9
7 Mass of Increment	9
8 Mass-basis Sampling	9
9 Time-basis Sampling	11
10 Random Stratified Sampling—Fixed Mass or Time Intervals	12
11 Mechanical Sampling	12
12 Manual Sampling	13
13 Packing and Marking of Samples	14
APPENDICES	
A Derivation of Equation for Minimum Gross Sample Mass	16
B Table of Student's t Values	17
C Mechanical Sampling Devices	18
D Manual Sampling Implement	20

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1985

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
for
ALUMINIUM ORES—SAMPLING

PART 1—SAMPLING FROM MOVING STREAMS

1 SCOPE. This standard sets out requirements for the sampling of aluminium ores from moving streams to provide gross samples for sample preparation.

The provisions of this standard do not include stopped-belt sampling. AS 2806.2 deals with the situation in which the conveyor belt is stopped for the purpose of sampling. Although this standard is intended to cover all aluminium ore sampling from moving streams, the procedures recommended may not be applicable in cases of extreme segregation of material, e.g. due to moisture run-off for a very wet ore or dust generation for a very dry ore. In such cases it may be necessary to revert to stopped-belt sampling.

2 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

- AS 1152 Test sieves
 AS 2806 Aluminium Ores—Sampling
 Part 2—Sampling from Stationary Situations
 Part 3—Preparation of Samples*
 Part 4—Determination of Quality Variation, Precision and Bias*
 ISO 3534 Statistics—Vocabulary and Symbols

3 DEFINITIONS. For the purpose of this standard, definitions given in ISO 3534 and the following apply:

3.1 Constant mass division—method of sample division in which the retained portion from individual increments is of uniform mass.

3.2 Cut—a single pass of the sampling device through the ore stream.

3.3 Divided increment—quantity of ore obtained by division of the increment in order to decrease its mass.

3.4 Division—process of decreasing the sample mass (without modification of the particle size of the constituent pieces) where a representative part of the sample is retained while the remainder may be rejected.

3.5 Duplicate sampling—a particular case of replicate sampling (with only two replicate samples), for the purpose of estimating the average precision of sampling from a number of lots or sampling units.

3.6 Fixed rate division—method of sample division in which the retained portion from individual increments is a constant proportion of the original mass.

3.7 Gross sample—a sample formed when all primary increments or subsamples, either as taken or after having been prepared individually to a particular

stage of sample preparation, are combined in correct proportions for preparation of a laboratory sample.

3.8 Increment—the quantity taken by—

- (a) a single pass of the sampling device in the case of mechanical sampling;
 (b) either a single pass or the combined sum of multiple passes of the sampling implement in the case of manual sampling.

3.9 Isolated lot—a lot that is to be sampled without knowledge of its sampling characteristics.

3.10 Lot—a quantity of ore delivered at one time. The lot may be composed of one or more sampling units.

3.11 Manual sampling—sampling when increments forming subsamples and gross samples are taken by human effort using a hand-held implement.

3.12 Mass-basis sampling—method of taking increments at uniform mass intervals throughout the lot or sampling unit.

3.13 Mechanical sampling—sampling when increments forming subsamples and gross samples are taken by a sampling machine.

3.14 Nominal top size—size of aperture of the finest sieve (complying with AS 1152) through which a minimum of 95 percent of the mass of the ore passes.

3.15 Quality variation—a measure of the heterogeneity of a lot. It is the standard deviation of the quality characteristics between strata.

3.16 Random stratified sampling—taking increments at irregular periods within constant intervals of time, mass or space.

3.17 Reduction (in particle size)—decrease in dimension of the pieces constituting the sample without modification of the mass nor of the composition.

3.18 Replicate sampling—taking increments from the lot at equal intervals of time, mass or space. Increments are placed in rotation into different containers to give several replicate samples of approximately equal mass.

3.19 Sampling unit—discrete units (e.g. trains, section of belt, daily production) which comprise the lot.

3.20 Strata—approximately equal parts of a lot or sampling unit based on intervals of time, mass or space.

* In course of preparation