

Australian Standard™

**Methods for the analysis and testing of
lower rank coal and its chars**

**Part 7: Lower rank coal—Determination
of moisture in the analysis sample**

This Australian Standard was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 16 September 2002 and published on 1 October 2002.

The following are represented on Committee MN-001:

Australasian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Preparation Society
Australian Institute of Energy
CSIRO, Energy Technology
Coalfield Geology Council of New South Wales
Department of Mines and Energy, Queensland
Electricity Supply Association of Australia
Institution of Engineers, Australia
Minerals Council of Australia
University of Newcastle
University of New South Wales
University of Queensland

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 02277.

Australian Standard™

**Methods for the analysis and testing of
lower rank coal and its chars**

**Part 7: Lower rank coal—Determination
of moisture in the analysis sample**

Originated as AS 2434.7—1986.
Second edition 2002.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 4856 2

PREFACE

This Standard was prepared by Standards Australia Committee MN-001, Coal and Coke, to supersede AS 2434.7—1986, *Methods for the analysis and testing of lower rank coal and its chars*, Part 7: *Determination of moisture in the analysis sample of lower rank coal*.

This Standard describes two procedures, viz. direct gravimetric and drying in nitrogen, for the determination of moisture in the analysis sample of lower rank coals. Moisture content of the analysis sample of lower rank coal is generally less than 15 per cent.

Although the value of the result obtained for moisture in the analysis sample has little significance in itself, it is required for the calculation of other results to any required basis. As moisture content of coal can vary on standing, test portions for moisture determinations should be taken and weighed simultaneously with test portions for determinations of other properties.

Reference to the vacuum method described in AS 1038.3, *Coal and coke—Analysis and testing*, Part 3: *Proximate analysis of higher rank coal* has been deleted as it gives unacceptable results for lower rank coals.

CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 SAFETY	4
5 SAMPLE.....	4
6 DETERMINATION OF MOISTURE IN THE ANALYSIS SAMPLE	5
7 REPORTING OF RESULTS.....	8
8 PRECISION	8
9 TEST REPORT	8

STANDARDS AUSTRALIA

Australian Standard

Methods for the analysis and testing of lower rank coal and its chars

Part 7: Lower rank coal—Determination of moisture in the analysis sample

1 SCOPE

This Standard sets out two procedures for the determination of moisture in the analysis sample of lower rank coal, viz. direct gravimetric method, where the water is absorbed into magnesium perchlorate and weighed, and an indirect method, where the difference in the mass of the coal before and after drying is measured. Both methods involve drying under nitrogen.

2 REFERENCED DOCUMENTS

The following Standards are referred to in this Standard:

AS

1038	Coal and coke—Analysis and testing
1038.16	Part 16: Assessment and reporting of results
1152	Specification for test sieves
2243	Safety in laboratories (series)
2418	Coal and coke—Glossary of terms
2508	Safe storage and handling information card (series)
4264	Coal and coke—sampling
4264.3	Part 3: Lower rank coal—Sampling procedures

3 DEFINITIONS

For the purpose of this Standard, the definitions in AS 2418 apply.

4 SAFETY

For information on laboratory safety, reference should be made to the relevant parts of AS 2243 and AS 2508.

5 SAMPLE

5.1 General

The sample shall be taken according to AS 4264.3 and shall be prepared so that at least 99 percent passes a 212 μm sieve complying with AS 1152.

5.2 Equilibration of the sample

The sample received in the laboratory shall be brought into approximate equilibrium with the laboratory atmosphere by exposure in a thin layer on a tray. As many lower rank coals are prone to oxidation, the exposure time shall be kept to the minimum necessary. The sample shall be thoroughly mixed, preferably by mechanical means, immediately before the determination. Portions for duplicate determinations shall be weighed out consecutively. The determinations should not be made in the same apparatus at the same time.