

FINAL VERSION

VERSION FINALE

**Specifications for particular types of winding wires –
Part 20: Solderable polyurethane enamelled round copper wire, class 155**

**Spécifications pour types particuliers de fils de bobinage –
Partie 20: Fil brasable de section circulaire en cuivre émaillé avec polyuréthane,
classe 155**



CONTENTS

FOREWORD	3
INTRODUCTION	5
1 Scope	6
2 Normative references	6
3 Terms, definitions, general notes and appearance	6
3.1 Terms and definitions	6
3.2 General notes	6
3.2.1 Methods of test	6
3.2.2 Winding wire	6
3.3 Appearance	7
4 Dimensions	7
5 Electrical resistance	7
6 Elongation	7
7 Springiness	7
8 Flexibility and adherence	7
9 Heat shock	7
10 Cut-through	7
11 Resistance to abrasion (nominal conductor diameters from 0,250 mm up to and including 0,800 mm)	7
12 Resistance to solvents	8
13 Breakdown voltage	8
14 Continuity of insulation	8
15 Temperature index	8
16 Resistance to refrigerants	8
17 Solderability	8
17.1 General	8
17.2 Nominal conductor diameters up to and including 0,100 mm	9
17.3 Nominal conductor diameters over 0,100 mm	9
18 Heat or solvent bonding	9
19 Dielectric dissipation factor	9
20 Resistance to transformer oil	9
21 Loss of mass	9
23 Pin hole test	9
30 Packaging	9
Bibliography	10
Table 1 – Resistance to abrasion	8

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 20: Solderable polyurethane enamelled round copper wire, class 155

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

DISCLAIMER

This Consolidated version is not an official IEC Standard and has been prepared for user convenience. Only the current versions of the standard and its amendment(s) are to be considered the official documents.

This Consolidated version of IEC 60317-20 bears the edition number 3.1. It consists of the third edition (2013-10) [documents 55/1411/FDIS and 55/1432/RVD] and its amendment 1 (2019-06) [documents 55/1689/CDV and 55/1738/RVC]. The technical content is identical to the base edition and its amendment.

This Final version does not show where the technical content is modified by amendment 1. A separate Redline version with all changes highlighted is available in this publication.

International Standard IEC 60317-20 has been prepared by IEC technical committee 55: Winding wires.

This third edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- new 3.2.2 containing general notes on winding wire, formerly a part of the scope;
- revision to references to IEC 60317-0-1:2013 to clarify that their application is normative;
- modification to Clause 15 to remove specific wire specimen sizes;
- consolidation of 17.1 and 17.2 of the solderability requirements;
- modification to Clause 19, Dielectric dissipation factor;
- new Clause 23, Pin hole test.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The numbering of clauses in this standard is not continuous from Clauses 20 and 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851);
- 2) Specifications for particular types of winding wires (IEC 60317);
- 3) Packaging of winding wires (IEC 60264).

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 20: Solderable polyurethane enamelled round copper wire, class 155

1 Scope

This part of IEC 60317 specifies the requirements of solderable enamelled round copper winding wire of class 155 with a sole coating based on polyurethane resin, which may be modified providing it retains the chemical identity of the original resin and meets all specified wire requirements.

NOTE A modified resin is a resin that has undergone a chemical change, or contains one or more additives to enhance certain performance or application characteristics.

The range of nominal conductor diameters covered by this standard is:

- Grade 1: 0,018 mm up to and including 0,800 mm;
- Grade 2: 0,020 mm up to and including 0,800 mm.

The nominal conductor diameters are specified in Clause 4 of IEC 60317-0-1:2013.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-1:2013, *Specifications for particular types of winding wires – Part 0-1: General requirements – Enamelled round copper wire*

3 Terms, definitions, general notes and appearance

3.1 Terms and definitions

Subclause 3.1 of IEC 60317-0-1:2013 applies.

3.2 General notes

3.2.1 Methods of test

Subclause 3.2.1 of IEC 60317-0-1:2013 applies. In case of inconsistencies between IEC 60317-0-1:2013 and this part of IEC 60317, the latter shall prevail.

3.2.2 Winding wire

Class 155 is a thermal class that requires a minimum temperature index of 155 and a heat shock temperature of at least 175 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be operated and this will depend on many factors, including the type of equipment involved.