

# Laboratory Screening Test to Determine the Ability of Scale Inhibitors to Prevent the Precipitation of Barium Sulfate or Strontium Sulfate, or Both, from Solution (for Oil and Gas Production Systems)

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

**CAUTIONARY NOTICE:** NACE International standards are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE FirstService Department, 15835 Park Ten Place, Houston, TX 77084-5145 (tel: +1 281-228-6200, email: [firstservice@nace.org](mailto:firstservice@nace.org)).

## ABSTRACT

*This standard describes a test method to screen scale inhibitors for their ability to prevent precipitation of BaSO<sub>4</sub> or SrSO<sub>4</sub>, or both, from oilfield brines. This standard test method is intended to provide the user with a relative and quantitative measure of the ability of scale inhibitors to prevent (1) the formation and (2) the precipitation of solid BaSO<sub>4</sub> or SrSO<sub>4</sub>, or both, which are necessary and critical stages in scale deposition. This standard is maintained by Task Group 383.*

## KEYWORDS

*Scale inhibitors, sulfate*

# Foreword

Mineral scale may be defined as an adherent deposit of predominantly inorganic compounds. A common process leading to scale formation is the precipitation of sparingly soluble salts from oilfield brines. Some oilfield brines contain sufficient sulfate ions ( $\text{SO}_4^{2-}$ ) in the presence of barium ions ( $\text{Ba}^{2+}$ ) or strontium ions ( $\text{Sr}^{2+}$ ), or both, that the potential for forming barium sulfate ( $\text{BaSO}_4$ ) scale or strontium sulfate ( $\text{SrSO}_4$ ) scale, or both, exists due to changes in physical or chemical conditions. Often the formation of scale results in reduced production and increased maintenance costs. In some locations, naturally occurring radioactive materials (NORM) have been found to incorporate themselves into the scale. This complication may result in significant health, safety, and liability concerns and increased scale disposal costs.

Removal of scale after it has formed is particularly difficult when  $\text{BaSO}_4$  and  $\text{SrSO}_4$  are involved. Therefore, oil and gas producers most often use treatment chemicals to inhibit precipitation of these scales and reduce their tendency to adhere to surfaces. The choice of the best scale inhibitor for a given application often follows a lengthy testing program. The program typically begins with the collection of potentially useful products and then evaluation of them through a screening process in the laboratory to determine whether specific products or classes of products perform better than others.

NACE Standard TM0374<sup>1</sup> addresses only the screening of  $\text{CaSO}_4$  and  $\text{CaCO}_3$  scale inhibitors. By contrast, this standard test method is intended to provide the user with a relative and quantitative measure of the ability of scale inhibitors to prevent (1) the formation and (2) the precipitation of solid  $\text{BaSO}_4$  or  $\text{SrSO}_4$ , or both, which are necessary and critical stages in scale deposition. This standard is intended for use by skilled laboratory personnel who have previously performed similar tests. The laboratory screening procedure described in this standard may not allow for the simulation of all oilfield system variables. It must be regarded only as a starting point in the evaluation of scale inhibitors. The procedure standardizes the collection of screening test results to facilitate discussion of the results by interested parties. No attempt has been made to define the test brine composition, test temperature, or test duration. Users of this standard must agree on these and other critical parameters to facilitate comparison of test results.

This standard was originally prepared in 1997 by Work Group T-1D-36a, a subgroup of Task Group (TG) T-1D-36, "Scale Inhibitor Evaluation in Oil and Gas Production," a component of Unit Committee T-1D, "Corrosion Monitoring and Control of Corrosion Environments in Petroleum Operations." It was reaffirmed in 2002 by Specific Technology Group (STG) 31, "Oil and Gas Production—Corrosion and Scale Inhibition," and it was revised in 2010 and 2018 by TG 383, "Scale Inhibitor Evaluation in Oil and Gas Production." This standard is issued by NACE International under the auspices of STG 31.

In NACE standards, the terms **shall**, **must**, **should**, and **may** are used in accordance with the definitions of these terms in the NACE Publications Style Manual. The terms **shall** and **must** are used to state a requirement, and are considered mandatory. The term **should** is used to state something good and is recommended, but is not considered mandatory. The term **may** is used to state something considered optional.

# Laboratory Screening Test to Determine the Ability of Scale Inhibitors to Prevent the Precipitation of Barium Sulfate or Strontium Sulfate, or Both, from Solution (for Oil and Gas Production Systems)

1.	General .....	4
2.	Test Equipment .....	4
3.	Reagents .....	4
4.	Preparation of Test Solutions .....	5
5.	Test Procedure .....	5
6.	Calculation and Reporting of Test Results .....	6
	References .....	7
	Appendix A: Sample Stabilization and Analysis (Nonmandatory) .....	7