

# Evaluation of Exterior Protective Coatings for Seawater Immersion Service

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

**CAUTIONARY NOTICE:** NACE International standards are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE FirstService Department, 15835 Park Ten Place, Houston, TX 77084-5145 (tel: +1 281-228-6200, email: [firstservice@nace.org](mailto:firstservice@nace.org)).

## ABSTRACT

*This updated NACE International standard test method specifies test methods to evaluate the performance of liquid coating systems for seawater immersion services. This test method is intended for use by facility owners and coating manufacturers. The test method covers liquid exterior protective coating systems for offshore platform steel structures, piers, docks, pilings, subsea valves, and well-heads at normal seawater temperature.*

*Included are four test methods—including cathodic disbondment, seawater immersion resistance, aging stability, and edge coverage—used to evaluate coating systems. The test method also includes two tables; Table 1 details fingerprinting of coating materials, and Table 2 details the test panel geometry, size, substrate material, and minimum quantity.*

## KEYWORDS

*Aging stability test, anode, anode isolation, cathodic disbondment test, coating system, DFT, dry film thickness, edge coverage test, fingerprinting test, flexure strain, high-impedance multimeter, holiday, induction time, liquid exterior protective coating systems, NACE No. 2, near-white metal, reference electrode, seawater immersion resistance test, STG 03, surface profile, synthetic seawater, test panels, TG 264, wet film thickness, WFT.*

# Foreword

Exterior surfaces of submerged offshore platform steel structures, piers, docks, pilings, subsea valves, and wellheads are normally protected by sacrificial anodes, impressed current, or mixed-mode cathodic protection (CP) system. The exterior surfaces of submerged steel can be coated with protective coatings before their subsea installation to complement the CP system. The coatings are designed to provide maintenance-free service during the designed service life of the subsea structures.

The purpose of this NACE International standard test method is to specify test methods to evaluate the performance of liquid coating systems for seawater immersion services. This test method is intended for use by facility owners and coating manufacturers.

This NACE standard test method was prepared in 2004 and revised in 2019 by NACE Task Group (TG) 264 on “Offshore Exterior Submerged Coatings: Standard Test Method.” This TG is administered by Specific Technology Group (STG) 03, “Coatings and Linings, Protective: Immersion and Buried Service.” It is sponsored by STG 33, “Oil and Gas Production—Nonmetallics and Wear Coatings (Metallic).” This standard is issued by NACE under the auspices of STG 03.

In NACE standards, the terms **shall**, **must**, **should**, and **may** are used in accordance with the definitions of these terms in the NACE Publications Style Manual. The terms **shall** and **must** are used to state a requirement, and are considered mandatory. The term **should** is used to state something good and is recommended, but is not considered mandatory. The term **may** is used to state something considered optional.

# Evaluation of Exterior Protective Coatings for Seawater Immersion Service

1.	General .....	4
2.	Definitions .....	4
3.	Coating Materials .....	4
4.	Test Solution.....	6
5.	Test Panels.....	6
6.	Coating Application .....	6
7.	Cathodic Disbondment Test .....	7
8.	Seawater Immersion Resistance Test.....	10
9.	Aging Stability Test.....	11
10.	Edge Coverage Test.....	11
	References.....	13
<b>Tables</b>		
	Table 1. Fingerprinting of Coating Materials.....	5
	Table 2. Test Panel Geometry, Size, Substrate Material, and Minimum Quantity .....	6
<b>Figure</b>		
	Figure 1. 90° Aluminum Angle for Edge Coverage Test .....	12