



Metallic materials — Tensile testing — Method of test at room temperature



AS 1391:2020

This Australian Standard® was prepared by MT-006, Mechanical Testing Of Metals. It was approved on behalf of the Council of Standards Australia on 17 June 2020.

This Standard was published on 26 June 2020.

The following are represented on Committee MT-006:

- Australian Pipelines and Gas Association
- Bureau of Steel Manufacturers of Australia
- Materials Australia
- National Association of Testing Authorities Australia
- University of Technology Sydney
- Weld Australia

This Standard was issued in draft form for comment as DR AS 1391:2020.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76072 913 4



Metallic materials — Tensile testing — Method of test at room temperature

Originated as AS A23—1928.
Third edition 1964.
Revised and redesignated as AS 1391—1974.
Previous edition 2007.
Fifth edition 2020.

COPYRIGHT

© ISO 2020 — All rights reserved
© Standards Australia Limited 2020

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Test Method was prepared by the Standards Australia Committee MT-006, Mechanical Testing of Metals to supersede AS 1391—2007 *Metallic materials—Tensile testing at ambient temperature*.

The objective of this Test Method is to specify the method for tensile testing of metallic materials and define the mechanical properties which can be determined at room temperature.

NOTE Annex A contains further recommendations for computer controlled testing machines.

This Test Method is identical with, and has been reproduced from, ISO 6892-1:2019, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*.

As this document has been reproduced from an International Standard or Test Method or Technical Specification or Technical Report, the following applies:

- (a) In the source text “this part of ISO 6892” should read “this Australian Test Method”.
- (b) A full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface	ii
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	6
5 Principle	7
6 Test pieces	8
6.1 Shape and dimensions	8
6.1.1 General	8
6.1.2 Machined test pieces	8
6.1.3 Unmachined test pieces	8
6.2 Types	9
6.3 Preparation of test pieces	9
7 Determination of original cross-sectional area	9
8 Original gauge length and extensometer gauge length	9
8.1 Choice of the original gauge length	9
8.2 Marking the original gauge length	10
8.3 Choice of the extensometer gauge length	10
9 Accuracy of testing apparatus	10
10 Conditions of testing	10
10.1 Setting the force zero point	10
10.2 Method of gripping	11
10.3 Testing rates	11
10.3.1 General information regarding testing rates	11
10.3.2 Testing rate based on strain rate (method A)	11
10.3.3 Testing rate based on stress rate (method B)	13
10.3.4 Report of the chosen testing conditions	14
11 Determination of the upper yield strength	15
12 Determination of the lower yield strength	15
13 Determination of proof strength, plastic extension	15
14 Determination of proof strength, total extension	16
15 Method of verification of permanent set strength	16
16 Determination of the percentage yield point extension	16
17 Determination of the percentage plastic extension at maximum force	16
18 Determination of the percentage total extension at maximum force	17
19 Determination of the percentage total extension at fracture	17
20 Determination of percentage elongation after fracture	17
21 Determination of percentage reduction of area	18
22 Test report	19
23 Measurement uncertainty	19
23.1 General	19
23.2 Test conditions	20

23.3	Test results.....	20
Annex A	(informative) Recommendations concerning the use of computer-controlled tensile testing machines.....	33
Annex B	(normative) Types of test pieces to be used for thin products: sheets, strips, and flats between 0,1 mm and 3 mm thick.....	39
Annex C	(normative) Types of test pieces to be used for wire, bars, and sections with a diameter or thickness of less than 4 mm.....	42
Annex D	(normative) Types of test pieces to be used for sheets and flats of thickness equal to or greater than 3 mm and wire, bars, and sections of diameter or thickness equal to or greater than 4 mm.....	43
Annex E	(normative) Types of test pieces to be used for tubes.....	47
Annex F	(informative) Estimation of the crosshead separation rate in consideration of the stiffness (or compliance) of the testing equipment.....	49
Annex G	(normative) Determination of the modulus of elasticity of metallic materials using a uniaxial tensile test.....	51
Annex H	(informative) Measuring the percentage elongation after fracture if the specified value is less than 5 %.....	60
Annex I	(informative) Measurement of percentage elongation after fracture based on subdivision of the original gauge length.....	61
Annex J	(informative) Determination of the percentage plastic elongation without necking, A_{wn}, for long products such as bars, wire, and rods.....	63
Annex K	(informative) Estimation of the uncertainty of measurement.....	64
Annex L	(informative) Precision of tensile testing — Results from interlaboratory programmes.....	68
Bibliography		75

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 1, *Uniaxial testing*.

This second edition cancels and replaces the first edition (ISO 6892-1:2009), which has been technically revised with the following changes:

- a) renumbering of [Clause 10](#);
- b) additional information about the use of Method A and B;
- c) new denomination for:
 - 1) Method A closed loop → A1
 - 2) Method A open loop → A2;
- e) addition of [A.5](#);
- f) addition in Annex F for determination of the stiffness of the testing equipment;
- g) new normative Annex G: Determination of the modulus of elasticity of metallic materials using a uniaxial tensile test;
- h) the old Annex G is renamed to Annex H, Annex H to Annex I, etc.

ISO 6892 consists of the following parts, under the general title *Metallic materials — Tensile testing*:

- *Part 1: Method of test at room temperature*
- *Part 2: Method of test at elevated temperature*
- *Part 3: Method of test at low temperature*
- *Part 4: Method of test in liquid helium*

Introduction

During discussions concerning the speed of testing in the preparation of ISO 6892, it was decided to recommend the use of strain rate control in future revisions.

In this part of ISO 6892, there are two methods of testing speeds available. The first, method A, is based on strain rates (including crosshead separation rate) and the second, method B, is based on stress rates. Method A is intended to minimize the variation of the test rates during the moment when strain rate sensitive parameters are determined and to minimize the measurement uncertainty of the test results. Therefore, and out of the fact that often the strain rate sensitivity of the materials is not known, the use of method A is strongly recommended.

Australian Standard[®]

Metallic materials — Tensile testing — Method of test at room temperature

1 Scope

This part of ISO 6892 specifies the method for tensile testing of metallic materials and defines the mechanical properties which can be determined at room temperature.

NOTE Annex A contains further recommendations for computer controlled testing machines.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

NOTE In what follows, the designations “force” and “stress” or “extension”, “percentage extension”, and “strain”, respectively, are used on various occasions (as figure axis labels or in explanations for the determination of different properties). However, for a general description or point on a curve, the designations “force” and “stress” or “extension”, “percentage extension”, and “strain”, respectively, can be interchanged.

3.1

gauge length

L

length of the parallel portion of the test piece on which elongation is measured at any moment during the test

3.1.1

original gauge length

L_0

length between *gauge length* (3.1) marks on the test piece measured at room temperature before the test

3.1.2

final gauge length after fracture

L_u

length between *gauge length* (3.1) marks on the test piece measured after rupture, at room temperature, the two pieces having been carefully fitted back together so that their axes lie in a straight line

3.2

parallel length

L_c

length of the parallel reduced section of the test piece

Note 1 to entry: The concept of parallel length is replaced by the concept of distance between grips for unmachined test pieces.

3.3

elongation

increase in the *original gauge length* (3.1.1) at any moment during the test