

Australian/New Zealand Standard™

Methods of test for pulp and paper

Method 203s: Forming handsheets for physical testing of pulp



AS/NZS 1301.203s:2007

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 14 November 2007 and on behalf of the Council of Standards New Zealand on 30 November 2007. This Standard was published on 31 December 2007.

The following are represented on Committee PK-019:

Australian Institute of Packaging
Australian Plantation Products and Paper Industry Council (A3P)
Appita
Ensis Papro, SCION
National Association of Forest Industries

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.standards.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR 07168.

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

RECONFIRMATION

OF

AS/NZS 1301.203s:2007

Methods of test for pulp and paper

Method 203s: Forming handsheets for physical testing of pulp

RECONFIRMATION NOTICE

Technical Committee PK-019 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 4 April 2017.

Approved for reconfirmation in New Zealand on behalf of the Standards Council of New Zealand on 10 August 2017.

The following are represented on Technical Committee PK-019:

Appita
New Zealand Paper Forum
Monash University
Scion

NOTES

Australian/New Zealand Standard™

Methods of test for pulp and paper

Method 203s: Forming handsheets for physical testing of pulp

Originated in Australia as AS 1301.P203m—1957.
Previous edition AS/NZS 1301.203s:1993.
Sixth edition AS/NZS 1301.203s:2007.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 476, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

Contents

	<i>Page</i>
1 Scope.....	1
2 Normative references.....	1
3 Apparatus.....	1
4 Preparation of sample	1
5 Forming handsheets.....	4
6 Report.....	8
Annex A Bibliography.....	9

Foreword

This standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper, as part of AS/NZS 1301, *Methods of test for pulp and paper*.

This edition cancels and replaces AS/NZS 1301.203s:1993.

This Standard has been revised for technical reasons; particularly to define the disintegration procedure more precisely and to correct an erroneous statement in the couching procedure.

The term 'informative' has been used in this Standard to define the application of the annex to which it applies. An 'informative' annex is only for information and guidance.

NOTES

Forming handsheets for physical testing of pulp

1 Scope

This Standard prescribes the procedure to be used for making handsheets from samples of pulp for subsequent physical testing according to AS/NZS 1301.208s. Two sheet making procedures are described. One involves draining an aliquot of stock on a wire, discarding the white water and then couching, pressing and drying the formed sheet. The second, which is particularly applicable to high-yield pulps, uses the same technique except that the white water, instead of being discarded, is recirculated so that the contribution of the fines fraction is not lost.

2 Normative references

The following documents are referred to in this standard.

AS

1301.417s Sampling paper, board and pulp for testing

AS/NZS

1301.206s Freeness of pulp

1301.207s Determination of stock concentration

1301.208s Physical testing of pulp handsheets

1301.214s Equipment for preparation of handsheets

1301.215s Removal of latency

1301.415s Standard atmosphere for testing paper and board and procedure for monitoring the atmosphere

NZS

1301.417s Sampling paper, board and pulp for testing

3 Apparatus

3.1 Sheetmaking equipment—as described in AS/NZS 1301.214s.

4 Preparation of sample

4.1 General

If the handsheets are being formed to evaluate a pulp lot, the sample shall be selected in accordance with AS 1301.417s/NZS 1301.417s. If the sheets are being formed from another type of sample, report the source of the sample and, if possible, the sampling procedure used.

Make sure that the portions taken for making handsheets are representative of the pulp.

If the pulp is not processed immediately, store the sample in a cool dark place. Protect dry samples from dust by wrapping or by the use of dustproof containers. Store slush pulp and moist pulp in airtight containers.

Use distilled or deionized water, or the equivalent, for all operations up to and including dilution in the stock divider [1], [2] and [3]. The water used in the sheet machine need not be this quality, but it must be colourless and free from suspended matter and entrained air, except when using recycled white water.

4.2 Conventional sheet former

If it is required that latency in the pulp be removed, which is usually the case with mechanical pulps, do this according to AS/NZS 1301.215s and then proceed to Clause 4.4.