

AS 1397:2021



Continuous hot-dip metallic coated steel sheet and strip — Coatings of zinc and zinc alloyed with aluminium and magnesium



AS 1397:2021

This Australian Standard® was prepared by MT-001, Iron And Steel. It was approved on behalf of the Council of Standards Australia on 11 February 2021.

This Standard was published on 26 February 2021.

The following are represented on Committee MT-001:

- Australasian Corrosion Association
- Australian Building Codes Board
- Australian Industry Group
- Australian Steel Association
- Australian Steel Institute
- Bureau of Steel Manufacturers of Australia
- Materials Australia

This Standard was issued in draft form for comment as DR AS 1397:2020.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76113 218 6

Continuous hot-dip metallic coated steel sheet and strip — Coatings of zinc and zinc alloyed with aluminium and magnesium

Originated as part of AS A20—1934.
Revised and redesignated as AS 1397—1973.
Previous edition 2011.
Seventh edition 2021.

© Standards Australia Limited 2021

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-001, Iron and Steel, to supersede AS 1397—2011.

This Standard maintains the requirements of AS 1397 — 2011 and includes a reduction in the minimum aluminium content threshold for Type ZM coatings (from 5 % to 3 %). The expanded chemistry range for Type ZM coatings has resulted in nomination of two sub-Types, identified as “ZMa” and “ZMb”. The revised Standard also introduces an additional coating class for Type AM coatings, AM225.

Committee MT-001 has sought to align with the following international and national Standards, where applicable:

- (a) ISO 9364:2017, *Steel sheet, 55 % aluminium-zinc alloy-coated by the continuous hot-dip process of commercial, drawing and structural qualities*
- (b) ISO 4998:2014, *Continuous hot-dip zinc-coated and zinc-iron alloy-coated carbon steel sheet of structural quality*
- (c) ISO 3575:2016, *Continuous hot-dip zinc-coated and zinc-iron alloy-coated carbon steel sheet of commercial and drawing qualities*
- (d) ASTM A1046/A1046M, *Standard specification for steel sheet, zinc-aluminium-magnesium alloy-coated by the hot-dip process*
- (e) ASTM A902-18a, *Standard terminology relating to metallic coated steel products*
- (f) ASTM A875/A875M-13, *Standard specification for steel sheet, zinc-5 % aluminium alloy-coated by the hot-dip process*
- (g) EN 10346:2015, *Continuously hot-dip coated steel flat products for cold forming — Technical delivery conditions*
- (h) JIS G 3323:2019, *Hot-dip zinc-aluminium-magnesium alloy-coated steel sheet and strip*

The major changes in this edition are as follows:

- (i) Inclusion of additional coating chemistries within the ZM Coating Type and division of that coating Type into two sub-Types, (ZMa and ZMb).
- (ii) Inclusion of ZM Type coatings with aluminium content (by mass) in the range of 3 % to less than 5 % to broaden compatibility with coating chemistries contained within ASTM A1046/A1046M. The expanded range of coating chemistries (Type ZMb) is reflected by ASTM A1046/A1046M Type 2 coating chemistries.
- (iii) The inclusion of an additional coating class within Type AM coatings of AM225.

The terms “normative” and “informative” are used in Standards to define the application of the appendices to which they apply. A “normative” appendix is an integral part of a Standard, whereas an “informative” appendix is only for information and guidance.

Contents

Preface	ii
Section 1 Scope and general	1
1.1 Scope	1
1.2 Normative references	1
1.3 Terms and definitions	2
1.4 Product designation	4
1.4.1 General	4
1.4.2 Designation of steel grade	4
1.4.3 Designation of coating class and surface finish	4
1.5 Rounding of test result values	6
1.5.1 General	6
1.5.2 For tensile test results	6
1.5.3 For coating mass results	6
1.6 Marking	6
1.6.1 Package	6
1.6.2 Product	6
Section 2 Steel base	7
2.1 Scope of section	7
2.2 Chemical composition	7
2.2.1 General	7
2.2.2 Cast analysis	7
2.2.3 Unspecified chemical elements	7
2.2.4 Product analysis	7
2.3 Tensile test	8
2.3.1 General	8
2.3.2 Orientation of test piece	8
2.4 Bend test	8
2.4.1 General	8
2.4.2 Orientation of test pieces	8
2.5 Dimensional tolerances	9
2.5.1 General	9
2.5.2 Specified thickness	9
Section 3 Coating	11
3.1 Scope of section	11
3.2 Determination of coating mass	11
3.2.1 General	11
3.2.2 Test specimens for spot tests	11
3.2.3 Test Methods	11
3.2.4 Continuous monitoring	11
3.3 Determination of coating adhesion	12
3.3.1 General	12
3.3.2 Selection of test specimen	12
Appendix A (informative) Purchasing guidelines	15
Appendix B (normative) Means of demonstrating conformance with this Standard	17
Appendix C (informative) Information on coating thickness determination and on the thickness/mass relationship between base steel and coating	19
Appendix D (informative) Information and guidelines on the selection of steel grades and coating classes	23
Appendix E (informative) Surface conditioning and surface treatment	27
Bibliography	29

NOTES

Australian Standard[®]

Continuous hot-dip metallic coated steel sheet and strip — Coatings of zinc and zinc alloyed with aluminium and magnesium

Section 1 Scope and general

1.1 Scope

This Standard specifies requirements for continuously hot-dip metallic coated sheet steel and strip supplied in thicknesses up to and including 5.0 mm.

Requirements for product conformity to this Standard are given in [Appendix B](#).

Requirements covered in this Standard are as follows:

- (a) Formability grades of steel.
- (b) Structural grades of steel.
- (c) Classes of zinc coating, including differential coatings.
- (d) Classes of zinc coating converted to zinc/iron alloy.
- (e) Classes of zinc/aluminium coatings.
- (f) Classes of zinc/aluminium/magnesium alloy coating.
- (g) Classes of aluminium/zinc alloy coating.
- (h) Classes of aluminium/zinc/magnesium alloy coating.
- (i) Surface finish.

NOTE 1 Advice and recommendations on information to be supplied by the purchaser at the time of enquiry or order are contained in [Appendix A](#).

NOTE 2 The specified requirements apply to the full length and full width of the product supplied, unless otherwise indicated.

NOTE 3 Within the description of the classes of coatings, the majority element present is listed first, followed by the next major element and followed by a third element if applicable.

1.2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document.

NOTE Documents referenced for informative purposes are listed in the Bibliography.

AS 1391, *Metallic materials — Tensile testing of ambient temperature*

AS 2331.2.1, *Methods of test for metallic and related coatings, Method 2.1: Tests for average coating mass per unit area or for thickness — Dissolution methods — Strip and weigh, and analytical*

AS 2331.2.3, *Methods of test for metallic and related coatings, Method 2.3: Tests for average coating mass per unit area or for thickness — Hydrogen evolution method for zinc coatings*

AS 2505.1, *Metallic materials, Method 1: Sheet, strip and plate — Bend tests*

AS/NZS 1050, *Methods for the analysis of iron and steel (all parts)*

AS/NZS 1365, *Tolerances for flat-rolled steel products*