

IN-LB

Inch-Pound Units

SI

International System of Units

Form Pressure Exerted by Self-Consolidating Concrete: Primary Factors and Prediction Models—Report

Reported by ACI Committee 237

ACI PRC-237.2-21



American Concrete Institute
Always advancing



Form Pressure Exerted by Self-Consolidating Concrete: Primary Factors and Prediction Models—Report

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Form Pressure Exerted by Self-Consolidating Concrete: Primary Factors and Prediction Models—Report

Reported by ACI Committee 237

Anton K. Schindler*, Chair

Lloyd J. Keller*, Secretary

Mohamed Bassuoni
Claude Bedard
Peter H. Billberg
Joseph A. Daczko
Geert De Schutter
Kirk K. Deadrick
Liberato Ferrara

Dimitri Feys
G. Terry Harris
Jiong Hu
Venkatesh S. Iyer
Samuel Keske
Kamal H. Khayat**
Eric P. Koehler

David A. Lange*
Darmawan Ludirdja
George Morcouc
H. Celik Ozyildirim
Eric S. Peterson*
Ketan R. Sompura
Mohammed Sonebi

Caroline M. Talbot
Nathan A. Tregger
Stacia Van Zetten*
Olafur H. Wallevik
Kejin Wang
Ammar Yahia

Consulting Members

Erika E. Holt

Gary F. Knight

Caijun Shi

*Voting members who led the development of this report.

‡Subcommittee Chair.

The committee acknowledges K. Vallurupalli, A. Omran, M. Matias, L. Proietti, and D. Toon for their contributions to this report.

Given the high flowability and relatively fast casting rate of self-consolidating concrete (SCC), such concrete can exert high form pressure. Accurate assessment of form pressure is necessary from safety and economic points of view. The maximum form pressure and pressure decay are dependent on the structural buildup of the concrete at rest following placement, as well as on the placement parameters. The structural buildup at rest is affected by the thixotropy of the mixture. This report presents information on key parameters, including constituent materials; mixture proportioning; and casting parameters such as the casting rate, concrete temperature, and reinforcement percentage, affecting thixotropy and SCC form pressure. Prediction models available for estimating SCC form pressure are presented. Findings from two round-robin field studies

conducted to validate these models are also discussed. This report should be of interest to concrete professionals, including concrete suppliers and formwork designers, because it covers: 1) the influence of SCC proportions and casting parameters on form pressure; 2) means to estimate formwork pressure with examples; and 3) techniques to measure formwork pressure in field applications.

Keywords: form pressure; lateral pressure; self-consolidating concrete; structural buildup at rest; thixotropy.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 2

1.1—Introduction, p. 2

1.2—Scope, p. 3

1.3—Use of U.S. Customary Units in this report, p. 3

CHAPTER 2—NOTATION AND DEFINITIONS, p. 4

2.1—Notation, p. 4

2.2—Definitions, p. 4

ACI Committee Reports and Guides are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI PRC-237.2-21 was adopted and published July 2021.

Copyright © 2021, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 3—THIXOTROPY AND FORM PRESSURE, p. 4

- 3.1—Thixotropy, p. 4
- 3.2—Thixotropy test methods, p. 5
- 3.3—Influence of thixotropy on form pressure, p. 9

CHAPTER 4—EFFECT OF MIXTURE CHARACTERISTICS ON FORM PRESSURE, p. 11

- 4.1—Introduction, p. 11
- 4.2—Binder constituents and content, p. 11
- 4.3—Water content, p. 12
- 4.4—Aggregate characteristics, p. 12
- 4.5—Chemical admixtures, p. 13

CHAPTER 5—EFFECT OF CASTING PARAMETERS ON FORM PRESSURE, p. 14

- 5.1—Introduction, p. 14
- 5.2—SCC mixture temperature, p. 14
- 5.3—Casting rate, p. 14
- 5.4—Formwork characteristics, p. 15
- 5.5—Reinforcement percentage, p. 16

CHAPTER 6—PREDICTION MODELS FOR SCC FORM PRESSURE, p. 17

- 6.1—Introduction, p. 17
- 6.2—Model by Gardner et al. (2012), p. 17
- 6.3—Model by Khayat and Omran (2010b), p. 17
- 6.4—Model by Tejeda-Dominguez et al. (2005), p. 18
- 6.5—Model by Ovarlez and Roussel (2007), p. 19

CHAPTER 7—MEASUREMENT TECHNIQUES, p. 19

- 7.1—Strain-gauge-based pressure sensor setup, p. 19
- 7.2—Pressure reading graph example, p. 21
- 7.3—Precautions and maintenance when measuring form pressure, p. 21

CHAPTER 8—FIELD VALIDATION OF PREDICTION MODELS, p. 21

- 8.1—Stockholm, Sweden, 2012, p. 21
- 8.2—Toronto, Canada, 2014, p. 23
- 8.3—Validation of models, p. 26
- 8.4—Considerations for formwork design, p. 27

CHAPTER 9—SUMMARY, p. 27

CHAPTER 10—REFERENCES, p. 27

Authored references, p. 27

APPENDIX A—EXAMPLE CALCULATIONS, p. 29

- A1—Calculation of form pressure using model by Gardner et al. (2012), p. 30
- A2—Calculation of form pressure using model by Khayat and Omran (2010b), p. 30
- A3—Calculation of form pressure using model by Tejeda-Dominguez et al. (2005), p. 31
- A4—Calculation of form pressure using model by Ovarlez and Roussel (2007), p. 31

CHAPTER 1—INTRODUCTION

1.1—Introduction

Self-consolidating concrete (SCC) is highly flowable non-segregating concrete that can spread into place, fill the formwork, and encapsulate the reinforcement without any mechanical consolidation. SCC is designed to have a relatively low yield stress compared to conventional concrete to ensure high flowability without segregation. Yield stress corresponds to the critical shear stress value beyond which the material starts to flow. SCC can have slump flow values typically in the range of 22 to 30 in. (560 to 760 mm). Due to the high fluidity of SCC, formwork systems are often designed to sustain full hydrostatic pressure. Accurate estimation of form pressure for field application of SCC is necessary for the economical design of formwork and to ensure safety during and after casting. Field and laboratory investigations involving the measurement of lateral pressure exerted by SCC on formwork systems indicate that form pressure can be considerably lower than hydrostatic pressure (Assaad and Khayat 2005c; Assaad et al. 2003b; Billberg et al. 2014; Gardner et al. 2016). This is illustrated in Fig. 1.1 for SCC used for the rehabilitation of wall elements that measure 20 ft (6 m) in height, 23 ft (7 m) in length, and 7.5 in. (0.19 m) in width (Assaad 2004; Khayat et al. 2005b). The casting rate was approximately 21 ft/h (6.5 m/h). The pressure distribution envelopes exerted by a representative SCC mixture determined at the end of the placement and then after 1 and 3 hours are shown in Fig. 1.1 (left). The variations in the maximum lateral pressure with time for five different SCC mixtures that were proportioned with different thixotropic values are illustrated in Fig. 1.1 (right).

Form pressure is affected by structural buildup; structural buildup increases with rest time, hence reducing form pressure (Assaad et al. 2003b; Assaad and Khayat 2005c). The rate of structural buildup is dependent on the concrete mixture characteristics, including:

- (a) Binder constituent (Assaad et al. 2003b)
- (b) Type and dosage of chemical admixtures (Assaad et al. 2003b; Khayat and Assaad 2006)
- (c) Water-cementitious materials ratio (w/cm) (Khayat and Assaad 2006)
- (d) Maximum aggregate size and the total aggregate content (Assaad and Khayat 2005a)

For a given casting rate R , lower form pressure can be observed for concrete with a higher rate of structural buildup at rest (Assaad and Khayat 2007). The structural buildup of the concrete corresponds to an increase in shear strength when the material is left at rest due to flocculation—a physical effect that is reversible—as well as hydration of the cement-based materials, which is irreversible. At very early age, the flocculation component is dominant, and the structural buildup is reversible and can be broken down if the mixture is agitated. However, as hydration progresses with time, the structural buildup gradually becomes less reversible (Roussel et al. 2012). The placement of SCC mixtures with a high rate of structural buildup, at relatively low to moderate casting rates—for example, approximately 7 to