

AS 2862.1:2021
ISO 12743:2021



Copper, lead, zinc and nickel concentrates — Sampling

Part 1: Sampling procedures for determination of metal and moisture content



AS 2862.1:2021

This Australian Standard ® was prepared by MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 13 August 2021.

This Standard was published on 27 August 2021.

The following are represented on Committee MN-005:

- Australasian Institute of Mining and Metallurgy
- Australian X-ray Analytical Association
- CSIRO
- Engineers Australia
- International Copper Association Australia
- Minerals Council of Australia
- The Chamber of Minerals and Energy of Western Australia

This Standard was issued in draft form for comment as DR AS 2862.1:2021.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

ISBN 978 1 76113 472 2

Copper, lead, zinc and nickel concentrates — Sampling

Part 1: Sampling procedures for determination of metal and moisture content

Originated as AS 2862.1—1999.
Previous edition 2008.
Third edition 2021.

COPYRIGHT

© ISO 2021 — All rights reserved
© Standards Australia Limited 2021

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth).

Preface

This Standard was prepared by the Standards Australia Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates, to supersede AS 2862.1—2008.

The objective of this document is to set out the basic methods for sampling copper, lead, zinc and nickel concentrates from moving streams and stationary lots, including stopped-belt sampling, to provide samples for chemical analysis, physical testing and determination of moisture content, in accordance with the relevant International Standards. Where the concentrates are susceptible to significant oxidation or decomposition, a common sample that is sufficiently representative, i.e. unbiased and sufficiently precise, is used for moisture determination and chemical analysis to eliminate bias (see AS 2863). Any large agglomerates (>10 mm) present in the primary sample are crushed prior to further sample processing. Sampling of concentrates in slurry form is specifically excluded from this document.

Stopped-belt sampling is the reference method for collecting concentrate samples against which mechanical and manual-sampling procedures can be compared. Sampling from moving streams is the preferred method. Both falling-stream and cross-belt samplers are described.

Sampling from stationary lots is used only where sampling from moving streams is not possible. The procedures described in this document for sampling from stationary lots only minimize some of the systematic sampling errors.

This document is identical with, and has been reproduced from, ISO 12743:2021, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*.

As this document has been reproduced from an International Standard, a full point substitutes for a comma when referring to a decimal marker. Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface	ii
Foreword	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Sampling theory	4
4.1 General	4
4.2 Total variance	4
4.3 Sampling-stage method of estimating sampling and total variance	6
4.4 Simplified method of estimating sampling and total variance	8
4.5 Interleaved sample method of measuring total variance	10
5 Establishing a sampling scheme	12
6 Mass of increment	17
6.1 General	17
6.2 Mass of increment for falling-stream samplers	17
6.3 Mass of increment for cross-belt samplers	17
6.4 Mass of increment for manual sampling from stationary lots	17
6.4.1 Primary increments	17
6.4.2 Mass of secondary and subsequent increments	18
6.5 Mass of increment for stopped-belt reference sampling	18
7 Methods of sampling from concentrate streams	18
7.1 General	18
7.2 Mass-basis systematic sampling	18
7.2.1 General	18
7.2.2 Sampling interval	19
7.2.3 Sample cutter	19
7.2.4 Taking of primary increments	19
7.2.5 Constitution of subsamples and lot samples	19
7.2.6 Types of division	20
7.2.7 Division of increments	20
7.2.8 Division of subsamples	20
7.2.9 Division of lot samples	20
7.3 Time-basis systematic sampling	21
7.3.1 General	21
7.3.2 Sampling interval	21
7.3.3 Sample cutter	21
7.3.4 Taking of primary increments	22
7.3.5 Constitution of subsamples and lot samples	22
7.3.6 Types of division	22
7.3.7 Division of increments and subsamples	22
7.3.8 Division of lot samples	22
7.4 Stratified random sampling	22
7.4.1 Fixed mass intervals	22
7.4.2 Fixed time intervals	23
8 Mechanical sampling of concentrate streams	23
8.1 General	23
8.2 Design of the sampling system	23
8.2.1 Safety of operators	23
8.2.2 Location of sample cutters	23
8.2.3 Provision for interleaved sampling	24
8.2.4 Provision for stratified random sampling	24

8.2.5	Checking precision and bias.....	24
8.2.6	Avoiding bias.....	24
8.2.7	Minimizing bias.....	24
8.2.8	Configuration of the sampling system.....	24
8.3	Sample cutters.....	25
8.3.1	General.....	25
8.3.2	Design criteria.....	25
8.3.3	Cutter speed.....	26
8.4	Mass of increments.....	27
8.5	Number of increments.....	27
8.6	Sampling interval.....	27
8.7	Routine checking.....	27
9	Manual sampling of concentrate streams.....	28
9.1	General.....	28
9.2	Choosing the sampling location.....	28
9.3	Sampling implements.....	29
9.4	Mass of increments.....	29
9.5	Number of increments.....	29
9.6	Sampling interval.....	29
9.7	Sampling procedures.....	29
9.7.1	General.....	29
9.7.2	Full stream cut from a falling stream.....	29
9.7.3	Partial stream cuts from a falling stream.....	29
9.7.4	Sampling from moving conveyor belts.....	30
10	Stopped-belt reference sampling.....	30
11	Sampling from grabs.....	31
11.1	General.....	31
11.2	Mass of primary increments.....	31
11.3	Number of primary increments.....	31
11.4	Method of sampling.....	32
11.5	Constitution of subsamples and lot samples.....	32
12	Sampling from trucks, railway wagons and sampling hoppers.....	32
12.1	General.....	32
12.2	Mass of primary increments.....	32
12.3	Number of primary increments.....	32
12.4	Method of sampling.....	33
12.5	Constitution of subsamples and lot samples.....	33
13	Sampling of concentrate in bags or drums.....	36
13.1	General.....	36
13.2	Mass of primary increments.....	36
13.3	Number of primary increments.....	36
13.4	Method of sampling.....	37
13.4.1	General.....	37
13.4.2	Sampling during filling or emptying.....	37
13.4.3	Spear sampling.....	37
13.5	Constitution of subsamples and lot samples.....	37
14	Sampling of stockpiles.....	38
15	Methods of comminution, mixing and division.....	38
15.1	General.....	38
15.2	Comminution.....	38
15.2.1	General.....	38
15.2.2	Mills.....	38
15.3	Mixing.....	39
15.3.1	General.....	39
15.3.2	Methods of mixing.....	39

15.4	Division	40
15.4.1	Chemical analysis samples	40
15.4.2	Moisture samples	41
15.4.3	Number of increments for division	41
15.4.4	Minimum mass of divided sample	41
15.4.5	Rotary sample division	42
15.4.6	Cutter-type division	43
15.4.7	Manual increment division	43
15.4.8	Spear division	43
15.4.9	Fractional shovelling	44
15.4.10	Ribbon division	45
15.4.11	Riffle division	47
16	Sample requirements	49
16.1	Moisture samples	49
16.1.1	Mass of test portion	49
16.1.2	Processing of samples	49
16.2	Chemical analysis samples	49
16.3	Physical test samples	50
17	Packing and marking of samples	50
Annex A	(normative) Sampling stage method of estimating sampling and total variance	51
Annex B	(informative) Estimation of total variance — Barge unloading using a grab	58
Annex C	(informative) Mechanical sample cutters	62
Annex D	(informative) Checklist for mechanical sampling systems	67
Annex E	(normative) Manual sampling devices	71
Annex F	(informative) Apparatus for manual sampling of concentrates from stopped belts	73
Annex G	(informative) Sampling of stockpiles	74
Annex H	(normative) Increment division scoops for conducting manual increment division	76
	Bibliography	77

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 183, *Copper, lead, zinc and nickel ores and concentrates*.

This fourth edition cancels and replaces the third edition (ISO 12743:2018), which has been technically revised. The main changes to the previous edition are as follows:

- The minimum cutting aperture for cross-belt cutters in [8.3.2.3](#) i) has been reduced to 30 mm.
- A NOTE has been added to [15.4.10](#) indicating that ribbons with smaller dimensions can be formed depending on the mass of sample to be divided, and that the ribbon division method is particularly suitable for dividing chemical analysis samples.
- The requirements for preparation of chemical analysis samples in [16.2](#) have been expanded.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Australian Standard®

Copper, lead, zinc and nickel concentrates — Sampling

Part 1: Sampling procedures for determination of metal and moisture content

WARNING — This document can involve hazardous materials, operations and equipment. It is the responsibility of the user of this document to establish appropriate health and safety practices and to ensure compliance with any other restrictions.

1 Scope

This document sets out the basic methods for sampling copper, lead, zinc and nickel concentrates from moving streams and stationary lots, including stopped-belt sampling, to provide samples for chemical analysis, physical testing and determination of moisture content, in accordance with the relevant International Standards. Where the concentrates are susceptible to significant oxidation or decomposition, a common sample that is sufficiently representative, i.e. unbiased and sufficiently precise, is used for moisture determination and chemical analysis to eliminate bias (see ISO 10251). Any large agglomerates (>10 mm) present in the primary sample are crushed prior to further sample processing. Sampling of concentrates in slurry form is specifically excluded from this document.

Stopped-belt sampling is the reference method for collecting concentrate samples against which mechanical and manual-sampling procedures can be compared. Sampling from moving streams is the preferred method. Both falling-stream and cross-belt samplers are described.

Sampling from stationary lots is used only where sampling from moving streams is not possible. The procedures described in this document for sampling from stationary lots only minimize some of the systematic sampling errors.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10251, *Copper, lead, zinc and nickel concentrates — Determination of mass loss of bulk material on drying*

ISO 12744, *Copper, lead, zinc and nickel concentrates — Experimental methods for checking the precision of sampling*

ISO 13292, *Copper, lead, zinc and nickel concentrates — Experimental methods for checking the bias of sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

representative sample

quantity of concentrate representing a larger mass of concentrate with both *precision* (3.29) and *bias* (3.28) within acceptable limits