

An ACI Standard
An ANSI Standard

Post-Installed Mechanical Anchors in Concrete— Qualification Requirements and Commentary

Reported by ACI Committee 355

ACI CODE-355.2-22



American Concrete Institute
Always advancing



Post-Installed Mechanical Anchors in Concrete—Qualification Requirements and Commentary

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint, and may be obtained by contacting ACI.

ACI codes, specifications, and practices are made available in the ACI Collection of Concrete Codes, Specifications, and Practices. The online subscription to the ACI Collection is always updated, and includes current and historical versions of ACI's codes and specifications (in both inch-pound and SI units) plus new titles as they are published. The ACI Collection is also available as an eight-volume set of books and a USB drive.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Post-Installed Mechanical Anchors in Concrete— Qualification Requirements and Commentary

An ACI Standard

Reported by ACI Committee 355

Robert R. McGlohn, Chair

Anthony J. Lamanna, Vice Chair

Neal S. Anderson
Jacques A. Bertrand
T. J. Bland
Peter J. Carrato
Rachel Chicchi
Jay Dorst

Rolf Eligehausen
Werner A. F. Fuchs
Brian C. Gerber
Andra Hoermann-Gast
Amy S. Kolczak
Thomas A. Kolden

Nam-Ho Lee
Giovanni Muciaccia
Daniel T. Mullins
John E. Pearson
Marlou B. Rodriguez
Milton Rodriguez

Peter Christian Schillinger
John F. Silva
Howard Silverman
Jian Zhao

Consulting Members

Robert W. Cannon
Ronald A. Cook
Branko Galunic

Herman L. Graves
Neil M. Hawkins
Paul R. Hollenbach

Donald F. Meinheit
Conrad Paulson
Dan R. Stoppenhagen

J. Bret Turley

ACI CODE-355.2 prescribes testing programs and evaluation requirements for post-installed mechanical anchors intended for use in structural applications addressed by ACI 318 and subjected to static or seismic loads in tension, shear, or combined tension and shear. Criteria are prescribed for determining whether anchors are acceptable for use in uncracked concrete only, or in cracked as well as uncracked concrete. Performance categories for anchors are established, as are the criteria for assigning anchors to each

category. The anchor performance categories are used by ACI 318 to assign capacity reduction factors and other design parameters.

Keywords: anchors; cracked concrete; expansion anchors; fasteners; mechanical anchors; post-installed anchors; screw anchors; undercut anchors.

This Code was developed by an ANSI-approved consensus process.

ACI CODE-355.2-22 supersedes ACI 355.2R-19 and was adopted and published in September 2022.

Copyright © 2022, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CONTENTS

CHAPTER 1—GENERAL, p. 5

- 1.1—Scope , p. 5
- 1.2—General , p. 5
- 1.3—Purpose , p. 5
- 1.4—Applicability , p. 5
- 1.5—Interpretation , p. 6

CHAPTER 2—NOTATION AND DEFINITIONS, p. 7

- 2.1—Notation, p. 7
- 2.2—Definitions, p. 12

CHAPTER 3—REFERENCED STANDARDS, p. 14

CHAPTER 4—SIGNIFICANCE AND USE, p. 15

CHAPTER 5—GENERAL REQUIREMENTS, p. 19

- 5.1—Testing sequence, p. 19
- 5.2—Test samples, p. 29
- 5.3—Testing by independent testing and evaluation agency and by manufacturer, p. 29
- 5.4—Changes to product, p. 30

CHAPTER 6—REQUIREMENTS FOR TEST SPECIMENS, INSTALLING ANCHORS, AND CONDUCTING TESTS, p. 32

- 6.1—Concrete for test members, p. 32
- 6.2—Anchor installation, p. 32
- 6.3—Test methods, p. 41
- 6.4—Tests in cracked concrete, p. 41
- 6.5—General requirements for anchor behavior, p. 41

CHAPTER 7—REQUIREMENTS FOR ANCHOR IDENTIFICATION, p. 46

- 7.1—Determination of critical characteristics of anchors, p. 46
- 7.2—Specification of critical characteristics of anchors, p. 46
- 7.3—Verification of conformance to drawings and specifications, p. 46

CHAPTER 8—REFERENCE TESTS, p. 49

- 8.1—Purpose, p. 49
- 8.2—Reference tension tests for single anchors without spacing and edge effects (Table 5.1a, Tests 1 through 3, or Table 5.1b, Tests 1 through 5), p. 49
- 8.3—Required calculations using results of reference tests, p. 50

CHAPTER 9—RELIABILITY TESTS, p. 52

- 9.1—Purpose, p. 52
- 9.2—Reliability tests using reduced installation effort (Table 5.1a, Test 4, and Table 5.1b, Test 6), p. 52
- 9.3—Reliability in low-strength concrete with large drill bit (Table 5.1a, Test 5, and Table 5.1b, Test 7), p. 53
- 9.4—Reliability in high-strength concrete with small drill bit (Table 5.1a, Test 6, and Table 5.1b, Test 8), p. 53

9.5—Reliability under repeated load (Table 5.1a, Test 7, and Table 5.1b, Test 10 for screw anchors), p. 53

9.6—Reliability in cracked concrete where crack width is cycled (Table 5.1b, Test 9), p. 55

9.7—Reliability of screw anchors for brittle failure (Table 5.1a, Test 8, and Table 5.1b, Test 11), p. 57

9.8—Reliability tests of screw anchors to setting method (Table 5.1a, Tests 9, 10, and 11, or Table 5.1b, Tests 12, 13, and 14), p. 64

CHAPTER 10—SERVICE-CONDITION TESTS, p. 67

- 10.1—Purpose, p. 67
- 10.2—Service-condition tension test with single anchor and with two edges (corner) (Table 5.1a, Test 12, and Table 5.1b, Test 15), p. 67
- 10.3—Service-condition test at minimum edge distance and minimum spacing (Table 5.1a, Test 13, and Table 5.1b, Test 16), p. 68
- 10.4—Service-condition shear test for single anchors without spacing and edge effects (Table 5.1a, Test 14, and Table 5.1b, Test 17), p. 71
- 10.5—Service-condition, simulated seismic tension tests (Table 10.1b, Test 18), p. 72
- 10.6—Service condition, simulated seismic shear tests (Table 5.1b, Test 19), p. 74
- 10.7—Torque tests (Table 5.1a, Test 15, and Table 5.1b, Test 20) - Optional, p. 77

CHAPTER 11—ESTABLISHING ANCHOR CATEGORIES, p. 80

CHAPTER 12—PRESENTING ANCHOR DATA, p. 81

- 12.1—Data analysis, p. 81
- 12.2—Format of data sheet, p. 81
- 12.3—General requirements, p. 81
- 12.4—Contents of evaluation report, p. 81

CHAPTER 13—REQUIREMENTS FOR INDEPENDENT TESTING AND EVALUATION AGENCY, p. 84

CHAPTER 14—COMMENTARY REFERENCES, p. 85

- Authored documents, p. 85

APPENDIX A1—REQUIREMENTS FOR NORMALIZATION OF RESULTS, p. 86

- A1.1—Normalization of capacities to take account of concrete and steel strengths, p. 86
- A1.2—Concrete breakout or splitting failure, p. 86
- A1.3—Pullout and pull-through failure, p. 86
- A1.4—Steel failure, p. 86

APPENDIX A2—REQUIREMENTS FOR ESTABLISHING CHARACTERISTIC CAPACITIES, p. 87

- A2.1—Scope, p. 87
- A2.2—Procedure, p. 87

APPENDIX A3—REQUIREMENTS FOR TEST MEMBERS, p. 88


- A3.1—Tests in uncracked concrete, p. 88
- A3.2—Tests in cracked concrete, p. 88
- A3.3—Casting and curing of test members, p. 89

APPENDIX B—EXAMPLE OF EVALUATION OF AN EXPANSION ANCHOR FOR USE IN UNCRACKED CONCRETE, p. 90

- B1—Anchor specifications, p. 90
- B2—Test results, p. 91
- B3—Evaluation, p. 92
- B3.1—General, p. 92

- B3.2—Reference tests in uncracked low-strength concrete, p. 92
- B3.3—Reference tests in uncracked high-strength concrete, p. 93
- B3.4—Reliability tests, reduced installation effort, p. 93
- B3.5—Reliability tests, large hole diameter, p. 94
- B3.6—Reliability tests, small hole diameter, p. 94
- B3.7—Reliability tests, repeated load, p. 94
- B3.8—Service-condition tests, corner test, p. 95
- B3.9—Service-condition tests, minimum edge distance, and spacing, p. 96
- B3.10—Service-condition tests, shear tests, p. 96
- B4—Establishing anchor category, p. 97
- B5—Report of anchor data, p. 98





PAGE LEFT INTENTIONALLY BLANK.

CODE

CHAPTER 1—GENERAL

1.1—Scope

ACI CODE-355.2 prescribes testing and evaluation requirements for post-installed mechanical anchors intended for use in concrete designed under the provisions of ACI 318. Criteria are prescribed to determine whether anchors are acceptable for use in uncracked concrete only, or in cracked as well as uncracked concrete. Criteria are prescribed to determine the performance category for each anchor. The anchor performance categories are used by ACI 318 to assign capacity reduction factors and other design parameters.

1.2—General

ACI CODE-355.2 describes the tests required to qualify a post-installed mechanical anchor or anchor system for use under the provisions of ACI 318.

1.3—Purpose

ACI CODE-355.2 applies to post-installed mechanical anchors (torque-controlled expansion anchors, displacement-controlled expansion anchors, undercut anchors, and screw anchors) placed into predrilled holes and anchored within the concrete by mechanical means.

1.4—Applicability

ACI CODE-355.2 applies to expansion, undercut, and screw anchors with a minimum effective embedment depth of 1-1/2 in. and with a nominal diameter of 1/4 in. or larger. Screw anchors are limited to a maximum effective embedment of $10d_a$.

COMMENTARY

CHAPTER R1—GENERAL

R1.1—Scope

ACI CODE-355.2 prescribes the testing programs required to qualify post-installed mechanical anchors for use with the design method of ACI 318-19 Chapter 17, where it is assumed that anchors have been tested either for use in uncracked concrete or for use in cracked and uncracked concrete. This testing is performed in concrete specimens controlled by the testing laboratory as a means of simulating concrete, both cracked and uncracked, that might occur in actual structures. Post-installed mechanical anchors exhibit a range of working principles, proprietary designs, and performance characteristics. ACI 318-19 Chapter 17 addresses this situation by basing capacity reduction factors for anchors on anchor performance categories. ACI CODE-355.2 is intended to develop the data required by ACI 318-19 Chapter 17 to confirm an anchor's reliability and place it in the appropriate anchor category.

ASTM E488/E488M includes some details for cracked concrete test members similar to those in this document. ASTM E488/E488M also has detailed test procedures for testing in cracked concrete.

R1.4—Applicability

The design method deemed to satisfy the anchor design requirements of ACI 318-19 Chapter 17 is based on an analysis of a database of anchors with a maximum diameter of 2 in. and an embedment depth not greater than 25 in. ACI CODE-355.2 can be used for anchors with those maximum dimensions. While ACI CODE-355.2 gives no limitations on maximum anchor diameter or embedment depth, for anchors beyond these dimensions, the testing authority should decide if the tests described herein are applicable or if alternative tests and analyses are more appropriate. The minimum diameter of 1/4 in. is based on practical considerations regarding the limit of structural anchor applications. The current database of screw anchors contains products with an embedment up to $h_{ef} = 10d_a$ due to practical limits of manufacturing and ability to install at deep embedments. This database has been shown to satisfy the design requirements of ACI 318-19 Chapter 17.