

Standard Practice for Sandwich Plate Repair of Steel Structures

©2022 Association for Materials Protection and Performance (AMPP). All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means (electronic, mechanical, photocopying, recording, or otherwise) without the prior written permission of AMPP.

Standard Practice for Sandwich Plate Repair of Steel Structures

This AMPP standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this AMPP standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. AMPP assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official AMPP interpretations issued by AMPP in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this AMPP standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This AMPP standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this AMPP standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities, if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: AMPP standards are subject to periodic review and may be revised or withdrawn at any time in accordance with AMPP technical committee procedures. AMPP requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of AMPP standards may receive current information on all standards and other AMPP/NACE/SSPC publications by contacting AMPP Customer Support, 15835 Park Ten Place, Houston, Texas 77084-5145 (Tel: +1 281-228-6200, email: customersupport@ampp.org).

Document History

2022-06-29: Approved by AMPP Standards Committee (SC) 19, Maritime

AMPP values your input. To provide feedback on this standard, please contact: standards@ampp.org

AMPP SP21507-2022

©2022 Association for Materials Protection and Performance (AMPP). All rights reserved.

Standard Practice for Sandwich Plate Repair of Steel Structures

Foreword, Scope, Rationale	4
References	5
Section 1 General	5
Section 2 Definitions	6
Section 3 Repair Decision.....	7
Section 4 Documents for Approval of Sandwich Plate Repairs.....	9
Section 5 Damage Assessment	9
Section 6 Repair Design	10
6.1 Sandwich Plate Elements	10
6.2 Failure Modes of Sandwich Plate Repairs	11
6.3 Properties under Fire	12
6.4 Repair Classes.....	12
6.5 Safety Factors.....	12
6.6 Repair Design Basis and Considerations.....	12
6.7 Repair Design Calculations.....	13
6.8 Design Report	15
Section 7 Personnel Qualification	15
Section 8 Materials.....	16
8.1 Faceplates and Perimeter Bars.....	16
8.2 Core Materials.....	16
8.3 Bond Strength	17
8.4 Prefabricated Components	17
Section 9 Installation Procedure and Quality Assurance	18
9.1 General	18
9.2 Typical Procedure of Sandwich Plate Repair Installation.....	18
9.3 Corrosion Protection of the Exposed Surface of Steel Plates.....	20
Section 10 In-Service Inspection, Maintenance and Monitoring	20
10.1 General	20
10.2 Inspection.....	21
10.3 Inspection Frequency.....	21
Other Referenced Documents.....	21
Figures	
Figure 1 Schematic Representation of a Damaged Structure Repaired Using Sandwich Plate	6
Figure 2 Decision-making Process on Sandwich Plate Repair	8
Figure 3 Development Length of the Sandwich Plate Repair.....	14
Tables	
Table 1 Recommended Sandwich Plate Elements and Their Functions	11
Table 2 Equivalent Repair Classes from AMPP-NACE, ABS, and DNV	12
Table 3 Recommended Minimum Thicknesses of Faceplate and Elastomer Core for Handling and Curing	15
Table 4 Typical Elastomer Core Material Properties and Test Standards.....	17

Foreword

Oil and gas industry onshore and offshore drilling, production, storage, and transportation generally experience very corrosive environments. Even though corrosion prevention systems, such as cathodic protection, protective coatings, and liquid/vapor phase inhibitors are usually used for corrosion protection, severe corrosion of the structures is still unavoidable without effective corrosion protection and appropriate corrosion management. The repair of degraded structural members having substantial corrosion damage is critical for maintaining structural integrity for safe and continuous operations.

The “crop-and-replace” repair method (by cutting and welding) is normally used in the oil and gas industry. However, such repairs are considered as hot-work, which creates a considerable safety concern for continuous oil and gas operations (drilling, production, and storage). When hot work repair of a tank is planned, safety regulations require the tank to be repaired, as well as adjacent tanks, to be in a “gas-free” condition. Due to significant impact on the continuous operation of the units, preparing for these repairs is very costly.

Safety and cost-effective solutions are the driving forces for consideration of non-hot-work repair methods. Thus, sandwich plate repairs without cutting and welding, using a new steel plate bonded to the existing steel structure, are generally preferred. With the increased use of sandwich plate repairs, more performance data and better repair practices make it possible to develop better industry standards. This repair method is preferable for applications on site-specific onshore and offshore structures which require immediate repair of severe corrosion and/or mechanical damage. It can also be applicable to other structures, vessels, or tanks, where permitted.

This standard practice formalizes a methodology of steel sandwich plate repair technology. This methodology uses a new steel plate or prefabricated structural component laid on top of the existing steel plate to be repaired. An elastomer core is used to bond the new plate/component and the existing steel plate to form a steel sandwich plate structure, thereby repairing the existing steel substrate without it being cut and replaced. This method is intended to restore the strength of the damaged structural members, or to reinforce existing structures.

Several classification societies, such as the American Bureau of Shipping (ABS),⁽¹⁾ Lloyds Register (LR)⁽²⁾, Det Norske Veritas (DNV)⁽³⁾, and the China Classification Society (CCS)⁽⁴⁾ have set out their own rules, guidelines, or provisions for sandwich plate construction and/or repairs for steel structures, which serve for classifications for specific marine and offshore vessels. This standard practice covers only steel sandwich plate repairs for more general applications, including use on non-classed structures, civil structures, onshore storage tanks, as well as in refineries. This standard practice may serve as a unified standard of steel sandwich plate repairs for all industry applications, where permitted.

Scope

This standard covers the methodology and guidelines for accomplishing structural repairs by using steel sandwich plate technology. It is mainly applied to steel structure repairs for damages from corrosion deterioration and mechanical damages. It can also be applied to repairs of aluminum structures.

This standard includes assessment, design, qualification, installation, and inspection of the repairs using steel sandwich plate technology.

This standard does not cover use of fiber reinforced plastics (FRP). The repair materials used include steel plates as face plates and elastomer as a core material.

Rationale

The steel sandwich plate repair technology provides an alternative to traditional hot work renewal repairs, especially where hot work is considered risky to the unit’s operation. The steel sandwich plate repair technology can be used to reinstate the integrity of the structure by utilizing a new steel plate bonded to the degraded existing steel structure using a core elastomer material. [Figure 1](#) provides a schematic representation of a damaged structure repaired using sandwich plate. This sandwich plate repair method can also be used for modification or upgrading of the existing structures for reinforcement.

⁽¹⁾ American Bureau of Shipping (ABS), 1701 City Plaza Drive, Spring, TX 77389, <https://www2.eagle.org/>

⁽²⁾ Lloyds Register (LR), 71 Fenchurch Street, London, EC3M 4BS, UK, <https://www.lr.org>

⁽³⁾ Det Norske Veritas (DNV), Thormøhlensgt. 49A, 5006 Bergen, Norway, <https://www.dnv.com>

⁽⁴⁾ China Classification Society (CCS), CCS Mansion, 9 Dongzhimen Nan Da Jie, Beijing, PRC, <https://www.ccs.org.cn/ccswzen/>