

AASHTO/AWS D1.5M/D1.5:2002
An American National Standard

Bridge Welding Code

A Joint Publication of
American Association of State Highway
and Transportation Officials



American Welding Society

Key Words—Bridge fabrication requirements, construction steels, fracture control plan, steel bridges, stud welding, weld connection design, welding inspection

**AASHTO/AWS D1.5M/D1.5:2002
An American National Standard**

**Approved by
American National Standards Institute
November 30, 2001**

Bridge Welding Code

Supersedes ANSI/AASHTO/AWS D1.5-96

Prepared by
AWS D1 Committee on Structural Welding
AASHTO Highway Subcommittee on Bridges and Structures

Under the Direction of
AWS Technical Activities Committee
AASHTO Executive Committee

Approved by
AWS Board of Directors
AASHTO Board of Directors/Policy Committee

Abstract

This code covers the welding requirements for AASHTO welded highway bridges made from carbon and low-alloy constructional steels. This 2002 edition contains dimensions in metric SI Units and U.S. Customary Units. Sections 1 through 7 constitute a body of rules for the regulation of welding in steel construction. Section 9 of the previous edition has had its provisions distributed throughout the 2002 edition. Sections 8, 10, and 11 do not contain provisions, as their analogue D1.1 sections are not applicable to the D1.5 Code. Section 12 contains the requirements for fabricating fracture critical members.

A Joint Publication of:

**American Association of State
Highway and Transportation Officials**
444 N. Capitol Street, N.W., Suite 225
Washington, DC 20001

American Welding Society
550 N.W. LeJeune Road
Miami, FL 33126

Statement on Use of AWS American National Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute. When AWS standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

International Standard Book Number: 0-87171-653-4

American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126

© 2002 by American Welding Society. All rights reserved

Printed in the United States of America

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guaranty or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is not undertaking to render professional or other services for or on behalf of any person or entity. Nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

This standard may be superseded by the issuance of new editions. Users should ensure that they have the latest edition.

Publication of this standard does not authorize infringement of any patent. AWS disclaims liability for the infringement of any patent resulting from the use or reliance on this standard.

Finally, AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may be obtained by sending a request, in writing, to the Managing Director Technical Services, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126 (see Annex D). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. However, such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time between the AWS D1 Committee on Structural Welding and the AASHTO Technical Committee on Welding. It must be reviewed every five years and if not revised, it must be either reapproved or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the joint AASHTO/AWS subcommittee and the AWS D1 Committee on Structural Welding and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D1 Committee on Structural Welding to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

Photocopy Rights

Authorization to photocopy items for internal, personal, or educational classroom use only, or the internal, personal, or educational classroom use only of specific clients, is granted by the American Welding Society (AWS) provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: 978-750-8400; online: <http://www.copyright.com>.

Personnel

AWS D1 Committee on Structural Welding

<i>D. L. McQuaid, Chair</i>	D. L. McQuaid and Associates
<i>D. D. Rager, Vice Chair</i>	Rager Consulting
<i>D. K. Miller, Vice Chair</i>	The Lincoln Electric Co.
<i>A. W. Sindel, Vice Chair</i>	Sindel and Associates
<i>H. H. Campbell III, Secretary</i>	American Welding Society
<i>W. G. Alexander</i>	Consultant
<i>N. B. Altebrando</i>	Hardesty and Hanover
<i>A. Anderson</i>	Alcotec Wire Co.
<i>F. G. Armao</i>	The Lincoln Electric Co.
<i>R. E. Avery</i>	Nickel Development Institute
<i>D. K. Baird</i>	Argonne National Laboratory
<i>E. M. Beck</i>	Law Engineering and Environmental Services, Inc.
<i>*F. R. Beckmann</i>	Consultant
<i>R. M. Bent</i>	Bent Engineering
<i>E. L. Bickford</i>	J. Ray McDermott, Inc.
<i>R. D. Block</i>	Diamond Power International, Inc.
<i>*O. W. Blodgett</i>	The Lincoln Electric Co.
<i>R. Bonneau</i>	Canadian Welding Bureau
<i>F. C. Breismeister</i>	Bechtel Corp.
<i>C. R. Briden</i>	Consultant
<i>B. M. Butler</i>	Walt Disney World Co.
<i>*S. Camo</i>	Weidlinger Associates Inc.
<i>J. J. Cecilio</i>	Consultant
<i>H. A. Chambers</i>	TRW Nelson Stud Welding Division
<i>C. B. Champney</i>	TRW Nelson Stud Welding Division
<i>L. E. Collins</i>	Team Industries, Inc.
<i>S. Cook</i>	Michigan Department of Transportation
<i>R. B. Corbit</i>	Amer Gen
<i>S. L. Cotham</i>	Quality Engineering and Inspection
<i>M. V. Davis</i>	Consultant
<i>D. A. DelSignore</i>	Sr. Metallurgical and Welding Engineer
<i>R. A. Dennis</i>	Consultant
<i>P. B. Dickerson</i>	Consultant
<i>W. Doukas</i>	Maine Department of Transportation
<i>*J. D. Duncan</i>	Bechtel Corp.
<i>J. L. Ellerman</i>	Wyoming Department of Transportation
<i>*G. L. Fox</i>	Consultant
<i>*A. R. Fronduti</i>	Rex Fronduti & Associates
<i>R. D. Fry</i>	Georgia Department of Transportation
<i>R. S. Funderburk</i>	The Lincoln Electric Co.
<i>J. A. Grewe</i>	Omaha Public Power District
<i>M. A. Grieco</i>	Massachusetts Highway Department
<i>D. P. Gustafson</i>	Concrete Reinforcing Steel Institute
<i>R. Hamburger</i>	EQE International Inc.

*Advisor

AWS D1 Committee on Structural Welding (Continued)

<i>M. J. Harker</i>	Idaho National Engineering and Environmental Laboratories
<i>E. Hartwell</i>	Consultant
<i>C. W. Hayes</i>	The Lincoln Electric Co.
<i>C. R. Hess</i>	High Steel Structures, Inc.
<i>G. J. Hill</i>	G. J. Hill and Associates, Inc.
<i>M. L. Hoitomt</i>	Consultant
<i>E. R. Holby</i>	IFR Engineering
<i>C. W. Holmes</i>	Modjeski and Masters, Inc.
<i>W. Jaxa-Rozen</i>	Bombardier Transportation
<i>M. J. Jordan</i>	Bergen Southwest Steel
<i>A. J. Julicher</i>	A. J. Julicher and Associates
<i>S. Kern</i>	Tru-Weld Division TFP Corp.
<i>J. H. Kiefer</i>	Conoco, Inc.
<i>J. R. Kissell</i>	The TGB Partnership
<i>L. A. Kloiber</i>	LeJeune Steel Co.
<i>S. W. Kopp</i>	High Steel Structures
<i>J. E. Koski</i>	Stud Welding Products, Inc.
<i>*R. M. Kotan</i>	Omaha Public Power District
<i>D. J. Kotecki</i>	The Lincoln Electric Co.
<i>V. Kuruvilla</i>	Havens Steel Co.
<i>K. Landwehr</i>	Schuff Steel Co.
<i>D. R. Lawrence II</i>	Butler Manufacturing
<i>D. L. Long</i>	PDM Strocal, Inc.
<i>D. R. Luciani</i>	Canadian Welding Bureau
<i>H. W. Ludewig</i>	Caterpillar, Inc.
<i>*S. Mahin</i>	Earthquake Engineering Research Center
<i>J. Malley</i>	Degenkolb Engineers
<i>P. W. Marshall</i>	MHP Systems Engineering
<i>D. M. Marudas</i>	Morrison Knudsen Corp.
<i>M. J. Mayes</i>	Mayes Testing Engineers, Inc.
<i>J. W. McGrew</i>	Babcock & Wilcox
<i>R. D. Medlock</i>	Texas Department of Transportation
<i>J. K. Merrill</i>	Law Engineering and Environmental Services, Inc.
<i>J. K. Mieske</i>	PDM Bridge
<i>W. A. Milek, Jr.</i>	Consultant
<i>R. W. Miller</i>	State of Alaska Department of Transportation
<i>R. C. Minor</i>	Hapco Aluminum Poles
<i>J. L. Munnerylyn</i>	Consultant
<i>J. E. Myers</i>	SMI Owen Steel Co., Inc.
<i>C. K. Nicholson</i>	Law Engineering and Environmental Services, Inc.
<i>T. Niemann</i>	Minnesota Department of Transportation
<i>J. C. Nordby</i>	Consumers Energy
<i>T. Omura</i>	Kawada Industries
<i>J. A. Packer</i>	University of Toronto, Canada
<i>F. J. Palmer</i>	Steel Tube Institute
<i>C. C. Pease</i>	C P Metallurgical
<i>*T. Pekoż</i>	Cornell University
<i>D. C. Phillips</i>	ITW-Hobart Brothers Co.
<i>R. Pietrowski</i>	Pietrowski and Associates
<i>C. W. Pinkham</i>	S. B. Barnes and Associates
<i>J. W. Post</i>	J. W. Post and Associates, Inc.

*Advisor

AWS D1 Committee on Structural Welding (Continued)

<i>D. Rees-Evans</i>	Nucor-Yamato Steel
<i>J. E. Roth</i>	James E. Roth, Inc.
* <i>W. W. Sanders, Jr.</i>	Iowa State University
<i>T. Schlafly</i>	American Institute of Steel Construction
<i>D. R. Scott</i>	Scott Associates
<i>L. Seum</i>	Sheedy Drayage Co.
<i>D. Shapira</i>	LGT Limited (Morrison-Knudsen)
<i>J. G. Shaw</i>	Mountain Enterprises, Inc.
<i>R. E. Shaw, Jr.</i>	Steel Structures Technology Center, Inc.
* <i>D. L. Sprow</i>	Consultant
<i>R. W. Stieve</i>	Greenman-Pederson, Inc.
<i>R. G. Stobaugh</i>	Carolina Steel Corp.
<i>P. J. Stolarski</i>	California Department of Transportation
<i>C. R. Stuart</i>	Shell Offshore, Inc.
<i>P. J. Sullivan</i>	Massachusetts Highway Department (Retired)
<i>W. A. Svekric</i>	Welding Consultants, Inc.
<i>G. R. Swank</i>	State of Alaska
<i>M. M. Tayarani</i>	Massachusetts Highway Department
<i>A. A. Taylor</i>	J. M. Consulting Group
* <i>S. J. Thomas</i>	VP Buildings Inc.
<i>W. Thornton</i>	Cives Corp.
<i>R. H. R. Tide</i>	Wiss, Janney, Elstner Associates
<i>C. Uang</i>	University of California—San Diego
<i>J. E. Uebele</i>	Waukesha County Technical College
<i>B. M. Urbany</i>	Professional Services Industries
<i>K. K. Verma</i>	Federal Highway Administration
<i>B. D. Wright</i>	Advantage Aviation Technologies
<i>O. Zollinger</i>	Copeland Corporation

AASHTO Technical Committee for Welding

<i>J. E. Sothen, Chair</i>	West Virginia Department of Transportation
<i>P. Liles, Vice Chair</i>	Georgia Highway Department
<i>A. K. Bardow</i>	Massachusetts Department of Transportation
<i>E. Davisson</i>	California Department of Transportation
<i>D. Fleming</i>	Minnesota Department of Transportation
<i>H. L. James</i>	Mississippi Department of Transportation
<i>S. Larson</i>	Iowa Department of Transportation

Joint AASHTO/AWS Bridge Welding Subcommittee

<i>M. A. Grieco, AASHTO Cochair</i>	Massachusetts Highway Department
<i>C. R. Hess, AWS Cochair</i>	High Steel Structures Inc.

AASHTO Representatives

<i>S. Cook</i>	Michigan Department of Transportation
<i>W. Doukas</i>	Maine Department of Transportation
<i>J. L. Ellerman</i>	Wyoming Department of Transportation
<i>R. D. Fry</i>	Georgia Department of Transportation
<i>E. Hartwell</i>	New York Department of Transportation
<i>R. Medlock</i>	Texas Department of Transportation
<i>T. Niemann</i>	Minnesota Department of Transportation
<i>P. J. Stolarski</i>	California Department of Transportation

*Advisor

AWS Representatives

<i>*W. G. Alexander</i>	Consultant
<i>*N. J. Altebrando</i>	Hardesty and Hanover
<i>*F. R. Beckmann</i>	Consultant
<i>*L. E. Collins</i>	Team Industries, Inc.
<i>*A. R. Fronduti</i>	Rex Fronduti and Associates
<i>*C. W. Holmes</i>	Modjeski and Masters Inc.
<i>*D. L. McQuaid</i>	D. L. McQuaid and Associates Inc.
<i>*J. K. Merrill</i>	Law Engineering and Environmental Services, Inc.
<i>J. K. Mieske</i>	PDM Bridge
<i>D. K. Miller</i>	The Lincoln Electric Co.
<i>J. E. Myers</i>	SMI Owen Steel Co.
<i>D. C. Phillips</i>	ITW Hobard Brothers Co.
<i>T. J. Schlafly</i>	American Institute of Steel Construction
<i>*R. W. Stieve</i>	Greenman-Pedersen, Inc.
<i>R. G. Stobaugh</i>	Carolina Steel Corp.
<i>M. M. Tayaran</i>	Massachusetts Turnpike Authority
<i>K. K. Verma</i>	Federal Highway Administration

*Advisor

Foreword

(This Foreword is not a part of AASHTO/AWS D1.5M/D1.5:2002, *Bridge Welding Code*, but is included for information purposes only.)

The preparation of this specification was undertaken in response to a need for a common welding specification for the fabrication of steel highway bridges by welding. The departments of highways and transportation in the 50 states, the District of Columbia, and Puerto Rico that make up the American Association of State Highway and Transportation Officials have routinely used the specifications of the American Welding Society Structural Welding Committee, with appropriate modifications, to produce contract documents suitable for the construction of bridges using Federal Highway funds. The proliferation of requirements by the 50 states, District of Columbia and Puerto Rico that make up AASHTO (American Association of State Highway and Transportation Officials) resulted in the recognition of the need for a single document that could produce greater economies in bridge fabrication, while at the same time addressing the issues of structural integrity and public safety.

The first AWS code for *Fusion Welding and Gas Cutting in Building Construction* was published in 1928. In 1934, a committee was appointed to prepare specifications for the design, construction, alteration, and repair of highway and railway bridges. The first bridge specification was published in 1936. Until 1963, there were separate AWS committees for bridges and buildings. These two committees joined in 1963 to form the Structural Welding Committee of the American Welding Society. The committee has since promulgated standards for the application of welding to the design and construction of structures.

The Federal Highway Administration of the United States Department of Transportation requires states using federal funds for the construction of welded highway bridges to conform to specified standards for design and construction. Conformance to the AWS *Specification for Welded Highway and Railway Bridges* was first specified in the third edition of the AASHTO *Standard Specifications for Highway Bridges* in 1941. In 1962, the Bureau of Public Roads, now the Federal Highway Administration (FHWA), required conformance to a Circular Memorandum, dated November 13, 1962, which transmitted additional provisions for welding A36 steel pending publication of an AWS specification which would contain certain essential provisions not then in the code. Another Circular Memorandum, dated February 11, 1965, specified requirements for CVN testing, and a further Circular Memorandum, dated August 19, 1966, modified provisions of the 1966 Edition of the AWS D2.0-66, *Specification for Welded Highway and Railway Bridges*. An FHWA notice, dated July 7, 1971, recommended that ultrasonic inspection not be used for final acceptance of welds made by electrogas or electroslog procedures because of concern that the acceptance levels of AWS D2.0-69, Appendix C, were not suitable to detect or reject piping porosity of major dimensions.

In 1974, AASHTO published the first edition of the *Standard Specification for Welding of Structural Steel Highway Bridges*. The Eleventh Edition of the AASHTO *Standard Specifications for Highway Bridges*, dated 1977, directed “Welding shall conform to the requirements of the AASHTO *Standard Specifications for Welding of Structural Steel Highway Bridges* 1974 and subsequent interim specifications...” AASHTO published the Second and Third editions of the *Standard Specifications for Welding of Structural Steel Highway Bridges* in 1977 and 1981. All of the AASHTO specifications were required to be part of the Contract Documents as modifications or additions to the AWS *Structural Welding Code—Steel*. This was a cumbersome procedure.

In 1982, a subcommittee was formed jointly by AASHTO and AWS, with equal representation from both organizations, to seek accommodation between the separate and distinct requirements of bridge Owners and existing provisions of AWS D1.1. The *Bridge Welding Code* is the result of an agreement between AASHTO and AWS to produce a joint AASHTO/AWS *Structural Welding Code* for steel highway bridges that addresses essential AASHTO needs and makes AASHTO revisions mandatory.

The 1988 version of the *Bridge Welding Code* provided for the qualification of welding procedures by test to assure that weld had the strength, ductility, and toughness necessary for use in redundant structures. Nonredundant fracture critical bridge members were not provided for in the first edition of the code. While qualification of welding procedures is

required, a major effort has been made to specify the minimum number of tests and the simplest tests that give reasonable assurance of required mechanical properties. Efforts are made to discourage individual States from requiring duplication of weld testing unless that testing is specified in the bid documents. Special attention is directed to avoidance of unnecessary hardening of base metal HAZs and the avoidance of hydrogen and other items that can lead to weld or base-metal cracking.

Consequently, while the D1.5-88 document has a superficial resemblance to D1.1 in its general format, there are significant differences that users should be aware of, among them the lack of provisions relating to statically loaded structures, tubular construction or the modification of existing structures. Users are encouraged to develop their own requirements for these applications or use existing documents (e.g., D1.1) with the appropriate modifications.

The publication of AASHTO/AWS D1.5M/D1.5:2002 was justified by the need to monitor, revise, and update code provisions based on the needs of AASHTO member states and industry. The following is a list of the major revisions in 2002 edition:

- (1) Addition of U.S. Customary Units.
- (2) Addition of a Commentary for Sections 1, 2, 3, 5, 6, 7, and 12.
- (3) Deletion of Section 9 and incorporation of that information into other parts of the code. (See Annex F for a description of the changes.)
- (4) Revision to WPS Qualification Test Methods.
- (5) Addition of the use of edge blocks for RT.
- (6) Revision to Tables 4.1 and 4.2
- (7) Addition of undermatching specifications.

Changes in Code Requirements. Changes to the text of the 2002 edition are indicated by underlining. Changes to illustrations are highlighted by vertical lines in the margin.

Future revisions to this code will be made based on proposals from the Joint AASHTO/AWS Committee as well as those from document users. It should be re-emphasized here that the Joint Committee is the primary agency for receiving feedback from industry, and requires this input in order to produce a quality document. Other documents that do not receive the ANSI/AASHTO/AWS accreditation should not be relied on as substitutes for the Joint Committee's interpretation of D1.5 provisions.

While the D1.1 and D1.5 codes do share a number of common provisions, it should not be assumed that revisions to one document provision automatically revises its analogous provision in the other; therefore, users are encouraged to treat each code as an independent document.

This code was prepared by the AASHTO/AWS Bridge Welding Committee operating as a Subcommittee of the AWS Structural Welding Committee. The Committee is made up of representatives from the AWS Structural Welding Committee and the AASHTO Technical Committee for Welding. Accommodation was sought on all items where there was disagreement between AASHTO and AWS members. Specific issues considered essential by AASHTO were included in this code to eliminate the need for supplemental exclusions or additions by AASHTO.

The AASHTO/AWS D1.5, *Bridge Welding Code*, will be subject to regular review by the Bridge Welding Committee and will be republished or reaffirmed on an as-needed basis, at intervals not to exceed five years. All proposed changes to this code will be subject to approval by AWS and AASHTO prior to publication.

Comments or inquiries pertaining to this code are welcome (see Annex D). They should be addressed to the Secretary, Structural Welding Committee, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126, or to the Chairman of the AASHTO Technical Committee for Welding, American Association of State Highway and Transportation Officials, 444 N. Capitol Street, N.W., Suite No. 225, Washington, DC 20001.

Official interpretations of any of the technical requirements of this standard may be obtained by sending a request, in writing, to the Managing Director of Technical Services Division, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126. A formal reply will be issued after it has been reviewed by the appropriate personnel following established procedures.

Table of Contents

	Page No.
<i>Personnel</i>	iii
<i>Foreword</i>	v
<i>List of Tables</i>	xiii
<i>List of Figures</i>	xiv
<i>List of Forms</i>	xvi
1. General Provisions	1
1.1 Application	1
1.2 Base Metal	1
1.3 Welding Processes	2
1.4 <u>Fabricator Requirements</u>	2
1.5 Definitions	2
1.6 Welding Symbols	2
1.7 Safety Precautions	2
1.8 Standard Units of Measurement	3
1.9 Welding Procedure Specifications (WPSs)	3
1.10 Mechanical Testing	3
1.11 <u>Reference Documents</u>	3
2. Design of Welded Connections	5
<i>Part A—General Requirements</i>	5
2.1 Drawings	5
2.2 Basic Unit Stresses	5
2.3 Effective Weld Areas, Lengths, Throats, and Sizes	6
<i>Part B—Structural Details</i>	6
2.4 General	6
2.5 Welded Filler Plates	7
2.6 PJP Groove Welds	7
<i>Part C—Details of Welded Joints</i>	7
2.7 Joint Qualification	7
2.8 Details of Fillet Welds	7
2.9 Details of Plug and Slot Welds	9
2.10 Lap Joints	10
2.11 Corner and T-Joints	10
2.12 CJP Groove Welds	10
2.13 PJP Groove Welds	10
2.14 Prohibited Types of Joints and Welds	44
2.15 Combinations of Welds	44
2.16 Welds in Combination with Rivets and Bolts	44
2.17 Connection Details	45
3. Workmanship	49
3.1 General Requirements	49
3.2 Preparation of Base Metal	49
3.3 Assembly	53

3.4	Control of Distortion and Shrinkage.....	55
3.5	Dimensional Tolerances.....	55
3.6	Weld Profiles.....	57
3.7	Repairs.....	59
3.8	Peening.....	60
3.9	Caulking.....	60
3.10	Arc Strikes.....	60
3.11	Weld Cleaning.....	60
3.12	Weld Termination.....	60
3.13	Weld Backing.....	61
4.	Technique.....	63
	<i>Part A—General Requirements.....</i>	<i>63</i>
4.1	Filler Metal Requirements.....	63
4.2	Preheat and Interpass Temperature Requirements.....	66
4.3	Heat Input Control for Grade 690 (100) and 690W (100W).....	70
4.4	Stress Relief Heat Treatment.....	70
	<i>Part B—Shielded Metal Arc Welding (SMAW).....</i>	<i>71</i>
4.5	Electrodes for SMAW.....	71
4.6	Procedures for SMAW.....	72
	<i>Part C—Submerged Arc Welding (SAW).....</i>	<i>73</i>
4.7	General Requirements.....	73
4.8	Electrodes and Fluxes for SAW.....	73
4.9	Procedures for SAW with a Single Electrode.....	74
4.10	Procedures for SAW with Parallel Electrodes.....	75
4.11	Procedures for SAW with Multiple Electrodes.....	76
	<i>Part D—Gas Metal Arc Welding (GMAW) and Flux Cored Arc Welding (FCAW).....</i>	<i>76</i>
4.12	Electrodes.....	76
4.13	Shielding Gas.....	77
4.14	Procedures for GMAW and FCAW with a Single Electrode.....	77
	<i>Part E—Electroslag Welding (ESW) and Electrogas Welding (EGW).....</i>	<i>78</i>
4.15	Qualification of Process, WPSs, and Joint Details.....	78
4.16	Mechanical Properties.....	78
4.17	Condition of Electrodes and Guide Tubes.....	78
4.18	Shielding Gas.....	78
4.19	Condition of Flux.....	78
4.20	Procedures for ESW and EGW.....	78
	<i>Part F—Plug and Slot Welds.....</i>	<i>79</i>
4.21	Plug Welds.....	79
4.22	Slot Welds.....	79
4.23	Plug and Slot Welds.....	79
	<i>Part G—Control of Production Welding Variables.....</i>	<i>79</i>
4.24	Tests.....	79
4.25	Control of Variables.....	79
4.26	Calibration of Equipment.....	79
4.27	Current Control.....	79
5.	Qualification.....	81
5.0	Scope.....	81
	<i>Part A—Welding Procedure Specification (WPS) Qualification.....</i>	<i>81</i>
5.1	Approval.....	81

5.2	Qualification Responsibility	81
5.3	Duration	81
5.4	Base Metal	82
5.5	Welding Consumables	83
5.6	Test Plate Thickness.....	84
5.7	General Requirements for WPS Qualification.....	84
5.8	Position of Test Welds.....	88
5.9	Options for WPS Qualification or Prequalification	88
5.10	Fillet Weld WPS Qualification	88
5.11	Prequalified WPS.....	91
5.12	Heat Input WPS	92
5.13	Production Procedure WPS	93
5.14	ESW and EGW	95
5.15	Type of Tests and Purpose	95
5.16	Weld Specimens—Number, Type, and Preparation.....	95
5.17	Nondestructive Testing (NDT).....	100
5.18	Method of Testing Specimens.....	100
5.19	Test Results Required	106
5.20	Retests	106
	<i>Part B—Welder, Welding Operator, and Tack Welder Qualification</i>	<i>107</i>
5.21	General Requirements.....	107
5.22	Production Welding Positions Qualified.....	107
5.23	Qualification Tests Required.....	108
5.24	Limitations of Variables.....	115
5.25	Test Specimens: Number, Type, and Preparation	117
5.26	Method of Testing Specimens.....	117
5.27	Test Results Required	120
5.28	Retests	121
6.	Inspection.....	123
	<i>Part A—General Requirements</i>	<i>123</i>
6.1	General.....	123
6.2	Inspection of Materials	124
6.3	Inspection of WPS Qualification and Equipment.....	124
6.4	Inspection of Welder, Welding Operator, and Tack Welder Qualifications	124
6.5	Inspection of Work and Records.....	124
6.6	Obligations of the Contractor	125
6.7	Nondestructive Testing (NDT).....	125
	<i>Part B—Radiographic Testing (RT) of Groove Welds in Butt Joints.....</i>	<i>127</i>
6.8	Extent of Testing	127
6.9	General.....	127
6.10	RT Procedure	127
6.11	Acceptability of Welds.....	134
6.12	Examination, Report, and Disposition of Radiographs	134
	<i>Part C—Ultrasonic Testing (UT) of Groove Welds</i>	<i>134</i>
6.13	General.....	134
6.14	Extent of Testing	134
6.15	UT Equipment.....	134
6.16	Reference Standards	136
6.17	Equipment Qualification.....	140
6.18	Calibration for Testing	140
6.19	Testing Procedures	141

6.20	Preparation and Disposition of Reports	146
6.21	Calibration of the UT Unit with IIW or Other Approved Reference Blocks.....	146
6.22	Equipment Qualification Procedures	148
6.23	Flaw Size Evaluation Procedures.....	149
6.24	Scanning Patterns.....	149
6.25	Examples of dB Accuracy Certification	150
	<i>Part D—Weld Acceptance Criteria</i>	150
6.26	Quality of Welds	150
7.	Stud Welding.....	155
7.1	Scope.....	155
7.2	General Requirements.....	155
7.3	Mechanical Requirements.....	155
7.4	Workmanship	156
7.5	Technique	157
7.6	Stud Application Qualification Requirements	158
7.7	Production Control.....	159
7.8	Inspection Requirements.....	160
8.	Statically Loaded Structures (No Applications within this code).....	161
9.	Welded Steel Bridges <u>(The provisions of this section in ANSI/AASHTO/AWS [for D1.5-96] have been distributed throughout AASHTO/AWS [for D1.5M/D1.5:2002])</u>	
10.	Tubular Structures (No Applications within this code)	165
11.	Strengthening and Repairing Existing Structures (No Applications within this code)	167
12.	AASHTO/AWS Fracture Control Plan (FCP) for Nonredundant Members.....	169
12.1	General Provisions	169
12.2	Definitions.....	169
12.3	Contract Documents	169
12.4	Base Metal Requirements	170
12.5	Welding Processes	170
12.6	Consumable Requirements	170
12.7	Welding Procedure Specification (WPS).....	174
12.8	<u>Certification and Qualification</u>	174
12.9	As-Received Inspection of Base Metal.....	175
12.10	Thermal Cutting	175
12.11	Repair of Base Metal	175
12.12	Straightening, Curving, and Cambering	175
12.13	Tack Welds and Temporary Welds.....	176
12.14	Preheat and Interpass Temperature Control.....	176
12.15	Postweld Thermal Treatments	176
12.16	Weld Inspection	178
12.17	Repair Welding	179
	<i>Annexes—Mandatory Information</i>	
	<i>Annex I—Effective Throat</i>	183
	<i>Annex II—Effective Throats of Fillet Welds in Skewed T-Joints</i>	185
	<i>Annex III—Suggested Sample Welding Forms</i>	187
	<i>Annex IV—Flatness of Girder Webs—Bridges</i>	195
	<i>Annex V—Terms and Definitions</i>	201
	<i>Annex VI—Manufacturer’s Stud Base Qualification Requirements</i>	209
	<i>Annex VII—Part A—Qualification and Calibration of the UT Unit with Other Approved Reference Blocks</i>	213
	<i>Part B—UT Equipment Qualification Procedures</i>	215
	<i>Annex VIII—Guidelines on Alternative Methods for Determining Preheat</i>	223

Annexes—Nonmandatory Information

Annex A—Weld Quality Requirements for Tension Joints 233

Annex B—Description of Common Weld and Base Metal Discontinuities..... 235

Annex C—Short Circuiting Transfer 245

Annex D—Guidelines for Preparation of Technical Inquiries for the Joint AASHTO/AWS Subcommittee on Bridge Welding 247

Annex E—Reference Documents 249

Annex F—Location of Section 9 Provisions of 1996 Edition in AASHTO/AWS D1.5M/D1.5:2002 251

Commentary on Bridge Welding Code 253

C1. General Provisions 259

C2. Design of Welded Connections..... 263

C3. Workmanship 273

C5. Qualification 295

C6. Inspection..... 315

C7. Stud Welding..... 331

C12. AASHTO/AWS Fracture Control Plan (FCP) for Nonredundant Members..... 337

Index 355

List of Tables

Table		Page No.
2.1	Minimum Fillet Weld Size	9
2.2	Minimum Effective Weld Size for PJP Groove Welds.....	44
3.1	Limits on Acceptability and Repair of Cut Edge Discontinuities of Material	51
3.2	Camber Tolerance for Typical Girder.....	56
3.3	Camber Tolerance for Girders without a Designed Concrete Haunch.....	56
4.1	Matching Filler Metal Requirements for WPSs Qualified in Conformance with 5.12.....	64
4.2	Matching Filler Metal Requirements for WPSs Qualified in Conformance with 5.13.....	67
4.3	Filler Metal Requirements for Exposed Bare Application of M270M (M270) (A709M [A709]) Gr. 345W (50W) Steel.....	69
4.4	Minimum Preheat and Interpass Temperature, °C [°F].....	70
4.5	Minimum Holding Time	71
4.6	Alternate Stress-Relief Heat Treatment	71
4.7	Allowable Atmospheric Exposure of Low-Hydrogen SMAW Electrodes.....	72
5.1	WPS Qualification Requirements for Consumables	83
<u>5.2</u>	<u>WPS Qualification or Prequalification Options</u>	<u>88</u>
5.3	PQR Essential Variable Changes for WPSs Qualified per 5.13.3.....	96
5.4	Additional PQR Essential Variable Changes Requiring WPS Requalification for ESW or EGW	99
5.5	Required Number of Test Specimens—WPS Qualification.....	100
5.6	Welder Qualification—Type and Position Limitations	107
5.7	Number and Type of Specimens and Range of Thickness Qualified—Welder and Welding Operator Qualification.....	109
6.1	Hole-Type IQI Requirements	127
6.1A	Wire IQI Requirements	128
6.2	Testing Angle	142
6.3	UT Acceptance-Rejection Criteria—Tensile Stress	144
6.4	UT Acceptance-Rejection Criteria—Compressive Stress.....	145
7.1	Mechanical Property Requirements for Studs.....	156
7.2	Minimum Fillet Weld Size for Small Diameter Studs	158
12.1	CVN Test Values of Weld Metal with Matching Strength	171
12.2	Tack Weld Requirements.....	176
12.3	M270M (M270) (A709M [A709]) Gr. 250 (36), 345 (50) Minimum Preheat and Interpass Temperatures, °C [°F]	177
12.4	M270M (M270) (A709M [A709]) Gr. 345W (50W), 485W (70W) Minimum Preheat and Interpass Temperatures, °C [°F]	177
12.5	M270M (M270) (A709M [A709]) Gr. 690 (100), 690W (100W) Minimum and Maximum Preheat/Interpass Temperatures, °C [°F].....	177
II-1	Equivalent Fillet Weld Leg Size Factors for Skewed T-Joints, R = 0	185
VIII-1	Susceptibility Index Grouping as Function of Hydrogen Level “H” and Composition Parameter P_{cm}	231
VIII-2	Minimum Preheat and Interpass Temperatures for Three Levels of Restraint.....	231
B-1	Common Types of Discontinuities	236
<u>C-1</u>	<u>Typical Current Ranges for Short Circuiting Transfer Gas Metal Arc Welding (GMAW-S) of Steel ..</u>	<u>245</u>

List of Figures

Figure		Page No.
2.1	Filler Plates Less Than 6 mm [1/4 in.] Thick.....	8
2.2	Filler Plates 6 mm [1/4 in.] or Thicker.....	8
2.3	Details for Fillet Welds.....	9
2.4	Details of Welded Joints for CJP Groove Welds	12
2.5	Details of Welded Joints for PJP Groove Welds	32
2.6	Fillet Welds on Opposite Sides of a Common Plane of Contact.....	44
2.7	Transition of Thickness at Butt Joints of Parts Having Unequal Thickness	46
2.8	Transition of Width at Butt Joints of Parts Having Unequal Width.....	47
3.1	Discontinuities in Cut Plate.....	51
3.2	Workmanship Tolerances in Assembly of Groove Welded Joints.....	54
3.3	Acceptable and Unacceptable Weld Profiles.....	58
4.1	Weld Bead in Which Depth and Width Exceed the Width of the Weld Face.....	74
5.1	WPS Qualification or Pretest—Test Plate A	85
5.2	WPS Verification—Test Plate B.....	86
5.3	Weld Soundness Test Plate for Details Not Conforming to Figure 2.4 or Figure 2.5— Test Plate C.....	87
5.4	Positions of Fillet Welds.....	89
5.5	Positions of Groove Welds	90
5.6	Position of Test Plates for Groove Welds	91
5.7	Position of Test Plates for Fillet Welds	92
5.8	Fillet Weld Soundness Test (Macroetch) for WPS Qualification—Test Plate D	94
5.9	Standard Round All-Weld-Metal Tension Specimen	101
5.10	Reduced Section Tension Specimen	101
5.11	Side-Bend Specimen	102
5.12	Face- and Root-Bend Specimen	102
5.13	CVN Test Specimen—Type A	103
5.14	Guided Bend Test Jig	104
5.15	Alternative Wraparound Guided Bend Test Jig.....	105
5.16	Alternative Roller-Equipped Guided Bend Test Jig for Bottom Ejection of Test Specimen	105
5.17	Test Plate for Unlimited Thickness—Welder Qualification.....	110
5.18	Optional Test Plate for Unlimited Thickness—Horizontal Position—Welder Qualification	110
5.19	Test Plate for Limited Thickness—All Positions—Welder Qualification	111
5.20	Optional Test Plate for Limited Thickness—Horizontal Position—Welder Qualification	111
5.21	Fillet-Weld-Break and Macroetch Test Plate—Welder Qualification—Option 1	112
5.22	Fillet Weld Root-Bend Test Plate—Welder Qualification—Option 2	113
5.23	Plug Weld Macroetch Test Plate—Welder Qualification	114
5.24	Test Plate for Unlimited Thickness—Welding Operator Qualification	115
5.25	Butt Joint for Welding Operator Qualification—ESW and EGW.....	116
5.26	Fillet-Weld-Break and Macroetch Test Plate—Welding Operator Qualification—Option 1	117
5.27	Fillet Weld Root Bend Test Plate—Welding Operator Qualification—Option 2	118
5.28	Fillet-Weld-Break Specimen—Tack Welder Qualification	119
5.29	Method of Rupturing Specimen—Tack Welder Qualification	120
6.1A	Radiographic Identification and Hole-Type or Wire IQI Locations on Approximately Equal Thickness Joints 250 mm [10 in.] and Greater in Length.....	129

Figure	Page No.
6.1B	Radiographic Identification and Hole-Type or Wire IQI Locations on Approximately Equal Thickness Joints Less than 250 mm [10 in.] in Length 129
6.1C	Radiographic Identification and Hole-Type or Wire IQI Locations on Transition Joints 250 mm [10 in.] and Greater in Length 130
6.1D	Radiographic Identification and Hole-Type or Wire IQI Locations on Transition Joints Less than 250 mm [10 in.] in Length..... 130
6.1E	Hole-Type IQI Design 131
6.1F	Wire-Type IQI 132
<u>6.2</u>	<u>RT Edge Block Placement</u> 135
6.3	Transducer Crystal 136
6.4	Qualification Procedure of Search Unit Using IIW Reference Block..... 136
6.5A	International Institute of Welding (IIW) UT Reference Blocks 137
6.5B	Other Approved UT Reference Blocks 138
6.6	Transducer Positions (Typical)..... 147
6.7	Plan View of UT Scanning Patterns 150
<u>6.8</u>	<u>Weld Quality Requirements for Discontinuities Occurring in Tension Welds (Limitations of Porosity and Fusion Discontinuities) 152</u>
<u>6.9</u>	<u>Weld Requirements for Discontinuities Occurring in Compression Welds (Limitations of Porosity or Fusion Type Discontinuities)..... 153</u>
7.1	Dimension and Tolerances of Standard-Type Shear Connectors 156
7.2	Typical Tension Test Fixture 157
7.3	Torque Testing Arrangement and Table of Testing Torques 159
VI-1A	Bend Testing Device 211
VI-1B	Suggested Type of Device for Qualification Testing of Small Studs 211
VII-1	Example of the Use of Form VII-8 UT Unit Certification 216
VII-2	Example of Form VII-9..... 217
VII-3	Example of the Use of Form VII-9 218
VII-4	Example of Form VII-10..... 219
VII-5	Example of the Use of Form VII-10 220
VII-6	Form VII-11—Report of UT of Welds..... 221
VIII-1	Zone Classification of Steels..... 225
VIII-2	Critical Cooling Rate for 350 VH and 400 VH..... 226
VIII-3	Charts to Determine Cooling Rates for Single-Pass Submerged Arc Fillet Welds 227
VIII-4	Relation Between Fillet Weld Size and Energy Input..... 230
B-1	Weld in Butt Joint..... 237
B-2	Weld in Corner Joint..... 238
B-3	Weld in T-Joint 239
B-4	Weld in Lap Joint 240
B-5	Single-Pass Fillet Weld in T-Joint 241
B-6	Single-V-Groove Weld in Butt Joint 242
C-1	Oscillograms and Sketches of Short Circuiting Arc Metal Transfer..... 246
Commentary Figures	
C-3.1	Examples of Unacceptable Reentrant Corners..... 277
C-3.2	Examples of Good Practice for Cutting Copos 278

List of Forms

Form		Page No.
III-1	Certificate of Conformance to Requirements for Welding Electrodes.....	188
III-2	Sample Welding Procedure Specification	189
III-3	Procedure Qualification Record (PQR) for Qualification, Pretest, and Verification Results.....	190
III-4	Welder and Welding Operator Qualification Record	191
III-5	Report of Radiographic Examination of Welds	192
III-6	Report of Magnetic Particle Examination of Welds.....	193

Bridge Welding Code

1. General Provisions

1.1 Application

1.1.1 This code covers welding fabrication requirements applicable to welded highway bridges. It is to be used in conjunction with the *AASHTO Standard Specification for Highway Bridges* or the *AASHTO LRFD Bridge Design Specifications*.

The code is not intended to be used for the following:

- (1) Steels with a minimum specified yield strength greater than 690 MPa [100 ksi]
- (2) Pressure vessels or pressure piping
- (3) Base metals other than carbon or low alloy steels
- (4) Structures composed of structural tubing

Fabrication of structures or components not specifically addressed by this code shall be performed in conformance with the special provisions of the contract or in conformance with the written directives of the Engineer who may choose to reference an alternate applicable welding standard.

1.1.2 The fundamental premise of the code is to provide general stipulations applicable to any routine bridge situation. Acceptance criteria for production welds different from those described in the code may be used for a particular application, provided they are suitably documented by the proposer and approved by the Engineer.

Such alternate acceptance criteria may be based upon evaluation of suitability for service using past experience, experimental evidence, or engineering analysis considering material type, service load effects, and environmental factors.

1.1.3 The term *Engineer* as used in this code shall mean the State Bridge Engineer, or the Bridge Engineer's designated representative. The Engineer acts on behalf of the State or Owner and unless otherwise specified, shall be the Owner's official representative. All references to

acceptance or approval shall mean acceptance or approval by the Engineer.

1.1.4 The term *Contractor* as used in this code indicates the party responsible for performing the work as required by the contract documents. The term Contractor is used collectively to mean contractor, manufacturer, fabricator, erector, or other party performing the work.

1.2 Base Metal

1.2.1 Specified Base Metal. The contract documents shall designate the specification and classification of base metals to be used.

1.2.2 Approved Base Metals. Unless otherwise specified, base metals to be welded under this code shall meet the requirements of the latest edition of AASHTO M270M (M270) (ASTM A 709M [A 709]) for the grade of steel shown on the plans or described in the specifications. All Grade 345 (50) steel that is to be welded shall be Type 1, 2, or 3. Other steels may be approved by the Engineer. Thickness limitations shall not apply to bearing components.

M270M (M270) steels of a designated grade are essentially the same as ASTM A 709M (A 709) steels of the same grade. A 709M (A 709) may be used as a reference and a guide to other ASTM "referenced documents;" however, when there is a difference, the provisions of M270M (M270), including the documents referenced in M270M (M270), shall govern. The provisions of this code are not intended for use with steels having a minimum specified yield strength over 690 MPa [100 ksi].

1.2.3 Thickness Limitations. The provisions of this code do not apply to welding base metals less than 3 mm [1/8 in.] thick. Where base metals thinner than 3 mm